

PRODUCT DATA SHEET

SikaWrap®-117 C Pre-saturated

Carbon fiber fabric for structural strengthening

PRODUCT DESCRIPTION

SikaWrap®-117 C Pre-saturated is a unidirectional carbon fiber fabric pre-saturated to form a carbon fiber reinforced polymer (CFRP) used to strengthen structural concrete elements.

USES

Load Increases

- Increased live loads
- Increased traffic volumes on bridges
- Installation of heavy machinery in industrial buildings
- Vibrating structures
- Changes of building utilization

Seismic Strengthening

- Column wrapping
- Masonry walls

Damage to Structural Parts

- Aging of construction materials
- Vehicle impact
- Fire
- Blast resistance

Change in Structural System

- Removal of walls or columns
- Removal of slab sections for openings

Design or Construction Defects

- Insufficient reinforcements
- Insufficient structural depth

CHARACTERISTICS / ADVANTAGES

- Used for shear, confinement or flexural strengthening
- Flexible, can be wrapped around complex geometries
- High Strength
- Light Weight
- Non-corrosive
- Alkali Resistant
- Low aesthetic impact

PRODUCT INFORMATION

Fiber Type

Primary Fiber Direction: 0°F (unidirectional)
Color: Black

Packaging

Rolls: 24 in. x 30 ft.; Box of 2 rolls

Shelf Life	1 year in original packaging at recommended storage conditions
Storage Conditions	Store dry at 40°F - 95°F (4° - 35°C)
Dry Fibre Density	0.065 lbs./in ³ (1.8 g/cc)
Mass per Unit Length	9 oz. / sq. yd. (300 g/m ²)

TECHNICAL INFORMATION

Nominal Ply Thickness	Cured Properties:		
	Avg. Ultimate Value	Design Value	
	0.019 psi	0.018 psi	
	0.48 MPa	0.48 MPa	
Tensile Strength	5.5 x 10 ⁵ psi (3,793 MPa)		
	Cured Properties:		
	Avg. Ultimate Value	Design Value	(ASTM D-3039)
	119,770 psi	(f*fu) 93,662* psi	(ASTM D-7565)
	825 MPa	645* MPa	
	* Average ultimate value minus 3 standard deviations		
Tensile Modulus	34 x 10 ⁶ (234,500 MPa)		
	Cured Properties:		
	Avg. Ultimate Value	Design Value	(ASTM D-3039)
	-	(ET) 8,973,997 psi	(ASTM D-7565)
	-	61,873 MPa	
Tensile % Elongation	1.5%		
	Cured Properties:		
	Avg. Ultimate Value	Design Value	(ASTM D-3039)
	1.22 psi	(ε*fu) 1.04* psi	(ASTM D-7565)
	1.22 MPa	1.04* MPa	
	* Average ultimate value minus 3 standard deviations		
Tensile Resistance	Cured Properties:		
	Avg. Ultimate Value	Design Value	
	5.17 kips/in. width psi	1.78 kips/in. width* psi	
	-	-	
	* Average ultimate value minus 3 standard deviations		
Tensile Stiffness	Cured Properties:		
	Avg. Ultimate Value	Design Value	
	-	170.5 kips/in. width psi	
	-	-	

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Surface must be clean and sound. It may be dry or damp, but free of standing water and frost. Remove dust, laitance, grease, curing compounds, impregnations, waxes, foreign particles, disintegrated materials and other bond inhibiting materials from the surface. Consult the current product data sheets for

Sikadur 330/Sikadur 340/Sikadur 345 for additional information on surface preparation.

Existing uneven surfaces must be filled with an appropriate repair mortar. The adhesive strength of the concrete must be verified after surface preparation by random pull-off testing (ASTM D-4541) at the discretion of the engineer. Minimum tensile strength, 200 psi (1.4 MPa) with concrete substrate failure.

Preparation Work: Concrete - Blast clean, shot-blast or use other approved mechanical means to provide a roughened, open-textured surface. Round all corners to

1/2" radius in certain "contact critical" applications and at the engineer's discretion, a thorough cleaning of the substrate using low pressure sand or water blasting may be sufficient.

APPLICATION METHOD / TOOLS

Prior to placing the fabric, the concrete surface is primed and sealed using either Sikadur 330, Sikadur 340 or Sikadur 345. In either case, installation of this system should be performed only by a specially trained contractor.

Tooling & Finishing

Fabric can be cut to appropriate lengths by using a commercial quality heavy duty scissor. Since the dull or worn cutting implements can damage, weaken or fray the fabric, their use should be avoided.

Open Time: 2 hrs. after foil is opened

LIMITATIONS

- System is a vapor barrier. Concrete should not be fully encapsulated in areas of freeze/thaw.
- Design calculations must be made and certified by an independent licensed professional engineer.
- Do not place carbon fiber in direct contact with steel. Must be isolated (e.g. glass fabric) to protect against corrosion.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
SikaWrap®-117 C Pre-saturated
March 2020, Version 01.03
020206020050000005

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

SikaWrap-117CPre-saturated-en-US-(03-2020)-1-3.pdf

