

## PRODUCT DATA SHEET

# Sikadur<sup>®</sup>-42 Grout-Pak PT

Pre-proportioned, epoxy, anchorage protection system

### PRODUCT DESCRIPTION

Sikadur<sup>®</sup>-42 Grout-Pak PT is a 3-component, 100 % solids, moisture-tolerant, epoxy anchorage protection system.

### USES

Sikadur<sup>®</sup>-42 Grout-Pak PT may only be used by experienced professionals.

- To protect the anchorages of post-tensioning tendons or bars (i.e. pour-back box) on segmental bridge projects.

### CHARACTERISTICS / ADVANTAGES

- Ready to mix, pre-proportioned kit.
- Excellent adhesion.
- Impermeable and resistant to chemicals, corrosion, impact and stress.
- Moisture-tolerant.
- Low heat development/low peak exothermic system for large pours.
- High compressive strength.
- Long working time.
- High vibration resistance.
- Fast strength gain.
- Minimal shrinkage/expansion.
- High effective bearing area.
- Good flowability.

### PRODUCT INFORMATION

<b>Packaging</b>	0.5 cu. ft. kit consists of epoxy resin (Component 'A' and 'B') and 50 lb. aggregate. (Component 'C') in a multi-wall bag.
<b>Color</b>	Dark Gray
<b>Shelf Life</b>	2 years in original, unopened containers.
<b>Storage Conditions</b>	Store dry at 40–95°F (4–35°C). Condition material to 75–85 °F (24–29 °C) before using. Component 'C' must be kept dry.

## TECHNICAL INFORMATION

Compressive Strength	40 °F (5 °C)	73 °F (23 °C)	90 °F (32 °C)	(ASTM C-579) 50 % R.H.
	8 hours	-	-	
16 hours	-	10,000 psi (68.9 MPa)	13,000 psi (89.6 MPa)	
1 day	-	11,000 psi (75.8 MPa)	14,000 psi (96.5 MPa)	
3 days	6,500 psi (44.8 MPa)	14,200 psi (97.9 MPa)	15,000 psi (103.4 MPa)	
7 days	7,200 psi (49.6 MPa)	15,000 psi (103.4 MPa)	15,000 psi (103.4 MPa)	
14 days	9,000 psi (62.1 MPa)	16,000 psi (110.4 MPa)	16,500 psi (113.9 MPa)	
28 days	11,000 psi (75.9 MPa)	17,000 psi (117.3 MPa)	17,500 psi (120.8 MPa)	

Material cured and tested at the temperatures indicated.

<b>Modulus of Elasticity in Compression</b>	2,600 ksi (17,940 MPa) (7 days)	(ASTM C-469) 73 °F (23 °C) 50 % R.H.
<b>Effective Bearing Area</b>	> 95 % final surface area of grout in contact with bearing plate	(ASTM C-1339)
<b>Flexural Strength</b>	3,700 psi (25.5 MPa) (7 days)	(ASTM C-580) 73 °F (23 °C) 50 % R.H.
<b>Modulus of Elasticity in Flexure</b>	1,400 ksi (9,655 MPa) (7 days)	(ASTM C-580) 73 °F (23 °C) 50 % R.H.
<b>Tensile Strength</b>	2,200 psi (15.1 MPa) (7 days)	(ASTM C-307) 73 °F (23 °C) 50 % R.H.
<b>Tensile Adhesion Strength</b>	Bond Strength to Concrete (wet cure) 3,100 psi (21.3 MPa) (7 days) Bond Strength to Steel (wet cure) 3,600 psi (24.8 MPa) (7 days)	(ASTM C-882 modified) 73 °F (23 °C) 50 % R.H.
<b>Shrinkage</b>	0.022 % (7 days)	(ASTM C-531) 73 °F (23 °C) 50 % R.H.
<b>Creep</b>	1 day 0.0085 in./in. (0.0085 mm/mm) 7 days 0.0086 in./in. (0.0086 mm/mm) 28 day 0.0093 in./in. (0.0093 mm/mm)	(ASTM C-1181) 400 psi (2.7 MPa) 140 °F (60 °C), 50 % R.H.
<b>Thermal Compatibility</b>	Passes test (5 cycles)	(ASTM C-884) 73 °F (23 °C) 50 % R.H.

<b>Coefficient of Thermal Expansion</b>	73–212 °F (23–100 °C)	19.2 x 10 <sup>-6</sup> in./in./°F (10.0 x10 <sup>-6</sup> mm/mm/°C)	(ASTM C-531)
	0–160 °F (-18–71 °C)	12.6 x 10 <sup>-6</sup> in./in./°F (6.8 x10 <sup>-6</sup> mm/mm/°C)	
<b>Heat Deflection Temperature</b>	[fiber stress loading = 264 psi (1.8 MPa)] (7 days)		(ASTM D-648) 125 °F (52 °C) 50 % R.H.
<b>Water Absorption</b>	0.04 % (7 days)		(ASTM C-413) (2-hour boil) 73 °F (23 °C) 50 % R.H.

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	Component A : B : C = 3.6 : 1 : 34 by weight Solid / liquid = 7.4 : 1 by weight	
<b>Peak Exotherm</b>	<b>Specimen Size Tested</b> 13 in. x 10 in. x 6 in. (330 mm x 254 mm x 152 mm)	(ASTM D -2471) 118 °F (48 °C)
<b>Pot Life</b>	Approximately 90 minutes Gel Time: Approximately 3.25 hrs.	(ASTM D-2471) 73 °F (23 °C) 50 % R.H.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

Concrete must be older than 28 days (dependent on minimum strength requirements).

The substrate surface (all types) must be clean, dry and free from contaminants such as dirt, oil, grease, existing surface treatments and coatings, etc.

Steel substrates must be de-rusted to a standard equivalent to Sa 2.5.

The substrate must be sound, and all loose particles must be removed. Substrate must be dry or mat damp and free from any standing water, ice, etc.

### SUBSTRATE PREPARATION

Substrate and other contact areas must be clean, sound, and free of standing water. Remove dust, laitance, oils, grease, curing compounds, waxes, impregnations, foreign particles, coatings and disintegrated materials by mechanical means (i.e. sandblasting, bush hammering). Sandblast metal contact surfaces to a commercial white finish for maximum adhesion. Apply grout immediately to prevent re-oxidizing. Concrete substrate shall have reached its desired strength [3,000 psi (20.7 MPa) minimum] and must be dimensionally stable.

### MIXING

Pour the entire contents of Components 'A' & 'B' into an appropriate mixing vessel (e.g. 5 gal. bucket) and mix for 30 seconds with a 1/2 in. Jiffy mixing paddle (5 in. blade

diameter) on a low-speed (400–600 rpm) 3/4 in. drive rotary drill, taking care not to entrain air during mixing. It is critical to the performance of the grout that there be no appreciable air bubbles in the resin. Slowly add the entire contents of Component 'C' and mix until uniformly blended (approx. 5 minutes).

### APPLICATION METHOD / TOOLS

Pour the mixed epoxy grout into the prepared forms from one side only to eliminate air entrapment. Pour back box should have vent holes around periphery to prevent air pockets from developing. Maintain the liquid head to ensure intimate contact with the pour-back box. Plungers may be used to ease placement. Place sufficient epoxy grout in the forms to rise slightly above the underside of the base plate. Grout depth of 1 in. (25 mm) minimum required.

**Forming:** The flowable consistency of the epoxy grout system requires the use of forms to contain the material. In order to prevent leakage or seepage, completely seal all forms. In applications where forms will be stripped, apply polyethylene film or bond breaker to all forms to prevent adhesion of the grout. Prepare form work to maintain a 2 in. (50 mm.) liquid head to facilitate placement. A grout box that can be attached to the form will enhance the grout flowability. In base plate applications, projected anchor bolts should be wrapped with neoprene foam rubber (or similar) to prevent grout from adhering to the bolts. The use of expansion joints is recommended on large pours to minimize the potential for cracking in the epoxy grout [maximum 3–4 ft.

(0.9–1.2 m.) spacing in each direction].

## LIMITATIONS

- Minimum substrate and ambient temperature should be 40 °F (5 °C).
- Do not thin. Addition of solvents will prevent proper cure.
- Material is a vapor barrier after cure.
- Minimum grout depth should be 1 in. (25 mm.). Maximum grout depth should be 12 in. (305 mm).
- Anchorage pour-back box should be shielded from direct sunlight and rain for a minimum of 24 hours before epoxy grouting, and after grouting until tack free.
- Component 'C' must be kept dry.
- Cold material may require churning, rodding and pushing during placement.
- For applications requiring good self-leveling and better flow capabilities, use Sikadur® 42, Grout-Pak (standard formulation - product code 0335-30N).
- For proper seating in base plate applications, allow grout to rise above the bottom of the base plate.
- Do not batch. Mix complete units.
- Not an aesthetic product. Color may alter due to variations in lighting and/or UV exposure.

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## OTHER RESTRICTIONS

See Legal Disclaimer.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

### Sika Corporation

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

### Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



### Product Data Sheet

Sikadur®-42 Grout-Pak PT  
March 2020, Version 01.02  
020202010010000024

Sikadur-42Grout-PakPT-en-US-(03-2020)-1-2.pdf

