



Sikaflex® Concrete Fix

One-component, polyurethane sealant



Neutral cure silicone for sealing expansion and control joints. Ideal for window and door perimeters, skylights, conventional glazing, and other building components.



Advantages

- **Non-sag & non-staining**
- **For vertical and horizontal applications**
- **Water immersible after cure**
- **Paintable, stainable, sandable**
- **Will not shrink or crack**
- **Excellent adhesion to aging and weathering**
- **Exceptional cut and tear resistance**

Typical Data

Shelf Life : 1 year in original unopened packaging

Storage Conditions : Store at 40°-95°F (4°-35°C).

Condition material to 65°-75°F (18°-24°C) before using.

Color : Gray

Application Temperature : -40°F -100°F .

Sealant should be installed when joint is at midrange of its anticipated movement.

Service Range : -40° to 170°F.

Curing Rate : Tack-free time (Meets ASTM C-920) Final cure : 7 days

Shore A Hardness : Meets ASTM C-920

Adhesion in Peel (ASTM C 794) :

Concrete : Meets ASTM C-920

Aluminium : Meets ASTM C-920

Glass : Meets ASTM C-920

Weathering Resistance : Excellent



SIKA CORPORATION
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225
Toll Free : 800.933.SIKA
usa.sika.com

SIKA CANADA INC.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

SIKA MEXICANA S.A. DE C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537

BUILDING TRUST

