

## PRODUCT DATA SHEET

# Sikagard<sup>®</sup>-515 Elastomeric

100% Acrylic, Highly Flexible Elastomeric coating

### PRODUCT DESCRIPTION

Sikagard<sup>®</sup>-515 Elastomeric is a highly flexible, crack bridging, vapor permeable protective and decorative coating for concrete, masonry, EIFS, and Stucco. Sikagard<sup>®</sup>-515 Elastomeric is available in light or dark tint bases and can be integrally colored with Colorfast pigments.

### USES

Exterior coating for

- EIFS
- Masonry
- Concrete
- Stucco
- Previously applied acrylic or elastomeric textured finishes

### CHARACTERISTICS / ADVANTAGES

- High flexibility and elongation
- Can bridge hairline cracks
- Vapor permeable
- UV resistant
- Resistant to mildew
- Good surface hardening capability
- Can be applied by brush, roller, or spray applications
- Water base VOC compliant
- Meets SCAQMD Rule 1113 when colored with Colorfast pigments

### PRODUCT INFORMATION

<b>Chemical Base</b>	<ul style="list-style-type: none"> <li>▪ Binder base: 100% Acrylic Elastomeric polymer</li> <li>▪ Pigment base: Titanium Dioxide.</li> <li>▪ Water base: VOC compliant</li> </ul>
<b>Packaging</b>	55 lb (25.4 kg) net weight in plastic pails
<b>Appearance / Color</b>	Factory tinted to desired color. Flat non-gloss smooth finish.
<b>Shelf Life</b>	15 months from date of manufacture in original, unopened container.
<b>Storage Conditions</b>	Store dry at 45–95 °F (7–35 °C). Condition material to 60–75 °F (15–24 °C) before using. Protect from direct sunlight and freezing at all times. If frozen, discard. Do not stack more than 3 pails high.
<b>Density</b>	11.94 lb/gal at 68°F
<b>pH-Value</b>	8.0-10.0

Solid content by weight	68%	
Solid content by volume	54%	
Elongation at Break	473%	(ASTM D412)
	1/8" diameter through 180 degrees at -30°F	Flexibility (ASTM D522)
Tensile Strength	200 psi	(ASTM D412)
Tensile Adhesion Strength	>300 psi	(ASTM D4541)
Resistance to Weathering	Accelerated Weathering	(ASTM G153)
	Pass at 2000 hours	
	Mildew-Fungus Resistance	(Federal Tests 141, 6241)
	Pass at 28 days	
Mildew Resistance	No growth	(MIL 810 B508)
	Salt Fog Resistance	(ASTM B117)
Pass at 500 hours		
Water Vapor Transmission	Permeable	(ASTM E96)

## APPLICATION INFORMATION

### Coverage

Theoretical yield per coat for :  
Porous surfaces: 50 - 75 ft<sup>2</sup> (4.6 - 7 m<sup>2</sup>)/gal/coat.  
Smooth, filled surfaces: 140 - 160 ft<sup>2</sup> (13 - 14.8 m<sup>2</sup>)/gal/coat.  
Recommended 'wet' film thickness: 10 mils (0.25 mm)/coat. Recommended 'dry' film thickness: 6 mils (0.15 mm)/coat. Normal coating system is two coats at a total dry film thickness of 12 mils\*. Consumption is dependent on porosity of substrate. In addition, allowance must be made for surface profile, unavoidable variation in applied film thickness, loss and waste.  
\*One coat coverage recommended only for recoating over existing coatings

### Waiting / Recoat Times

Waiting Time (between coats) and Curing Rates	45°F	68°F	85°F
Sikagard®-552W Primer + Sikagard®-515 Elastomeric (50% RH)	—	4 hours	2 hours
Sikagard®-515 Elastomeric (50% RH)	—	8 hours	4 hours
Rain Resistant (75% RH)	—	12 hours	8 hours

Note: Overcoating existing coatings will increase waiting times by 100%

## APPLICATION INSTRUCTIONS

### SURFACE PREPARATION

All surfaces to be coated must be dry, clean, sound, and frost free with curing compound residues and any other

foreign matter removed. An open textured sandpaper like surface is ideal (CSP-3). Where necessary, surfaces should be prepared mechanically by blast cleaning or high speed pressure water jetting. Allow adequate time for drying. For previously coated surfaces, all loose and chalking paint must be removed, and glossy surfaces

dulled. A mock up shall be performed to ensure adhesion over any previously coated substrates. Bug holes, cracks or irregularities of substrate should be filled and leveled with SikaTop®, SikaRepair®, SikaQuick® or acrylic surface fillers as appropriate. Moving cracks shall be routed and sealed with a polyurethane sealant before coating.

#### PRIMING

All porous areas or concrete with excessive porosity should be primed using Sikagard® 552W Primer or SikaLatex® R to allow easy application of Sikagard®-515 Elastomeric.

#### MIXING

Stir the coating to ensure uniformity using a slow speed (400-600 rpm) drill and 1/2" jiffy style mixing paddle. To minimize color variation when using multiple units, blend two pails of Sikagard®-515 Elastomeric. Use one pail and maintain the second pail to repeat this procedure (boxing) for the entire application.

#### APPLICATION

Any areas of glass or other surfaces should be masked. Recommended application temperatures (ambient and substrate) 45°-95°F (7°-35°C). Sikagard®-515 Elastomeric can be applied by brush, roller (3/8" Nap Roller recommended), or spray over entire area moving in one direction. Sikagard®-515 Elastomeric exhibits good surface coverage in single applications. However, for uncoated, unprimed surfaces of concrete, masonry or stucco, two coats of Sikagard®-515 Elastomeric are usually required to obtain adequate hiding and performance. At lower temperatures and high humidity, waiting time to recoat will be prolonged. At higher temperatures, work carefully to maintain a wet edge. As with all coatings, job site mock-ups should always be completed to confirm acceptability of workmanship, material and aesthetics.

NOTE: To achieve a dry film thickness of 12 mils, two coats should be anticipated. For maximum adhesion, (especially on porous substrates) the use of Sikagard® 552W is recommended. Sikagard® 552W primer can be applied by brush or roller. Brushing provides more even and pore free coats and better penetration.

#### CLEANING OF TOOLS

Water soluble prior to drying. Clean tools and containers with water prior to drying. Cured material can be removed mechanically.

#### LIMITATIONS

- Ambient and surface temperature must be 45°F (7°C) or higher during application and drying time.
- Provide supplemental heat and protection from precipitation as needed.
- Use only on surfaces that are sound, clean, dry, and free from any residue that might affect the ability of

the Sikagard®-515 Elastomeric coating to bond to the surface.

- Allow substrate sufficient time to dry after rain or other inclement conditions.
- Minimum age of concrete prior to the application is 14 days, depending on curing and drying conditions. Moisture content must be below 5%.
- Minimum age of SikaTop®, SikaRepair®, or SikaQuick® prior to application is three days, depending on curing and drying conditions. Moisture content must be below 5%.
- Normal coating system is two coats. One coat coverage recommended only for recoating over existing coatings.
- Sikagard®-515 Elastomeric coating should not be applied at relative humidity greater than 90%, or if rain is forecast within the specified rain resistance period.
- During application, regular monitoring of the wet film thickness and material consumption is advised to ensure that the correct layer thickness is achieved.
- When over-coating existing coatings, compatibility and adhesion testing is recommended.
- Application in direct sunlight in hot weather may adversely affect aesthetics.
- Not designed for use as a vehicular traffic bearing surface.
- Product must be protected from freezing, if frozen discard.
- Not recommended for roofing.
- Sika is not responsible for color correctness after finish has been applied.

#### BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

#### OTHER RESTRICTIONS

See Legal Disclaimer.

#### ENVIRONMENTAL, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

### Sika Corporation

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

### Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



### Product Data Sheet

Sikagard®-515 Elastomeric  
March 2020, Version 01.02  
020303030070000016

Sikagard-515Elastomeric-en-US-(03-2020)-1-2.pdf

