

PRODUCT DATA SHEET

Sikagard®-550 W Elastocolor

Low-VOC Elastomeric Wall Coating

PRODUCT DESCRIPTION

Sikagard® 550W Elastocolor is a low-VOC, elastomeric, crack-bridging, anti-carbonation, acrylic protective coating. Sikagard® 550W Elastocolor provides protection to reinforced concrete from the ingress of carbon dioxide and other aggressive gasses. It offers high resistance to chlorides and other waterborne salts and excellent UV light resistance. Sikagard® 550W Elastocolor will not act as a vapor barrier and will enhance the appearance of the structure.

USES

Protective, crack-bridging coating for concrete, mortar, stucco, masonry, and exterior finishing systems subject to cracking/dynamic movement. For use on building and civil engineering structures subject to cracking or as the top coat in complete repair and protection systems.

CHARACTERISTICS / ADVANTAGES

- Can bridge dynamically moving cracks.
- Excellent carbonation barrier.
- Vapor permeable.
- Provides resistance to weathering and frost.
- Crack bridging properties maintained at low temperatures.
- Excellent long term UV light resistance.
- Can be applied by brush, roller, or airless spray.
- Good color stability.
- Extremely resistant to dirt pick up and mildew.
- Non-flammable as a system.
- Easily maintained silk finish.
- Low-VOC (SCAQMD compliant)

PRODUCT INFORMATION

Packaging	5 gallon pail
Shelf Life	2 years in original unopened container
Storage Conditions	Store dry at 40°-95°F (4°-35°C) Condition material to 60°-75°F (15°-25° C) before using. Protect from freezing. If frozen discard.
Color	469 standard colors. Custom color-matching available.
Solid content by mass	62%
Solid content by volume	55%
Volatile organic compound (VOC) content	12.4 g/l

Tensile Strength		0°F (-17°C)	73°F (23°C)	(ASTM D-412) 21 days
	Strength	1100 psi	200 psi	
	Elongation at Break	225%	625%	
Crack Bridging Ability	Static	30 mils (0.75 mm)		(16 mils @ -4°F/-20°C)
	Dynamic	12 mils (0.3 mm)		
Resistance to wind-driven rain	No passage of water through coating			(TT-C-555B)
Permeability to Water Vapor	14.5 perms			(ASTM E-96)
Diffusion Resistance to Water Vapor	μ - value H2 O (diffusion coefficient)	2,146		(16 mils)
	SdH2 O (equivalent air thickness)	2.6 ft. (0.8 m)		
Lap Shear Strength	μ - value CO2 (diffusion coefficient)	214,000		(16 mils after 2000 hrs accelerated weathering)
	R (equivalent air thickness)	299 ft. (91 m)		
	Sc (Equivalent concrete thickness)	9 in. (23 cm)		
Resistance to Weathering	10,000 hrs.	Excellent, no chalking or cracking		(ASTM G-23)
Reaction to Fire	Flame Spread	5		(ASTM E-84)
	Smoke Development	5		
	Class Rating	A		
Coverage	Theoretical yield per coat: 100 ft²/gal/coat. Recommended ‘wet’ film thickness: 16 mils/coat. Recommended ‘dry’ film thickness: 8 mils/coat. Normal coating system is two coats at a total dry film thickness of 16 mils. Consumption is dependent on porosity of substrate. In addition, allowance must be made for surface profile, unavoidable variation in applied film thickness, loss and waste. Sikagard® Elastic Base Coat can be used as a first coat in a two coat system of Sikagard® 550W Elastocolor.			
Pot Life	Indefinite, provided proper care is taken in protecting the system from moisture, freezing, contamination, or evaporation			
Waiting / Recoat Times		45°F (8°C)	68°F (20°C)	85°F (30°C)
	Sikagard® 552W Primer+Sikagard® 550W	24 hrs	12 hrs	6 hrs
	Sikagard® 550W	12 hrs	8 hrs	6 hrs
	Rain resistant (at 75% R.H.)	24 hrs	4 hrs	2 hrs
(Note: Over coating old coatings will increase the waiting times by 100%)				

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

- Not designed for use as a traffic bearing surface.
- Substrates must be dry prior to application.
- Minimum age of concrete prior to application is 14 days, depending on curing and drying conditions

(moisture content must be below 5%).

- Minimum age of SikaTop®, SikaRepair®, or SikaQuick® prior to application is three days, depending on curing and drying conditions (moisture content must be below 5%).
- Allow sufficient time for substrate to dry after rain or other inclement conditions.
- Protect from freezing. If frozen, discard.
- Sikagard® 550W Elastocolor should not be applied at relative humidity greater than 90%, or if rain is forecast within the specified rain resistance period.
- Maximum crack width 1/32".
- During application, regular monitoring of the wet film thickness and material consumption is advised to ensure that the correct layer thickness is achieved. When over-coating existing coatings, compatibility and adhesion testing is recommended.
- When over-coating Sikaflex® sealants, a prime coat of Sikagard® 550W Elastocolor Accent Base Coat may be necessary over the sealant to minimize dirt pick up on cured coating.
- Do not store Sikagard® 550W Elastocolor in direct sunlight for prolonged periods.
- Strong winds can cause shrinkage if material is applied at lower temperatures.
- Ensure that the primer is thoroughly dry before over-coating to prevent formation of bubbles and blisters, particularly in warmer weather.
- Not recommended for roofing.

Recommended application temperatures (ambient and substrate) 45°-95°F (7°-35°C). Sikagard® 550W Elastocolor can be applied by brush, roller, or spray over entire area moving in one direction. Allow a minimum of two hours prior to re-coating. At lower temperatures and high humidity, waiting time will be prolonged. At higher temperatures, work carefully to maintain a wet edge. As with all coatings, job site mock-ups should always be completed to confirm acceptability of workmanship, material and aesthetics.

NOTE: To achieve a dry film thickness of 16 mils, two coats should be anticipated. For maximum adhesion, (especially on porous substrates) the use of Sikagard® 552W is recommended. Sikagard® 552W primer can be applied by brush or roller. Brushing provides more even and pore free coats and better penetration.

ENVIRONMENTAL, HEALTH AND SAFETY

SUBSTRATE PREPARATION

All surfaces to be coated must be dry, clean, sound, and frost free with curing compound residues and any other foreign matter removed. An open textured sandpaper like surface is ideal (CSP-3). Where necessary, surfaces should be prepared mechanically by blast cleaning or high speed pressure waterjetting. Allow adequate time for drying. Bug holes, cracks or irregularities of substrate should be filled and leveled with SikaTop®, SikaRepair®, SikaQuick® or acrylic surface fillers as appropriate. Cracks 1/32" or greater should be routed and sealed with a polyurethane sealant before coating.

Priming: All porous areas or concrete with excessive porosity should be primed using Sikagard® 552W Primer or SikaLatex® R to allow easy application of Sikagard® 550W Elastocolor.

MIXING

Stir the coating to ensure uniformity using a slow speed (400-600 rpm) drill and 1/2" jiffy style mixing paddle. To minimize color variation when using multiple units, blend two pails of Sikagard® 550W Elastocolor. Use one pail and maintain the second pail to repeat this procedure (boxing) for the entire application.

APPLICATION

Any areas of glass or other surfaces should be masked.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet

Sikagard®-550 W Elastocolor
August 2023, Version 01.02
020303110010000029

Sikagard-550WElastocolor-en-US-(08-2023)-1-2.pdf

