

PRODUCT DATA SHEET

Sikagard® AWB 665

(formerly MSeal AWB 665)

VAPOR PERMEABLE AIR/WATER-RESISTIVE BARRIER

PRODUCT DESCRIPTION

Sikagard® AWB 665 is a one-component, fluid-applied vapor permeable air/water-resistive barrier. This waterproof, resilient coating may be spray-, roller-, or brush-applied directly to approved above grade wall substrates. It provides excellent secondary moisture protection behind most wall claddings including brick, siding and metal panels.

USES

For use over the following exterior wall substrates: Poured concrete/unit masonry, poured concrete/unit masonry treated with Sika Thorocoat®-749 Block Filler, ASTM C1177 type sheathings, including DensGlass™ eXP™ sheathing, GlasRoc® sheathing, Securock™ glass-mat sheathing, Weather Defense™ Platinum sheathing, GreenGlass® sheathing, PermaBase™ cement-board by National Gypsum and other cement-boards (ASTM C1325 Type A Exterior), untreated Exposure I or exterior plywood sheathing (grade C-D or better), untreated Exposure I OSB, gypsum sheathing (ASTM C79/ASTM C1396), Fire resistive sheathing such as MagTec®, LP® FlameBlock®.

Do not use Sikagard® AWB 665 for below-grade applications or on surfaces subject to water immersion.

CHARACTERISTICS / ADVANTAGES

- Conforms to ICC ESR-3209
- <1% of allowable air leakage per ASTM E2357 Air Leakage of Building Assemblies Test
- Evaluated by the Air Barrier Association of America
- Meets ASTM D1970 nail sealability requirements with and without Sheathing Fabric
- Water-based, one-component, low-VOC formulation
- Nonflammable as applied. Class A Fire Rated (ASTM E84)
- Mineral oil and plasticizer free
- 180 Day UV Exposure
- 99% Drainage Efficiency per ASTM E 2273
- Meets NFPA 285 requirements when part of a tested assembly

APPROVALS / STANDARDS

- ICC-IBC, ICC-IRC, ICC-IECC, and ABAA-compliant material
- ICC-ES AC 212: Acceptance Criteria for Water-Resistive Coatings used as Water-Resistive Barriers over Exterior Sheathing
- ICC-ES AC 148: Acceptance Criteria for Flexible Flashing Materials

PRODUCT INFORMATION

Chemical Base	Sikagard® AWB 665 is based on Silica Fortified Rubber™ chemistry.
Packaging	Sikagard® AWB 665 ▪ 5-gallon pail (18.9 L) pail
Color	Light Gray

Shelf Life	Sikagard® AWB 665 has 2 years shelf life when properly stored
Storage Conditions	Store in unopened containers in a clean, dry place to protect liquid system components from freezing. Store at no less than 4 °C (40 °F) and below 49 °C (120 °F). Protect from extreme heat and direct sunlight. Do not stack pallets.
Solid content by mass	73%

TECHNICAL INFORMATION

Abrasion Resistance	Pull-Off Strength of Coatings Pass - Min. 110 kPa (15.9 psi) or substrate failure (Tested over exterior gypsum sheathing, ASTM C1177 glass-mat sheathing, cement board, OSB, plywood; PVC and galvanized flashing) (ASTM D 4541)
Tensile Strength	Tensile Strength after UV Exposure All samples meet the minimum requirement of 3.5N/mm (20 lbs/in) (ASTM D 5034, AAMA 711) Tensile Bond >103 kPa (15 psi) Tested over exterior gypsum sheathing, ASTM C1177 glassmat ASTM C1177 glass sheathing, cement board, OSB, plywood, CMU; pvc and galvanized flashing (ASTM C 297) (before & after freeze-thaw): >103 kPa (15 psi) avg; no failure of the lamina after 10 cycles freeze-thaw (Tested over various substrates) (ASTM C 297)
External Fire Performance	Radiant Heat Multi-Story Tests Passed using numerous wall assemblies. Engineering analyses are available upon request. (NFPA 268, NFPA 285)
Resistance to fire	Will not add or detract from the rating of a fire resistive wall assembly (ASTM E 119/UL 263)
Thermal Resistance	Compound Stability(Elevated Temperature) No flowing, dripping, or drop formation up to 177 °C (350 °F) (ASTM D 5147 Section 15)
UV Exposure	No cracking or bond failure to substrate (ICC-ES AC 212) No cracking or bond failure to substrate (ICC-ES AC 148)
Artificial Ageing	No cracking or bond failure to substrate (ICC-ES AC 212) No cracking or bond failure to substrate (ICC-ES AC 148)
Behavior after Artificial Weathering	Structural: No cracking at joints or interface of flashing (ASTM E 1233 Procedure A) Racking: No cracking at joints or interface of flashing (ASTM E 72) Restrained Environmental Conditioning: No cracking at joints or interface of flashing (ICC-ES AC 212)
Permeability to Water Vapor	18 Perms (grains/Hr. in Hg. ft2) at 12 mils wet film thickness (ASTM E 96 Method B) 14 Perms (grains/Hr. in Hg. ft2) at 20 mils wet film thickness
Water Penetration under Pressure	No water penetration after 90 min at 299 Pa (6.24 psf) Tested over OSB and gypsum sheathing (ASTM E 331)

	Hydrostatic Pressure Test: No water penetration at 55 cm (21.7") water column for 5 hours (AATCC 127-1985) Nail Sealability(without Sheathing Fabric) Pass - No water penetration at galvanized roofing nail penetration under 127 mm (ASTM D 1970) (5") head of water after 3 days at 4 °C (40 °F) Nail Sealability after Thermal Cycling Pass (ASTM D 1970 (Modified),AAMA 711)
Adhesion in peel	Tested over ASTM C1177 glass-mat sheathing, OSB, plywood, PVC and uncoated aluminum (ASTM D3330 Method F) After UV exposure: Pass After Accelerated Aging: Pass After Elevated Temperature Exposure: Pass After Water Immersion: Pass Resistance to Peeling: No signs of distress or failure after 24 hours of exposure at room temperature, 50 °C (122 °F), 65 °C (149 °F), 80 °C (176 °F) (AAMA 711)
Freeze-Thaw Stability	No sign of deleterious effects after 10 cycles (Tested over exterior gypsum sheathing, ASTM C1177 glass-mat sheathing, cement board, OSB, plywood) (ASTM E 2485 (Method B))
Water resistance	No sign of deleterious effects after 14-day exposure (Tested over exterior gypsum sheathing, ASTM C1177 glass-mat sheathing, cement board, OSB, plywood) (ASTM D 2247) Hydrostatic Pressure: No water penetration at 55cm (21.7") water column for 5 hours (AATCC 127-1985)
Water retention	Drainage Efficiency 99% (ASTM E 2273)
Low Temperature Bend	No cracking after bending around a 25 mm (1") mandrel after 2-hour exposure to -18 °C (0 °F) (ASTM D 1970, AAMA 711)
Air permeance	0049 l/s.m ² at 75 Pa (0.00098 cfm/ft ² at 1.57 psf) (ASTM E 2178)
Air leakage rate	0.0185 l/s.m ² at 75 Pa (0.0037 cfm/ft ² at 1.57 psf) (ASTM E 283) Air Leakage of Air Barrier Assemblies 0.0007 l/s.m ² (0.0001 cfm/ft ²) at 75 Pa (1.57 psf) positive/post conditioning (ASTM E 2178) 0.0014 l/s.m ² (0.0003 cfm/ft ²) at 75 Pa (1.57 psf) negative/post conditioning
Reaction to Fire	Class A Flame Spread (<25) Class A Smoke Developed Spread (<450) (ASTM E 84)

APPLICATION INFORMATION

Coverage	Substrate ASTM C1177 Type Sheathing: 525 ft ² (48 m ²) per pail Cement Board: 575 ft ² (53 m ²) per pail Plywood*: 295 ft ² (27 m ²) per pail Oriented Strand Board (OSB): 295 ft ² (27 m ²) per pail
-----------------	--

Concrete Masonry Units (CMU)*:

- Standard Weight 265 ft² (24 m²) per pail
- Medium Weight 180 ft² (17 m²) per pail
- Light Weight 125 ft² (12 m²) per pail

Poured Concrete*: 575 ft² (46m²) per pail

* Roll or spray/backroll for optimum coverage rate. Other application methods may provide less coverage. Actual results may vary depending on surface porosity, roughness, moisture uptake, or other factors.

Concrete/Masonry with Sika Thorocoat®-749 Block Filler: 500 ft² (46 m²) per pail

Drying Time

Allow to dry completely, typically 2 to 10 hours, before proceeding with cladding installation. Protect from rain and from temperatures less than 4 °C (40 °F) for 24 hours.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS**EQUIPMENT**

Airless spray equipment capable of spraying a minimum of 1 gallon per minute with a minimum size reversible tip of 0.019 is required. Airless equipment capable of greater deliveries can use larger tips. Tip sizes of 0.021 to 0.025 are recommended. Tip sizes greater than 0.025 provide too much material and affect the overall consumption of the material affecting the coverage rates. If pump filters are used, the minimum size of filter recommended is a 60 mesh filter. When spraying over Plywood and OSB, back rolling is recommended to completely encapsulate and create a pinhole-free application. For roller application, use a 13 mm (½") nap roller.

SUBSTRATE PREPARATION

Substrates shall be dry, clean, sound, and free of dust, release agents, paint, or other residue or coatings. Verify substrate is, free of fins or planar irregularities greater than 6.4 mm in 3 m (¼" in 10').

Unsatisfactory conditions shall be reported to the

general contractor and corrected before application of Sikagard® AWB 665.

Walls should be capped to prevent moisture and precipitation from entering the wall during construction. Limit UV and weather exposure of Sikagard® AWB 665 to a maximum of 180 days.

SURFACE PREPARATION

- Cold temperature application less than 40 °F (4 °C) down to 25 °F (-4 °C): expect extended dry time. Final air/water-resistive properties and film durability rely on temperatures rising above freezing (32 °F/0 °C)
 - Walls shall be capped to prevent moisture and precipitation from entering the wall during construction.
 - Treat expansion joints with Sikagard-540 Plus flashing membrane, and provide sufficient slack in Sikagard-540 Plus at the joint to allow for movement.
1. The substrate shall be of a type acceptable by Sika and shall be installed per substrate manufacturer's instructions and local code requirements.
 2. Rough openings and sheathing joints can be treated with Sikagard® AWB 900 Liquid Flashing Membrane.

Prior to installation of insulation and/or cladding materials, visually inspect the Sikagard® AWB 665 for voids, pinholes, surface deficiencies, etc. Repair deficiencies and areas that are not intact. Apply additional Sikagard® AWB 665 as necessary such that Sikagard® AWB 665 is free of voids, pinholes, etc. All sheathing joints, terminations, inside and outside corners must be reinforced with Sikagard-540 Plus or Sikagard® AWB 900." Reference Air/Vapor/Water-Resistive Barrier Guidelines technical bulletin for proper treatment of rough openings and sheathing joints.

MIXING

1. Use directly from original packaging or prepare in a container that is clean and free of foreign substances. Do not use a container that has contained or been cleaned with a petroleum-based product.
2. Mix Sikagard® AWB 665 with a clean, rust-free paddle and drill until thoroughly blended. Dilution of

Product Data Sheet

Sikagard® AWB 665

February 2026, Version 02.04

02189000000002006

BUILDING TRUST



- Sikagard® AWB 665 is not recommended.
3. Additives are not permitted.
 4. Close the container when not in use.
 5. Clean tools and equipment with water immediately after use. Dried material can only be removed mechanically.

APPLICATION

USING Sikagard® AWB 900

Flashing Rough Openings:

1. Apply a bead of Sikagard® AWB 900 in each corner of the rough opening and tool Sikagard® AWB 900 into corners, ensuring that corners are fully sealed. Where wood bucks are used, tool Sikagard® AWB 900 into gaps between bucks and between the building structure.
2. Apply additional Sikagard® AWB 900 in a zigzag pattern onto the head, sill, jambs, and exterior substrate. Spread Sikagard® AWB 900 evenly across the rough opening to form a uniform, continuous, void- and pinhole-free membrane with a 12-20 mil thickness. Spread Sikagard® AWB 900 before it skins, typically within 2-3 minutes of application.
3. Extend Sikagard® AWB 900 membrane minimum of 4 inches onto the exterior wall, maintaining 12-30 mil thickness.
4. Allow Sikagard® AWB 900 to skin before applying Sikagard® AWB 665 to the sheathing. Lap air/water-resistive barrier a minimum of 2 inches onto Sikagard® AWB 900, creating a continuous, monolithic air/water-resistive barrier.
5. Allow Sikagard® AWB 900 to cure before installing windows.

Sheathing Joints:

Sikagard® AWB 900 can be used to fill sheathing joints up to ½" wide.

1. Apply a thick bead of Sikagard® AWB 900 to sheathing joints.
2. Spread Sikagard® AWB 900 evenly 1-inch beyond the joint on either side. Apply 20 mils of Sikagard® AWB 900 across the sheathing joint.
3. Spot fastener heads with Sikagard® AWB 900 or Sikagard® AWB 665.
4. Allow Sikagard® AWB 900 to skin before applying a subsequent coat of air/water-resistive barrier.
5. See the Sikagard® AWB 900 product bulletin for coverages and additional product highlights.

LEGAL DISCLAIMER

- **KEEP CONTAINER TIGHTLY CLOSED**

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet

Sikagard® AWB 665
February 2026, Version 02.04
02189000000002006

- **KEEP OUT OF REACH OF CHILDREN**
- **NOT FOR INTERNAL CONSUMPTION**
- **FOR INDUSTRIAL USE ONLY**
- **FOR PROFESSIONAL USE ONLY**

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/about-us/terms-conditions-of-sale.html> or by calling 1-800-933-7452.

SikagardAWB665-en-US-(02-2026)-2-4.pdf

