

PRODUCT DATA SHEET

Sikagard® SN-40

SILANE BASED REACTIVE WATER REPELLENT PENETRATING SEALER

PRODUCT DESCRIPTION

Sikagard® SN-40 is a highly penetrating, water-repelling silane sealer. Using proven technology, the material has been formulated to provide an integral barrier against the ingress of moisture and water-borne salts into concrete and masonry.

USES

- Building facades and civil engineering structures.
- Suitable for use on exposed horizontal and vertical surfaces including bridges and parking decks, barriers, abutment walls and marine structures.
- Prevention of deterioration arising out of soluble salts and freeze/thaw damage in reinforced concrete and porous block or brickwork.
- To help prolonging the design or service life of buildings and civil engineering structures.

CHARACTERISTICS / ADVANTAGES

- Good penetration
- Solvent based emulsion, good for low temperatures
- Economic and easy to use
- Reduces capillary water absorption, protection against driving rain and splashing on vertical areas
- Reduction of absorption of aggressive or deleterious agents dissolved in water (i.e. chlorides)
- No change in water vapor permeability Increases the resistance of concrete to freeze and thaw cycles and de-icing salts
- Resistant to sea water
- Ready to use

PRODUCT INFORMATION

Chemical Base	100% reactive alkylalkoxy silane in mineral spirits
Packaging	55 gallon drum
Shelf Life	2 years in original, unopened container
Storage Conditions	Store between 0 and 85 °F (-18 and 30 °C). Condition material between 50 and 85 °F (10 and 30 °C) prior to use.
Density	6.9 lbs/gal.
Flash Point	102°F
Active Content	40%
Viscosity	<20 cps

TECHNICAL INFORMATION

Resistance to Alkalinity	85.3%	150 ft ² /gal	(Alberta BT002)
	84.2%	225 ft ² /gal	
Permeability to Water Vapor	90.2%	150 ft ² /gal	(Alberta BT001)
	84.3%	225 ft ² /gal	
Rapid Chloride Permeability	82%	1 day	(NCHRP 244 Series II)
	87%	5 days	
	90%	21 days	
	98%		(NCHRP 244 Series IV)
	53.5%	0.625-0.5" depth	(AASHTO T-259/260)
Coverage	The recommended coverage rate for most concrete substrates is 150 ft ² /gal. Very porous surfaces may require 2 coats.		
	Substrate	Coverage	
	Bridge Decks/Ramps	150-250 ft ² /gal	
	Resealing Bridge Decks/Ramps	150-300 ft ² /gal	
	Smooth Concrete	150-225 ft ² /gal	
	Exposed Aggregate	100-200 ft ² /gal	
	Concrete Block	50-100 ft ² /gal	
	Brick/Stone	60-200 ft ² /gal	
	Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.		
Substrate Temperature	Recommended substrate temperatures are between 40-90°F. Material may be applied as low as 20°F, providing the substrate is ice-free/frost-free, though lower penetration might be expected.		
Waiting / Recoat Times	Sikagard® SN-40 loses its solvent very rapidly after application. However, the reaction of the residual silane monomer with the substrate will take at least 24 hours at a temperature of 77 °F (25 °C). Drying is considerably longer at colder temperatures. Do not apply if rain is expected within 4-6 hrs of application.		

SURFACE PREPARATION

All surfaces must be clean, sound, frost free and dry (maximum depth of penetration is achieved when substrates are dry, with no damp patches). Any existing coatings, surfaces treatments, accumulated pollutants, dust, dirt, oil and efflorescence must be removed. A substrate clogged with dirt or oil will not permit proper sealer penetration. Uncoated surfaces must be free from curing compound residues and any material or contaminants detrimental to penetration. Best results are achieved when Sikagard® SN-40 is applied onto 28 days old or older concrete, however, due to its high alkali resistance, it is possible to apply it earlier. All substrates requiring preparation, such as contaminated surfaces or horizontal concrete slabs, must be properly cleaned before the sealer is applied. This is best achieved using grinding, light sand-blasting, shot-blasting or high pressure water blasting. Allow adequate

time for surfaces to dry (for best penetration) before proceeding with application. A test patch should always be performed to determine proper results and coverage rates prior to application.

MIXING

The material is ready for use and requires no mixing. Do not dilute.

APPLICATION

Vertical Surfaces: Apply Sikagard® SN-40 using a brush, roller or industrial spray equipment, working from top to bottom by maintaining a 12 in (30 cm) parallel curtain (run down). When applying the material on a vertical surface, avoid accumulation and run-off of the material. In the event of material accumulation or run-off lines being formed, redistribute the material on the surface or

remove by sponging. In most cases, the flood coat should be applied in two (2) passes. Apply a light spray to break the surface tension of the wall and follow immediately with a flood coat, "wet on wet", with the second pass at right angles to the first. Fully saturate all mortar joints.

Horizontal Surfaces: Apply Sikagard® SN-40 using a roller or low-pressure spray, ensuring that product penetrates the substrate and does not "pond" or "puddle" on the surface. If ponding occurs, make sure to redistribute or remove the excess material on the surface before material starts to dry and form a film that will prevent penetration of excess material. Where working on a horizontal surface the flood coat should be applied in two (2) passes, "wet on wet" with the second pass at right angles to the first. Complete and correct coverage of surfaces is crucial to the success of such sealers. Fully saturate all mortar joints.

LIMITATIONS

- Sikagard® SN-40 is best applied onto 28 day old concrete or older, however, due to its high alkali resistance, it is possible to apply it earlier, though lower penetration might be expected.
- Can be applied at temperatures down to 20°F, providing the surface is ice-free/frost-free, though lower penetration might be expected.
- Not recommended for exterior applications if rain is expected within 4-6 hours.
- Not intended for waterproofing under hydrostatic pressure, in permanent contact with water or for below ground waterproofing.
- Not intended to seal visible cracks from moisture ingress.
- Building materials not to be treated (e.g. window frames and glazing) must be protected from contact. In case of splashes, clean immediately using clean water and a squeegee.
- Some coatings and bituminous materials may be damaged by the Sikagard® SN-40; care is required during application or protection against contact may be necessary.
- Use Sikagard® SN-40 with adequate ventilation.
- Surfaces treated with Sikagard® SN-40 cannot be overcoated with either cement or lime-wash based paints.

- Sikagard® SN-40 is clear and typically "invisible" to the eye once cured and dried, however if there are strict aesthetic requirements (for example on natural stone) it is recommended to undertake preliminary trials as slight darkening of some surfaces may occur.
- Do not let dry excess material, darkening, change of color and appearance of substrate may occur

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL**

APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet

Sikagard® SN-40
March 2020, Version 01.02
020303010010000019

SikagardSN-40-en-US-(03-2020)-1-2.pdf

