



**DIVISION 7 – THERMAL AND MOISTURE PROTECTION**  
**Section 071800 – Traffic Coatings**

**Part 1 - General**

**1.01 Summary**

- A. This specification describes the application of a seamless waterproofing system resistant to specified traffic wear exposures. The specified products shall include Sikalastic polyurethane base coat, either single or two component, and Sikadur low-molulus epoxy top coat for added abrasion resistance.

**1.02 Quality Assurance**

- A. Manufacturing qualifications: The manufacturer of the specified product shall be ISO 9001/9002 certified and have in existence a recognized ongoing quality assurance program independently audited on a regular basis.
- B. Contractor qualifications: Contractor shall be qualified in the field of concrete repair and protection with a successful track record of 5 years or more. Contractor shall maintain qualified personnel who have received product training by a manufacturer's representative.
- C. Install materials in accordance with all safety and weather conditions required by manufacturer or as modified by applicable rules and regulations of local, state and federal authorities having jurisdiction. Consult Material Safety Data Sheets for complete handling recommendations.

**1.03 Delivery, Storage and Handling**

- A. All materials must be delivered in original, unopened containers with the manufacturer's name, labels, product identification, and batch numbers. Damaged material must be removed from the site immediately.
- B. Store all materials off the ground and protect from rain, freezing or excessive heat until ready for use.
- C. Condition the specified product as recommended by the manufacturer.

**1.04 Job Conditions**

- A. Environmental Conditions: Do not apply material if it is raining or snowing or if such conditions appear to be imminent. Minimum application temperature 40°F (5°C) and rising.
- B. Protection: Precautions should be taken to avoid damage to any surface near the work zone due to mixing and handling of the specified coating.

**1.05 Submittals**

- A. Submit two copies of manufacturer's literature, to include: Product Data Sheet, and appropriate Material Safety Data Sheets (MSDS).

**1.06 Warranty**

- A. Provide a written warranty from the manufacturer against defects of materials for a period of one (1) year, beginning with date of substantial completion of the project.

**Part 2 - Products**

**2.01 Manufacturers**

- A. Sikalastic 22 Lo-Mod Traffic System, as manufactured by Sika Corporation, 201 Polito Ave., Lyndhurst, NJ 07071, is considered to conform to the requirements of this specification.
- B. Any materials required for repair prior to installation shall be manufactured by the same supplier of the proposed traffic coating system.

**2.02 Materials**

- A. Sikalastic 22 Lo-Mod Traffic System is a complete system of compatible materials comprised of the following:
  - 1. Sikafloor FTP water-based epoxy primer or other primer recommended by manufacturer
  - 2. Option 1: Sikalastic 710 Base one-component aromatic polyurethane base coat
  - 3. Option 2: Sikalastic 720 Base two-component, high solids, fast curing polyurethane base coat
  - 4. Sikadur 22, Lo-Mod low-molulus, medium viscosity epoxy resin binder
  - 5. Optional top coats:: Sikalastic 715 Top, 735 AL, 736 AL Lo-VOC. 745 AL or 748 PA. See Silastictic Traffic Systems or separate Aliphatic Top Coats Product Data Sheets.
- B. Total dry film thickness exclusive of aggregate shall be 55 mils for heavy vehicular traffic. See data sheet System Guide for coverage rates and application methods.
- C. Aggregate shall be clean, rounded, oven dried quartz sand with a minimum gradation of 16-30 mesh for vehicular traffic and 20-40 mesh for pedestrian traffic, and a minimum hardness of 6.5 per the Moh's scale. Aggregate shall be supplied in pre-packaged bags and free of metallic or other impurities.

**2.03 Performance Criteria**

- A. Properties of Sikalastic base coat options:

	<u>710 Base</u>	<u>720 Base</u>
Viscosity / Pot Life	6500 +/- 3000 cps	10-15 minutes
Total Volume Solids (ASTM D2697)	71%	100%
VOC Content (ASTM D2369-81)	240 g/l	< 10 g/l
Tensile Strength (ASTM D412)	800 +/- 100 psi	2500 +/- 100 psi
Elongation at Break (ASTM D412)	500 +/- 50 %	800 +/- 100 %
Tear Resistance (Die C, ASTM D624)	170 +/- 25 pli	300 +/- 50 pli
Hardness (ASTM D2240)	55 +/- 5 Shore A	80 +/- 5 Shore A

B. Properties of Sikadur 22, Lo-Mod epoxy binder:

Viscosity	2000-2500 cps
Pot Life	30 minutes
Total Volume Solids (ASTM D2697)	100%
VOC Content (ASTM D2369-81)	56 g/l
Tensile Strength (ASTM D638)	5900 psi
Elongation at Break (ASTM D638)	30%
Hardness (ASTM D2240)	80 Shore D

C. Properties of Sikalastic standard top coat options:

	<u>715 Top</u>	<u>745 AL</u>
Viscosity / Pot Life	1500 +/- 500 cps	20-30 minutes
Total Volume Solids (ASTM D2697)	72%	100%
VOC Content (ASTM D2369-81)	243 g/l	< 10 g/l
Tensile Strength (ASTM D412)	3200 +/- 300 psi	3200 +/- 300 psi
Elongation at Break (ASTM D412)	500 +/- 50 %	450 +/- 45 %
Tear Resistance (Die C, ASTM D624)	350 +/- 50 pli	300 +/- 30 pli
Hardness (ASTM D2240)	85 +/- 5 Shore A	85 +/- 5 Shore A

B. Properties of Sikalastic high performance top coat options:

	<u>735 AL</u>	<u>736 AL Lo-VOC</u>	<u>748 PA</u>
Viscosity	2500 +/- 700 cps	3500 +/- 700 cps	200 +/- 50 cps
Total Volume Solids (ASTM D2697)	74%	83%	78%
VOC Content (ASTM D2369-81)	225 g/l	99 g/l	100 g/l
Tensile Strength (ASTM D412)	4200 +/- 300 psi	4000 +/- 300 psi	2300 +/- 300 psi
Elongation at Break (ASTM D412)	230 +/- 50 %	250 +/- 50 %	50 +/- 20 %
Tear Resistance (Die C, ASTM D624)	400 +/- 50 pli	400 +/- 50 pli	300 +/- 50 pli
Hardness (ASTM D2240)	90 +/- 5 Shore A	90 +/- 5 Shore A	50 +/- 5 Shore D

Note: Tests were performed with material and curing conditions at 75F and 50% relative humidity.

## Part 3 – Execution

### 3.01 Surface Preparation

- A. The substrate must be clean, dry, sound and free of surface contaminants. Remove all traces of dust, laitance, grease, oils, curing compounds, form release agents and foreign particles by mechanical means, i.e. – milling, scarifying, shotblasting, etc., as approved by the engineer. Blow surface free of

dust using compressed air line equipped with an oil trap. Surface Preparation Surface must be clean, dry and sound with an open texture. Remove dust, laitance, grease, curing. All projections, rough spots, etc. should be dressed off to achieve a level surface prior to the application.

- B. Concrete should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blast cleaning or equivalent mechanical means (CSP 3-4 per ICRI guidelines).
- C. Metal should be thoroughly cleaned by grinding or blast cleaning.

### **3.02 Priming**

- A. Concrete and plywood – Apply Sikafloor FTP primer at 300 sf/gal. with a flat squeegee or roller and work well into the substrate to insure adequate penetration and sealing and puddles are avoided. Refer to data sheet for more detailed information, or consult Sika for other primer options.
- B. Premix both components. Sikafloor FTP, Part “H” is dark olive green in color and may appear black in the container. Sikafloor FTP, Part “R” is light amber in color. Add the 1 gallon of Sikafloor FTP, Part “R” to the 1.25 gallons of Part “H” in the short filled Part “H” pail. Mix thoroughly with a mechanical mixer (Jiffy) for 3 minutes. This mixture will appear as a light olive green color. Slowly add 1.25 gallons of potable water to the mixture under agitation. Mix for an additional 2 minutes until the mixture is fully dispersed. Fully dispersed material will appear as light green in color. Allow primer to cure a minimum of 3-4 hours at 70°F and 50% RH or until tack free before applying base coat.
- C. Metal – Consult Sika regarding primer.

### **3.03 Detailing**

- A. Non-structural cracks up to 1/16 inch – Apply a detail coat of Sikalastic 710 Base at 32 mils wet, 4” wide, centered over the crack. Allow to become tack free before overcoating.
- B. Cracks and joints over 1/16 inch up to 1/2 inch – Route and seal with Sikaflex 2c or 1a sealant and allow to cure. Apply a detail coat of Sikalastic 710 Base at 32 mils wet or 720 Base at 24 mils, 4” wide, centered over crack. Allow to become tack free before overcoating.
- C. Joints over 1/2 inch – Should be treated as expansion joints and brought up through the Sikalastic 22 Lo-Mod Traffic System and sealed with Sikaflex 2c or 1a sealant.

### **3.04 Base Coat**

- A. Option 1: Thoroughly mix Sikalastic 710 Base using a mechanical mixer (Jiffy) at slow speeds until a homogenous mixture and color is obtained. Use care not to allow the entrapment of air into the mixture. Apply at the recommended coverage rate (see System Guide) using a notched squeegee or trowel and backroll using a phenolic resin core roller. Extend base coat over entire area including previously detailed cracks and control joints. Allow coating to cure a minimum of 16 hours at 70°F and 50% RH or until tack free before over coating.
- B. Option 2: Premix Sikalastic 720 Base Part A and Part B using a mechanical mixer (Jiffy) at slow speed to obtain uniform color, making sure to scrape the solids from the bottom and sides of the pail. Pour Part B into Part A slowly and while mixing scrape the sides of the container. Mix the combined material thoroughly until a homogenous mixture and color is obtained (typically 3 minutes). Use care not to allow the entrapment of air into the mixture. Apply at the recommended coverage rate (see System Guide) using a notched squeegee or trowel and backroll using a phenolic resin core roller. Extend base coat over entire area including previously detailed cracks and control joints. Allow coating to cure a minimum of 3-4 hours at 70°F and 50% RH or until tack free before over coating.

### 3.05 Binder Coat

- A. Premix Sikadur 22, Lo-Mod Part A and Part B and proportion equal parts by volume into a clean mixing container. Mix with a low-speed (400-600 rpm) mechanical mixer (Jiffy) using care not to allow the entrapment of air into the mixture. Apply at the recommended coverage rate (see System Guide) using a notched squeegee and backroll using a phenolic resin core roller. Apply aggregate evenly distributed at the appropriate rate immediately into wet coating. Allow coating to cure a minimum of 8 hours at 70°F and 50% RH or until tack free and remove all loose aggregate between coats, and a minimum of 48-72 hours depending upon base coat before opening to vehicular traffic.

### 3.06 Aggregate

- A. Slowly broadcast so the aggregate falls vertically into the binder making several passes, allowing the binder to bleed through the sand before making the next pass. Cover completely at a total rate of 1.5 lbs. per square foot before the binder becomes tack free.

### 3.07 Optional Top Coat

- A. Optional polyurethane top coats are available to provide improved wear and UV resistance. Consult Sika for application and coverage rates and refer to mixing and application instructions in relevant product data sheet for optional Sikalastic 715 Top, 735 AL, 736 AL Lo-VOC, 745 AL and 748 PA.

### 3.08 Mock-up

- A. A job site mock-up should always be completed to confirm acceptability of workmanship, material coverage rates and aesthetics.

### 3.08 Cleaning

- A. Uncured materials can be removed from tools or other surfaces with an approved solvent. Cured materials can only be removed by mechanical means.
- B. Leave finished work and work area in a neat, clean condition without evidence of spillovers onto adjacent areas.

The preceding specifications are provided by Sika Corporation as a guide for informational purposes only and are not intended to replace sound engineering practice and judgment and should not be relied upon for that purpose. **SIKA CORPORATION MAKES NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS OR THE CONTENTS OF THESE GUIDE SPECIFICATIONS.** Sika Corporation assumes no liability with respect to the provision or use of these guide specifications, nor shall any legal relationship be created by, or arise from, the provision of such specifications **SIKA SHALL NOT BE RESPONSIBLE UNDER ANY LEGAL THEORY TO ANY THIRD PARTY FOR ANY DIRECT OR CONSEQUENTIAL DAMAGES OF ANY KIND ARISING FROM THE USE OF THESE GUIDE SPECIFICATIONS.** The specifier, architect, engineer or design professional or contractor for a particular project bears the sole responsibility for the preparation and approval of the specifications and determining their suitability for a particular project or application.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available at [www.sikaconstruction.com](http://www.sikaconstruction.com) or by calling (201) 933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instructions for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.