

PRODUCT DATA SHEET

Sikalastic®-500 Flash

Single Component Silicone Roof Flashing

PRODUCT DESCRIPTION

Sikalastic®-500 Flash is an enhanced high solids silicone formula that can be used in conjunction with a variety of liquid coatings and a variety of roof membranes. It is designed to create a watertight liquid flashing for intricate roofing areas and details. With its low VOC's, the single-component, moisture-cure liquid flashing is environmentally friendly. This high performing high solids silicone is durable, reflective and UV resistant and has excellent vertical hang and performs well under ponding water.

USES

- Can be used for spot repairs
- Reinforce seams, flashings and penetrations
- Seal joint and penetration repairs for solar and air conditioning systems

CHARACTERISTICS / ADVANTAGES

- Can be used over a variety of roofing substrates including modified bitumen, built-up roofing, metal, spray polyurethane foam, wood, concrete, and a variety of systems.
- Its fast curing time helps the applicator save time.
- Can be used as part of a complete cool roof restoration system for the system.
- It also can be used for repairs of existing systems, roof repairs such as flashings, penetrations and seams

PRODUCT INFORMATION

Chemical Base	moisture cured Silicone	
Packaging	3.5 gal. (13.2 L) pail	
Color	White	
Shelf Life	12 months	
Storage Conditions	Keep containers closed and store in a dry, cool place away from heat, sparks, open flame, excessive heat, and moisture. Keep material stored above 65°F. Open containers should be blanketed with dry nitrogen before using.	
Solid content by weight	94 % (+/- 2)	(ASTM D-2697)
Solid content by volume	94 % (+/- 2)	(ASTM D-2697)

TECHNICAL INFORMATION

Shore A Hardness	45–55	(ASTM D-2240)
Tensile Strength	300 psi	(ASTM D-412)
Elongation at Break	200 %	(ASTM D-412)
Tear Strength	45 lb./in.	(ASTM D-624)

APPLICATION INFORMATION

Coverage	4 gal./100 ft ²
Ambient Air Temperature	41 °F (5 °C) min. / 95 °F (35 °C) max.
Relative Air Humidity	80 % R.H. max.
Substrate Temperature	41 °F (5 °C) min. / 140°F (60°C) max.
Dew Point	Beware of condensation. The substrate and uncured coating must be ≥ 5 °F (3 °C) above dew point.
Substrate Moisture Content	≤ 4 % moisture content Test method: Sika®-Tramex meter No rising moisture according to ASTM (Polyethylene-sheet).

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

1. Remove all unnecessary and non-functional equipment and debris from the roof.
2. Remove dirt, and foreign material detrimental to adhesion or application of fluid-applied roofing by thoroughly cleaning all roof surfaces with a high pressure (2,000–2500 psi, 13.79–17.24 MPa) wash. Surfaces contaminated with oil, grease, animal fats, etc. must be removed using tri-sodium phosphate and water, or other solutions as required by job conditions and as permitted by local, state, and federal regulations. Remove all cleaning solutions with plenty of fresh water and allow to dry.
3. Membranes with seam and flashing failure must be repaired using traditional and professional corrective measures and then detailed.
4. Seal watertight all round projections, machine legs, sign posts, guide wire straps, inside and outside corners, cant strips, gutters, parapet walls, caps, and seal watertight all screws, seams, skylights, joints, pipes, voids, protrusions and any areas where water could enter through the roof.
5. Clean and Seal all areas around drains watertight.
6. Allow roof and other prepared surfaces to dry completely before proceeding with field priming and/or coating application. Note: Thickness values of cured film are averages and can vary due to finish of surface. Always check the weather prior to application. Depending on the ambient, and substrate temperatures, relative humidity, and dew point take extra time and caution when applying the system

within 2 to 6 hours of precipitation and/or when raw or freezing temperatures are experienced or anticipated. Do not apply over wet insulation or related materials.

APPLICATION

Prior to coating any surface, be sure the coating will adhere by performing an adhesion test (ASTM D-903). Coating may be applied by brush, spatula or trowel. Do not apply when temperatures are below 41 °F (5 °C) or when precipitation is in the forecast within 48 hours. To avoid pin holes and blistering Sikalastic®-500 Flash should not be applied at a rate no thicker than 250 wet mils (6.35 mm) in one application.

LIMITATIONS

- To avoid dew point conditions during application, the substratetemperature must be at least 5 °F (3 °C) above measured dew point temperatures.
- Minimum ambient and substrate temperature during application and curing of material is 41 °F (5 °C); maximum is 95 °F (35 °C). Surface temperatures must be no higher than 140 °F (60 °C). Frequent monitoring of ambient and substrate temperature should always be done when applying silicone resins. Note that low temperatures and low humidity will slow down the cure, and high temperatures and high humidity will accelerate it.
- Do not apply on substrates with moisture content greater than 4 % by weight, measured by Tramex Concrete Moisture Encounter meter.
- Minimum age of concrete must be 21 - 28 days depending on curing and drying conditions.

- Do not thin with solvents.
- Do not store materials outdoors directly exposed to sunlight and moisture. Cover and protect materials with breathable type covers such as canvas tarpaulins to allow venting and protection from weather and moisture. Observe temperature storage and conditioning requirements.
- Do not apply to substrate surfaces where moisture vapor transmission will occur during application and cure.
- This condition may be checked using ASTM D-4263 (Polyethylene sheet method).
- Substrate must be dry prior to application. Do not apply to a frosted, wet or damp surface. Allow sufficient time for the substrate to dry after rain or inclement weather, as there is the potential for bonding problems.
- On substrates likely to exhibit outgassing apply during falling ambient and substrate temperature. If applied during rising temperature pinholing or blistering may occur.
- Use sunglasses with UV filter when applying highly reflective Sikalastic®-500 Flash White.
- Do not apply cementitious products, such as tile mortar directly onto Sikalastic®-500 Flash. See Sikalastic® 624 WP or Sikalastic®-644 Lo-VOC Product Data Sheet.
- Any repairs required to achieve a level surface must be performed prior to application (consult a Sika representative for guidance on various product solutions). Surface irregularities may reflect through the cured system.
- Unvented metal pan, split/sandwich slab with encapsulated membrane and/or insulation, cinder fill decks, and lightweight insulating concrete deck overlays should not be covered with Sikalastic®-500 Flash without additional deck evaluation and subsequent approval by Technical Services.
- Do not subject to continuous immersion, i.e., fountains, ponds, pools, or interior of tanks.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD**

BY OTHERS.

Sale of Sika products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Sarnafil

100 Dan Road
Canton, MA 02021
Phone: +1 800-451-2504
Fax: +1 781-828-5365
usa.sika.com/sarnafil
webmaster.sarnafil@us.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet

Sikalastic®-500 Flash
April 2018, Version 01.01
020915701000000001

Sikalastic-500Flash-en-US-(04-2018)-1-1.pdf

