

## PRODUCT DATA SHEET

# Sikalastic®-503 Primer

Two component Polyurethane primer for PVC & TPO substrates

#### PRODUCT DESCRIPTION

Two component, high solids, cool roof, polyurethane liquid applied primer with unique penetrating characteristics

#### **USES**

- For use with Sikalastic® -500 RoofCoat products
- PVC\*
- TPO\*
- Intercoat adhesion & re-coat primer for existing urethane systems

\*Some surfaces may be manufactured with a lacquer finish, contact Sika if pull/adhesion test yields less than required pli

## **CHARACTERISTICS / ADVANTAGES**

- High Solids
- Fast Re-Coat Time
- Low Odor
- Low Viscosity

#### PRODUCT INFORMATION

Chemical Base	Two component Polyurethane
Packaging	2 gal. kit Part A: 1 gal Part B: 1 gal
Shelf Life	12 months
Storage Conditions	Keep containers closed and store in a dry, cool place away from direct sunlight, heat, sparks, open flame, and moisture. Keep material stored above 65 °F (18 °C). Open containers should be blanketed with dry nitrogen before resealing.
Appearance / Color	Part A - black Part B - white
Density	Part A: 1.22 kg/l Part B: 0.98 kg/l
Viscosity	500 cps. (at 75 °F (24 °C) and 50 % R.H. Part A+B)

#### Product Data Sheet Sikalastic®-503 Primer

May 2023, Version 01.03 020915951000000058

#### APPLICATION INFORMATION

Mixing Ratio	Part A: Part B = 1:1 (by volume)
Ambient Air Temperature	41 °F (5 °C) min. / 104 °F (40 °C) max.
Relative Air Humidity	80 % R.H. max.
Dew Point	Beware of condensation.  The substrate and uncured coating must be ≥ 5 °F (3 °C) above dew point.
Substrate Temperature	41 °F (5 °C) min. / 140 °F (60 °C) max.
Pot Life	60–90 minutes (at 75 °F (24 °C) and 50 % R.H. Part A+B)
Waiting / Recoat Times	Allow primer to cure completely prior to applying membrane resin. Full cure: 2 - 4 hours at 68°F.  Maximum primer exposure is 12 hours. Primer exposed longer than 12 hours, exposed to water during curing and exhibiting a chalky appearance, must be reprimed. Deteriorated primer must be mechanically removed before reapplication.

#### **BASIS OF PRODUCT DATA**

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

#### **LIMITATIONS**

- Sikalastic®-503 Primer should be coated within 12 hours after it has become tack free
- Not UV stable
- Surfaces must be dry, clean and free of foreign matter
- Containers that have been opened must be used as soon as possible
- Sikalastic®-503 Primer is difficult to clean up after it has cured
- Do not dilute Sikalastic®-503 Primer

### **ENVIRONMENTAL, HEALTH AND SAFETY**

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

#### **APPLICATION INSTRUCTIONS**

#### MIXING

The volume mixing ratio is 1 part, Part-A (black liquid) into 1 part, Part-B (white liquid). Mix until even color distribution.

#### **APPLICATION**

Sikalastic®-503 Primer should be applied at the rate of 1 gal (mixture of Part-A & Part-B) / 300 ft². Coverage rate will depend on surface roughness and porosity. It can be applied using an airless sprayer, brush, or phenolic resin core roller. Do not allow the material to puddle.

#### OTHER RESTRICTIONS

See Legal Disclaimer.



#### **LEGAL DISCLAIMER**

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at https://usa.sika.com/en/group/SikaCorp/termsandconditions.html or by calling 1-800-933-7452.

#### Sika Corporation

201 Polito Avenue Lyndhurst, NJ 07071 Phone: +1-800-933-7452 Fax: +1-201-933-6225 usa.sika.com



Product Data Sheet Sikalastic®-503 Primer May 2023, Version 01.03 020915951000000058



Sikalastic-503Primer-en-US-(05-2023)-1-3.pdf