

## SYSTEM DATA SHEET

# Sikalastic®-624 WP Waterproofing System

Liquid applied alkaline-resistant single component fully reinforced system with fiberglass or polyester reinforcement

### PRODUCT DESCRIPTION

Sikalastic®-624 WP Waterproofing System combine a cold applied, aliphatic, single component, alkali resistant, moisture triggered polyurethane resin with fiberglass mat or polyester fleece reinforcement to create a seamless membrane and flashing system. Typical applications include a separate wearing course (overlayment or overburden), but Sikalastic®-624 WP Waterproofing System is UV resistant without protection board and is therefore suitable for direct exposure waterproofing applications as well.

#### System components are:

**Sika® or Sikalastic® Primer:** Select primer per substrate material in accordance with Priming Guide

**Sikalastic®-624 WP:** Resin used for all systems with Sika Reemat or Sika Fleece reinforcements

**Sikalastic® Reemat Premium:** Chopped strand fiberglass mat

**Sika® Fleece 120, 140, 170:** Non-woven, needle-punched polyester fleece in various weights

### USES

Sikalastic®-624 WP Waterproofing System may only be used by experienced professionals.

- Sikalastic® waterproofing systems, including Sikalastic® Plaza Deck/PMA and Vegetated systems for both new construction and refurbishment
- Split slab waterproofing - between slabs
- Vegetated deck waterproofing
- Plaza decks with concrete pavers, and asphalt or concrete paving stones in a sand bed
- Waterproofing under tile in a mortar bed

- Applications involving cementitious and asphalt pavement overlays
- Waterproofing around/beneath mechanical equipment

### CHARACTERISTICS / ADVANTAGES

- Proven technology with over 30 year track record
- Single component - no mixing and ready to use
- Fully reinforced with highly conformable Sika® Reemat or Sika® Fleece
- Integrated flashings utilizing same resin and reinforcements
- Ideal for complex details and geometry or when accessibility is limited
- Moisture triggered chemistry that is rapidly weatherproof after application
- Resistant to ponding water
- Highly elastic and crack bridging
- Seamless and fully adhered
- Vapor permeable
- UV resistant and non-yellowing
- Abrasion and chemical resistant
- Alkali resistant formulation
- Adheres to most common construction materials when suitable primer is used



### APPROVALS / STANDARDS

- Miami Dade County
- ASTM C836
- ASTM E-108
- Florida Building Code


# SYSTEM INFORMATION

## System Structure

## Sikalastic® RoofPro WP System Guide with Sika® Reemat



	RoofPro 15 WP*	RoofPro 20 WP*	RoofPro 25 WP*
1. Primer	See Priming Guide	See Priming Guide	See Priming Guide
2. Base Layer: Sikalastic®-624- WP	45 mils wet 35 sf/gal.	45 mils wet 35 sf/gal.	45 mils wet 35 sf/gal.
3. Reinforcement:	Sika® Reemat Premium	Sika® Reemat Premium	Sika® Reemat Premium
4. Top Layer: Sikalastic®-624- WP	30 mils wet 53 sf/gal.	40 mils wet 40 sf/gal.	30 mils wet 53 sf/gal.
5. Top Layer: Sikalastic®-624- WP	-	-	30 mils wet 53 sf/gal.



	RoofPro 15 WP*	RoofPro 20 WP*	RoofPro 25 WP*
1. Primer	See Priming Guide	See Priming Guide	See Priming Guide
2. Base Layer: Sikalastic®-624- WP	45 mils wet 35 sf/gal.	50 mils wet 32 sf/gal.	65 mils wet 24 sf/gal.
3. Reinforcement:	Sika® Fleece 120 (US)	Sika® Fleece 140 (US)	Sika® Fleece 170 (US)
4. Top Layer: Sikalastic®-624- WP	25 mils wet 64 sf/gal.	35 mils wet 45 sf/gal.	40 mils wet 40 sf/gal.

\* Substrates: Concrete or cementitious, metals, woods, single-ply or bituminous, stone. Primer required (see Substrate Priming Guide). Detailing: Sika® Flexitape Heavy or Sika® Joint Tape SA centered over seams, transitions and properly treated cracks and joints.

Note: Coverage rates provided are optimal and are not guaranteed - coverage rates will vary depending on temperature, surface roughness and porosity, aggregate selection and embedment, and application technique.

**Note: Coverage rates provided are optimal and are not guaranteed they will vary depending on temperature, surface roughness, porosity, aggregate selection, embedment, and application technique. For example, using Sikalastic® -624 WP Waterproofing System with Sika® Fleece 140 in a RoofPro 20 build up, a potential full system coverage rate for a mod-bit surface could be 14 - 16 sf/gal. Sikalastic® -624 WP Waterproofing System with Sika Reemat Premium in a RoofPro 15, 20 & 25 build up, a potential base coat coverage rate could be 25 - 28 sf/gal.**

**Composition**

Single component, moisture triggered, aliphatic polyurethane

**Color**

White, Pearl Gray, Custom Colors available with minimum order quantity

## Dry film thickness

### Sikalastic® RoofPro WP System Guide with Sika® Reemat

RoofPro 15	RoofPro 20 WP	RoofPro 25 WP
53 mils dry	60 mils dry	75 mils dry

### Sikalastic® RoofPro WP System Guide with Sika® Fleece

RoofPro 15 WP	RoofPro 20 WP	RoofPro 25 WP
50 mils dry	60 mils dry	75 mils dry

Note: Coverage rates provided are optimal and are not guaranteed - coverage rates will vary depending on temperature, surface roughness, porosity, aggregate selection, embedment, and application technique.

## TECHNICAL INFORMATION

<b>Resistance to Static Puncture</b>	<b>Sikalastic® WP 20 with Sika® Reemat Premium</b> > 55 lbf	<b>Sikalastic® WP 20 with Sika® Fleece 140</b> > 55 lbf	(ASTM D-5602)
Note: Data for other WP assemblies available upon request			
<b>Tensile Strength</b>	<b>Sikalastic® WP 20 with Sika® Reemat Premium</b> 2450 psi	<b>Sikalastic® WP 20 with Sika® Fleece 140</b> 1100 psi	(ASTM D-751 Proc. B)
Note: Data for other WP assemblies available upon request			
<b>Tear Strength</b>	<b>Sikalastic® WP 20 with Sika® Reemat Premium</b> 430 lbf/in	<b>Sikalastic® WP 20 with Sika® Fleece 140</b> 300 lbf/in	(ASTM D-624)
Note: Data for other WP assemblies available upon request			
<b>Elongation at Break</b>	<b>Sikalastic® WP 20 with Sika® Reemat Premium</b> 10 %	<b>Sikalastic® WP 20 with Sika® Fleece 140</b> 78 %	(ASTM D-751)
Note: Data for other WP assemblies available upon request			
<b>Reaction to Fire</b>	Class A		(ASTM E 108)
<b>Chemical Resistance</b>	Strong resistance to a wide range of reagents, including paraffin, petrol, fuel oil, white spirit, acid rain, detergents and moderate solutions of acids and alkalis. Some low molecular weight alcohols can soften the material. Contact Technical Service for specific recommendations. Salt spray to ASTM B117 (1000 hours continuous exposure) and prohesion testing to ASTM G85-94: Annex A5 (1000 hours cyclic exposure)		
<b>Solar Reflectance</b>	86.8 %		(ASTM C-1549) (White)
<b>Solar Reflectance Index</b>	109		(ASTM E-1980) (White)
<b>Thermal Emittance</b>	0.87		(ASTM C-1371) (White)
<b>Service Temperature</b>	-22–176 °F (-30–80 °C) intermittent		

## APPLICATION INFORMATION

<b>Ambient Air Temperature</b>	41 °F (5 °C) min. / 95 °F (35 °C) max
<b>Relative Air Humidity</b>	80 % R.H. max.

<b>Dew Point</b>	Beware of condensation. The substrate and uncured coating must be $\geq 5^{\circ}\text{F}$ ( $3^{\circ}\text{C}$ ) above dew point.			
<b>Substrate Temperature</b>	41 °F (5 °C) min. / 140°F (60°C) max.			
<b>Substrate Moisture Content</b>	$\leq 4\%$ moisture content Test method: Sika®-Tramex meter No rising moisture according to ASTM (Polyethylene-sheet)			
<b>Waiting / Recoat Times</b>	<b>Ambient Conditions</b>	<b>Minimum Waiting Time Overcoating</b>		
	+40 °F / 50 % r.h.	14 hours		
	+50 °F / 50 % r.h.	6 hours		
	+70 °F / 50 % r.h.	5 hours		
	*After 7 days the surface must be cleaned and primed with Sika® Reactivation Primer before continuing. Note: Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.			
<b>Applied Product Ready for Use</b>	<b>Ambient conditions</b>	<b>Rain resistant</b>	<b>Touch dry</b>	<b>Full cure</b>
	+40 °F / 50 % r.h.	10 min.	12 hours	24 hours
	+50 °F / 50 % r.h.	10 min.	6 hours	18–24 hours
	+70 °F / 50 % r.h.	10 min.	4 hours	12–18 hours
	Note: Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.			

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## LIMITATIONS

- Minimum age of concrete must be 28 days depending on curing and drying conditions
- Do not thin with solvents
- Do not store materials outdoors exposed to sunlight and moisture for prolonged periods
- Do not apply to substrate surfaces where moisture vapor transmission will occur during application and cure. This condition may be checked using ASTM D-4263 (Polyethylene Sheet method)
- Substrate must be dry prior to application. Do not apply to a frosted, wet or damp surface
- Allow sufficient time for the substrate to dry after rain or inclement weather, as there is the potential for bonding problems
- On substrates likely to exhibit outgassing apply during falling ambient and substrate temperature
- If applied during rising temperature pinholing may occur
- Use sunglasses with UV filter when applying highly reflective white resins
- Do not use for indoor applications
- Precautions should be taken to prevent vapors and/or odors from entering the building/ structure, including but not limited to turning off and sealing air intake vents and throughwall air conditioners, and other means of vapor/odor ingress during application and cure
- For areas with direct exposure to heavy or frequent foot traffic, an additional wear coat protection with slip resistant aggregate is required Opening to traffic prior to cure may result in loss of aggregate or permanent staining and subsequent premature failure
- Any repairs required to achieve a level surface must be performed prior to application (consult a Sika representative for guidance on various product solutions). Surface irregularities may reflect through the cured system
- When applying over existing coatings or membranes compatibility and adhesion testing, and subsequent approval by Technical Services is required
- Opening to traffic prior to cure may result in permanent staining and subsequent premature failure
- On grade concrete decks should not be covered with Sikalastic® RoofPro membrane systems
- Unvented metal pan, split/sandwich slab with encapsulated membrane and/or insulation, cinder fill decks, and lightweight insulating concrete overlays should not be covered with Sikalastic® RoofPro membrane systems without additional deck evaluation and subsequent approval by Technical Services
- Do not subject to continuous immersion
- Not recommended for use over ceramic tile

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## APPLICATION INSTRUCTIONS

### Substrate Pre-Treatment

Refer to Priming Guide to select primer for properly evaluated and prepared substrate. Refer to separate primer Product Data Sheet for application methods, coverage rates, cure times and recoat windows. Always allow primer to cure thoroughly before applying detail or base resin layer.

### Sikalastic® RoofPro-641 Lo-VOC Priming Guide

#### Substrates and Primer Options

##### Concrete \*1

Sikalastic® Concrete Primer Lo-VOC  
Sikalastic® DTE Primer  
Sikalastic® GDC Primer  
Sikalastic® EP Primer/Sealer  
Sikalastic® EP Primer Rapid

##### Lightweight Structural Concrete \*1

Sikalastic® Concrete Primer Lo-VOC  
Sikalastic® DTE Primer  
Sikalastic® GDC Primer  
Sikalastic® EP Primer/Sealer  
Sikalastic® EP Primer Rapid

##### Cement, Gypsum Based Roof Boards

Sikalastic® Concrete Primer Lo-VOC  
Sikalastic® EP Primer/Sealer  
Sikalastic® EP Primer Rapid

##### Brick, Stone \*3

Sikalastic® Concrete Primer Lo-VOC  
Sikalastic® EP Primer/Sealer  
Sikalastic® EP Primer Rapid

##### Bituminous Substrate

##### Asphalt, Bituminous Felts, Bituminous Coatings, Granulated or Smooth

##### SBS & Aged APP Cap Sheets \*2,3

Sikalastic® EP Primer/Sealer  
Sikalastic® EP Primer Rapid

##### Single Ply PVC Membranes \*3

##### Sarnafil, Sikaplan \*3

Sikalastic® EP Primer/Sealer

##### Hypalon \*3

Sika® Bonding Primer

##### TPO, EPDM \*3

Sikalastic® EPDM Primer  
Sikalastic® EPDM / TPO Primer Lo-VOC

##### Roof Tiles (unglazed) \*3,4

Sikalastic® EP Primer/Sealer

Sikalastic® EP Primer Rapid

##### Fiberglass \*3

Sikalastic® EP Primer/Sealer

Sikalastic® EP Primer Rapid

##### Polyurethane Foam - Sprayed or Slab Stock

Sikalastic® EP Primer/Sealer

Sikalastic® EP Primer Rapid

##### Metal \*3

**Aluminium, Galvanized, Cast Iron, Copper, Lead, Brass, Stainless Steel, Steel, Zinc**

Sikalastic® EP Primer/Sealer

Sikalastic® EP Primer Rapid

##### Pre-Coated Metal \*3

##### Paints & Coatings \*3

##### Aluminized Solar Reflective Coatings \*3

Sikalastic® EP Primer/Sealer

Sikalastic® EP Primer Rapid

##### Wood - Timber & Plywood \*5

Sikalastic® EP Primer/Sealer

Sikalastic® EP Primer Rapid

##### \* Consult Sika

- 1 New cementitious substrates must be Portland base and be cured min. 28 days.
- 2 The presence of volatile bitumen may cause discoloration of Sikalastic® if not properly primed.
- 3 Surface evaluation and field adhesion testing.
- 4 Glazed tile consult Sika.
- 5 Pressure treated lumber consult Sika.

## SUBSTRATE PREPARATION

### Concrete and Cementitious Substrates

New concrete shall be allowed to cure a minimum of 28 days. Concrete shall have a minimum compressive strength of 20.7 MPa (3000 psi) and exhibit a minimum tensile bond strength of 1.4 MPa (200 psi). Moist or sheet curing methods should be used, as opposed to the use of curing compounds, which may interfere with the bond of the membrane. Inspect the concrete, including upstands, and all areas should be hammer or chain drag tested. Concrete must be suitably finished, preferably by wood float or steel pan. A power float finish is acceptable where the surface is prepared to avoid laitance (a tamped finish is not acceptable). The surface finish must be uniform and free from defects such as laitance, voids or honeycombing.

Cementitious or mineral based substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and to achieve an open textured surface (CSP 2-4 per ICRI guidelines). Loose friable material and weak concrete must be completely removed and surface defects such as blowholes and voids must be fully exposed. The amount of embedment coat required may increase over rough or highly porous surfaces.

Repairs to the substrate, filling of joints, blowholes/voids and surface levelling must be carried out. Consult Sika for product recommendations based on project

#### System Data Sheet

Sikalastic®-624 WP Waterproofing System

April 2023, Version 01.04

020915909000000015

requirements. High spots must be removed by grinding or similar method. Outgassing is a naturally occurring phenomenon of concrete that can produce pinholes in liquid applied materials. The concrete must be carefully assessed for moisture content, air entrapment, and surface finish prior to any roofing work. Particular requirements for priming must also be considered. Installing the primer and membrane either when the concrete temperature is falling or stable can reduce outgassing. It is generally beneficial, therefore, to apply the primer and embedment coat in the late afternoon or evening.

#### **Gypsum and Cement Based Sheathing**

Sheathing boards shall be clean, dry and dust free, and shall be properly secured to the structure. Secure loose boards if in sound condition. Damaged or contaminated boards shall be removed and replaced.

#### **Brick and Stone**

Mortar joints must be sound and preferably flush pointed. Power wash and use biodegradable non-sudsing detergent with clean water rinse as required.

#### **Asphalt**

Asphalt contains volatiles which can cause bleeding and slight non-detrimental staining. The asphalt must be carefully assessed for moisture and/or air entrapment, grade and surface finish. Power wash and use biodegradable non-sudsing detergent with clean water rinse as required. All major cracks should be sealed to allow continuity of the Sikalastic® RoofPro system.

#### **Bituminous Felt**

Ensure that bituminous felt is firmly adhered or mechanically fixed to the substrate. Bituminous felt shall not contain badly degraded areas. Power wash and use biodegradable non-sudsing detergent with clean water rinse as required. Treat blisters by star cutting and removing any underlying water. Allow to dry and re-adhere using suitable adhesive.

#### **Bituminous Coatings**

Bituminous coatings should not be sticky or mobile. Volatile mastic coatings, or old coal tar coatings are not acceptable. Remove any loose or degraded coatings.

#### **Metals**

Metals must be in sound condition. Ferrous metals should be thoroughly cleaned by grinding or blast cleaning prior to priming (SSPC-SP3 to SP11 near-white

metal). Non-ferrous metals are prepared by removing any deposits of dust and oxidation and abrading to bright metal. Wire brushing can be used for soft metal such as lead. The surface must be clean and free from grease which, if present, must be removed with a solvent wipe or wash with detergent, rinse and dry. Stainless Steel must be mechanically abraded or ground to create an appropriate anchor profile.

#### **Wooden Substrates**

Plywood and timber based roof decks must be in good condition, firmly adhered and mechanically fixed. All plywood should be identified as conforming to PS 1 for construction and industrial plywood by grade, APA (American Plywood Association) trademark, or equivalent. For maximum smoothness, EXT Type APA, Grade A-C should be used, and the "A" side should be positioned to receive the Sikalastic® resin. Plywood decks to receive resin directly shall be at least 1/2" thick and attached and supported according to APA guidelines, using only non-rusting screw, spiral or coated nail type fasteners. A good practice would be to recess or counter sink fasteners 1/8 to 1/4" and fill with Sikaflex® sealant. Suitable edge support to prevent differential deflection between panels shall be provided. Panel edges shall be tongue and groove or supported on solid blocking. Space panels 1/8 to 3/16" at panel ends.

Timber and timber based roof decks require additional reinforcement such as the installation of plywood, approved insulation or cover board. Small timber protrusions and suitable decks may be treated directly, provided that the timber is of exterior quality, e.g. plywood. Fill joints flush with Sikaflex® sealant.

#### **Paints and Coatings**

Ensure the existing material is sound and firmly adhered. Remove any loose or degraded coatings. Ensure the surface is clean and free from oxidation, dust, dirt, and debris. Power wash and use biodegradable non-sudsing detergent with clean water rinse as required. Allow to dry.

#### **Existing Sikalastic® RoofPro System**

The existing Sikalastic® RoofPro System shall be soundly adhered to the substrate. Clean the membrane using a pressure washer at approximately 140bar (2000 psi) and biodegradable non-sudsing detergent with clean water rinse. Allow to dry.

## Sikaplan®/Sarnafil® Membranes

Clean the membrane using a pressure washer at approximately 140bar (2000 psi) and biodegradeable non-sudsing detergent with clean water rinse or use approved PVC membrane cleaner. Allow to dry.

### MIXING

No mixing necessary

### APPLICATION

#### Detailing

##### Non-structural Cracks Up To 1/16"

Detail application not necessary. Apply embedment/base resin layer per instruction. Non-structural cracks between 1/16" and 1/4" Rout and seal with Sikaflex® sealant. Apply 40–45 mil resin layer embedded with 3" Sika Flexitape Heavy or use Sika® Joint Tape SA centered over the crack. Apply embedment/base resin layer per instruction.

##### Cracks and Joints Between 1/4" and 1"

Rout and seal with Sikaflex® sealant. Apply bond breaker tape sufficient to span width of crack or joint followed by 40-45 mil resin layer embedded with 6" Sika® Flexitape Heavy or use Sika® Joint Tape SA centered over crack or joint. Apply embedment/base resin layer by terminating Sika® Reemat or Sika® Fleece at edges of crack or joint overlapping Sika® Flexitape Heavy or Sika® Joint Tape SA, a minimum of 2 inches on both sides of the crack or joint.

##### Joints Greater Than 1"

Treat as expansion joint. Consult Sika for recommendations.

##### Metal Seams and Plywood/Cover Board Joints

Apply 40–45 mil resin layer embedded with 3 or 6" Sika® Flexitape Heavy centered over seam. Alternatively Sika® Joint Tape SA can be applied centered over seam. Apply embedment resin layer per below.

##### Transitions Between Dissimilar Materials

Apply 40-45 mil resin layer embedded with Sika® Flexitape Heavy or use Sika® Joint Tape SA centered over edge. Apply embedment/base resin layer per instruction.

##### Embedment/Base Resin Layer with Sika® Reemat Reinforcement

Mixing not required. Apply Sikalastic®-624 WP at the

coverage rate listed in the RoofPro System Guide with a 1/2" nap phenolic resin core roller. Material can also be squeegee or spray applied, in which case it should be backrolled prior to embedding Sika® Reemat. Place Sika® Reemat in wet base resin layer overlapping seams a minimum of 2" (place frayed edge over cut edge of roll) and apply wet roller to topside to saturate completely. After approximately 5 minutes the binder will begin to dissolve allowing the fiber strands to conform to irregular surfaces.

Do not over work once the fibers have conformed to the substrate. Allow to cure 12 hours at 70 °F and 50 % R.H. or until tack free before top resin layer. Keep clean and dry and apply top resin layer within 7 days. If window is exceeded clean with non-sudsing detergent and clean water rinse, and allow to dry prior to application of Sika® Concrete Primer Lo-VOC or Sika® Reactivation Primer. Top Resin Layer with Sika® Reemat Reinforcement Mixing not required. Apply Sikalastic®-624 WP at the coverage rate listed in the RoofPro System Guide with a 1/2" nap phenolic resin core roller. Material can also be squeegee or spray applied, in which case it should also be backrolled. In the case of RoofPro 25 allow the first top resin layer to cure 12 hours at 70 degrees F and 50 % R.H. or until tack free before applying second top resin layer. On top of the complete RoofPro system additional resin layers may be applied with aggregate for slip resistance. Keep clean and dry and apply additional resin layers within 7 days. If window is exceeded clean with non-sudsing detergent and clean water rinse, and allow to dry prior to application of Sika® Concrete Primer Lo-VOC or Sika® Reactivation Primer.

##### Wet on Wet Application with Sika® Fleece Reinforcement

Mixing not required. To primed substrate apply two-thirds of the Sikalastic®-624 WP specified in the RoofPro System Guide with a 1/2" nap phenolic resin core roller. Immediately place specified Sika Fleece into wet resin overlapping seams a minimum of 3" along the edge and 6" end-to-end. Apply wet roller to topside with light pressure to saturate fleece from bottom and ensure air pockets are completely removed. Immediately apply all of remaining one-third of Sikalastic®-624 WP resin specified in the RoofPro System Guide. Ensure even and complete fleece saturation from topside.



### **Aggregated Surfacing**

Supplemental aggregate surfacing is required for all applications that will experience direct foot traffic such as balconies, terraces, walkways, and plazas. It is also recommended for areas that experience maintenance foot traffic. The aggregate surfacing is applied in a supplemental resin layer after the Sikalastic membrane has been installed. Aggregate is not applied into the top layer of the roofing/waterproofing membrane resin.

### **Seed and Back Roll Option**

The Seed and Backroll option is primarily intended for use for maintenance traffic-type applications where enhanced slip resistance is required. Apply Sikalastic®-624 WP resin at 15 mils wet film thickness to the installed, cured membrane system. While the supplemental resin application is still wet seed with kiln dried, iron free aggregate. Back roll the surface to encapsulate the aggregate in the Sikalastic resin.

### **Full Broadcast and Seal Option**

The Full Broadcast and Seal option is intended for use for applications where both enhanced slip resistance and physical protection of the roofing membrane is required. Apply Sikalastic®-624 WP resin at 15 mils wet film thickness to the installed, cured membrane system. While the supplemental resin application is still wet broadcast to rejection (full broadcast/beach) with kiln dried, iron free aggregate. Remove excess aggregate after cure. Seal with an additional coat of Sikalastic resin.

### **Aggregate Selection**

Use clean, rounded or semiangular, oven dried quartz sand with a minimum hardness of 6.5 per the Moh's scale. It should be supplied in prepackaged bags and free of metallic or other impurities. The following size gradations are recommended:  
16–30 or 20–40 mesh for pedestrian traffic systems

### **Overburden Application**

Sikalastic®-624 WP is used as the waterproofing layer under a wide range of overburden materials. Depending on the overburden type, different surfacing, drainage, and protection layers may be required.

### **Protected Membrane Assemblies**

Install Sika drainage mat over the Sikalastic®-624 WP waterproofing system prior to adding the extruded

polystyrene insulation layer. No aggregated membrane surfacing is required.

### **Concrete Pavers with Pedestal Supports**

Install Sika drainage mat over the Sikalastic®-624 WP waterproofing system to provide additional protection of the membrane under the pedestal supports.

### **Tile Adhered in a Cementitious Thin-Set Adhesive**

A full aggregate broadcast surfacing is required to provide an adhesion key for the tile adhesive. Apply a supplemental 15 wet mils of Sikalastic®-624 WP waterproofing resin, followed by a full broadcast of 16-30 or 12-20 kiln-dried sand to refusal, typically 40-50 lbs./100 sf. Remove all loose sand once resin has cured. Do not seal the aggregated surface.

### **Tile in a Cementitious Setting Bed**

Install Sika drainage mat over the Sikalastic®-624 WP waterproofing system prior to installation of the cementitious setting bed, which is typically 1-1/2"-3" in thickness, and can be sloped to create positive drainage. Secure the Sika drainage mat by spot-adhering with Sikaflex® 11 FC to the Sikalastic®-624 WP waterproofing system as required to prevent shifting during setting bed installation. Bi-level drains should be installed to provide drainage capability at the membrane level as well as drainage of the finished surface.

### **Concrete/Asphalt Pavers in a Sand Setting Bed**

Install Sika drainage mat over the Sikalastic®-624 WP waterproofing system prior to installing the sand setting bed, which is typically either graded silica sand or a mix of sand and asphalt. Secure the Sika drainage mat by spot-adhering with Sikaflex® 11 FC to the Sikalastic®-624 WP waterproofing system as required to prevent shifting during setting bed installation. Bi-level drains should be installed to provide drainage capability at the membrane level as well as drainage of the finished surface.

### **Vegetation and Growing Media/Soil**

The selection of a vegetated overburden assembly is specified by a qualified design professional. At a minimum, install Sika® GRS Drain Mat over the Sikalastic®-624 WP waterproofing system prior to application of all other overburden components. Secure the Sika® GRS Drain Mat to the Sikalastic®-624 WP waterproofing system by spot-adhering with Sikaflex® 11

FC as required to prevent shifting during vegetative overburden assembly components . Bi-level drains should be installed to provide drainage capability at the membrane level as well as drainage at grade level.

### Concrete Pavement

Install Sika® 1000 Drain Mat over the Sikalastic®-624 WP waterproofing system prior to application of the new concrete. Secure the Sika® 1000 Drain Mat to the Sikalastic®-624 WP waterproofing system by spot-adhering with Sikaflex® 11 FC as required to prevent shifting during concrete placement. Bi-level drains should be installed to provide drainage capability at the membrane level as well as drainage of the finished surface.

### Asphalt Pavement

Install Sika® 1000 Drain Mat over the Sikalastic®-624 WP waterproofing system, followed by the installation of a ¼" thick asphalt protection board. Secure the Sika® 1000 Drain Mat and asphalt protection board as required to prevent shifting during asphalt pavement placement. Bi-level drains should be installed to provide drainage capability at the membrane level as well as drainage of the finished surface.

### CLEANING OF TOOLS

Clean all tools and application equipment with appropriate solvent immediately after use. Hardened and/or cured material can only be removed mechanically

## OTHER RESTRICTIONS

See Legal Disclaimer.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at

#### Sika Corporation

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
usa.sika.com



#### System Data Sheet

Sikalastic®-624 WP Waterproofing System  
April 2023, Version 01.04  
02091590900000015

usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sikalastic-624WPWaterproofingSystem-en-US-(04-2023)-1-4.pdf