



PRODUCT DATA SHEET

Sikalastic® DTE Primer

Two-component damp tolerant epoxy primer

PRODUCT DESCRIPTION

Sikalastic® DTE Primer is a two-component, damp tolerant epoxy primer used to enhance the adhesion of Sikalastic® RoofPro Systems on damp concrete.

USES

Suitable for use on most sound concrete and masonry substrate surfaces where both a penetrative sealing and surface-lying effect is required.

CHARACTERISTICS / ADVANTAGES

- Low odor, low VOC formulation
- Seals concrete and masonry surfaces, reducing outgassing

PRODUCT INFORMATION

Chemical Base	Two-component epoxy
Packaging	1 gal. kit (0.62 gal. Part A, 0.38 gal. Part B)
Shelf Life	12 months
Storage Conditions	Store dry at 40–95 °F (2–35 °C).
Appearance / Color	Brown
Volatile organic compound (VOC) content	16 g/l (ASTM D-2369-81)

TECHNICAL INFORMATION

Service Temperature	-22–176 °F (-30– 80 °C) intermittent
---------------------	--------------------------------------

APPLICATION INFORMATION

Coverage	200 ft ² /gal on prepared, dry concrete, depending on substrate profile and porosity. 100 ft ² /gal when mixed with 10 lb. 20–40 mesh kiln-dried sand as a 30 mil slurry coat. Note: Rough, porous, or absorbent surfaces will reduce yield and may require an additional coat of primer.
Product Temperature	Condition material to 50–77 °F (10–25 °C) before using for ease of application
Ambient Air Temperature	41 °F (5 °C) min. / 95 °F (35 °C) max.
Relative Air Humidity	80 % R.H. max.
Dew Point	Not for use on surfaces with condensation. Air, substrate and uncured coating must be ≥ 5 °F (3 °C) above dew point.
Substrate Temperature	41 °F (5 °C) min. / 140 °F (60 °C) max.
Substrate Moisture Content	≤ 6 % moisture content Test method: Sika®-Tramex meter No rising moisture according to ASTM (Polyethylene-sheet).
Pot Life	45 minutes
Waiting / Recoat Times	Allow primer to cure completely prior to applying membrane resin. Full cure: 8 hours at 68°F. Apply membrane resin within 24 hours of primer application. Maximum primer exposure is 3 days. Primer exposed longer than 3 days, exposed to water during curing and exhibiting a chalky appearance, must be reprimed. Deteriorated primer must be mechanically removed before repriming

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

- Do not apply on substrates with moisture content greater than 6% by weight, measured by Tramex® Concrete Moisture Encounter Meter
- Minimum age of concrete must be 21-28 days depending on curing and drying conditions
- Do not thin with solvents
- Do not store materials outdoors exposed to sunlight and moisture for prolonged periods
- Do not apply to substrate surfaces where moisture vapor transmission will occur during application and cure. This condition may be checked using ASTM D-4263 (Polyethylene Sheet method).
- Do not apply to a frosted, wet or damp surface (max 6 % moisture content). Allow sufficient time for the substrate to dry after rain or inclement weather, as there is the potential for bonding problems
- On substrates likely to exhibit outgassing apply during falling ambient and substrate temperature. If applied during rising temperature pinholing may occur
- Precautions should be taken to prevent vapors and/or odors from entering the building/structure, including but not limited to turning off and sealing air intake vents and through-wall air conditioners, and other means of vapor/odor ingress during application and cure
- Any repairs required to achieve a level surface must be performed prior to application (consult a Sika representative for guidance on various product solutions). Surface irregularities may reflect through the cured system
- When applying over existing coatings or membranes perform compatibility and adhesion testing, subsequent approval by Technical Services is required
- On grade concrete decks should not be covered with Sikalastic® membrane systems
- Unvented metal pan, split/sandwich slab with encapsulated membrane and/or insulation, cinder fill decks, and lightweight insulating concrete overlays should not be covered with Sikalastic® membrane systems without additional deck evaluation and subsequent approval by Technical Services
- Not recommended for metal substrates
- Allow primer to cure completely prior to applying membrane resin

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

All substrate surfaces shall be clean, dry and sound. Acceptable substrates include: sound concrete and masonry. Reference separate System Data Sheet for specific surface preparation requirements.

MIXING

Mix ratio is 1.6:1 (A:B) by volume. Add Part B into Part A and mix with mechanical mixer (Jiffy) at low speed. Avoid adding air into the primer during mixing. When fully mixed, the primer should be free from streaks and of a uniform amber color. Do not break down kits into smaller quantities. For leveling/sealing slurry, add 10 lb. 20–40 mesh kiln-dried sand to mixed primer and mix with mechanical mixer (Jiffy) until a uniform consistency is achieved.

APPLICATION

Apply by brush or phenolic resin core roller at the recommended rate. Correct amount of primer will saturate the substrate and leave a slight film on the substrate top surface. Apply evenly without puddling. Apply slurry with flat-bladed squeegee or trowel.

Removal

Remove wet primer with solvent. Once cured, primer can only be removed by mechanical means. Strictly follow solvent manufacturer's warnings and instructions for use.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet
Sikalastic® DTE Primer
October 2023, Version 01.03
02091595100000015

SikalasticDTEPrimer-en-US-(10-2023)-1-3.pdf

