

BUILDING TRUST

PRODUCT DATA SHEET

Sarnafil® S 327-80 EnergySmart

80 mil thick PVC thermoplastic membrane

PRODUCT DESCRIPTION

Sarnafil® S 327-80 EnergySmart Roof Membrane is a PVC thermoplastic membrane produced with an integral polyester reinforcement for high strength, is highly reflective, with heat-weldable seams, and a unique lacquer coating applied to the top of the membrane to reduce dirt pick up.

USES

Used in mechanically attached applications with various fastening methods, over various substrates.

AREAS OF APPLICATION

- New Roofs
- Reroofs
- Recovers

CHARACTERISTICS / ADVANTAGES



- Highly reflective
- Excellent tear strength resistance
- Factory applied lacquer coated to reduce dirt pick up
- Hot-air welded seams for long-term performance
- Proven membrane performance
- Superior fire resistance

APPROVALS / STANDARDS

- FM Global
- Underwriters Laboratories
- Underwriters Laboratories of Canada
- ICC Code Compliance ESR 1157
- Miami-Dade County
- Florida Building Code
- NSF/ANSI 347: Platinum Certified
- California Title 24
- LEED / Green Globes

September 2023, Version 08.01 020905012060203002

PRODUCT INFORMATION

Chemical Base	High-quality, PVC membrane containing ultraviolet light stabilizers, flame retardant and polyester scrim reinforcement with a unique lacquer coating on the top surface.				
Recycled Content	9% Pre-consumer, 1% Post-consumer				
Reinforcing Material	Polyester				
Packaging	80 mil (2.0 mm) Membrane 10 ft x 100 ft (3 m x 30 m) roll, 520 lbs (236 kg) per roll 4 rolls per pallet 5 ft x 100 ft (1.5 m x 30 m) roll, 260 lbs (118 kg) per roll 9 rolls per pallet				
Shelf Life	N/A				
Storage Conditions	Store rolls on pallets and fully protected from the weather with clean canvas tarpaulins. Unvented polyethylene tarpaulins are not accepted due to the accumulation of moisture beneath the tarpaulin in certain weather conditions that may affect the ease of membrane weldability.				
Appearance / Color	Top: White, Tan, and Reflective GrayBottom: Gray				
Overall Thickness	80 mil (2.0 mm), minimum thickness 45 mil	(ASTM D-751 (ASTM Type III D-4434 Spec. Requirement			
Thickness Above Scrim	40 mil 16 mil	(ASTM D-7635 (ASTM Type III D-4434 Spec. Requirement)			
TECHNICAL INFORMATION	I				
Resistance to Static Puncture	Pass 33 lbf (15 kg)	(ASTM D-5602 (ASTM Type III D-4434 Spec. Requiremen			
Resistance to Dynamic Puncture	Pass 14.7 ft-lbf (20 J)	(ASTM D-5635 (ASTM Type III D-4434 Spec. Requirement			
Tensile Strength	325 lbf (1445 N) 200 lbf (890 N)	(ASTM D-751 (ASTM Type III D-4434 Spec. Requirement			
Elongation at Break	29.5 & 30.5% MD & CMD ¹ 15 & 15% MD & CMD ¹ ¹ MD = Machine Direction, CMD = Cross Machine Dire	(ASTM D-751 (ASTM Type III D-4434 Spec. Requirement			
Tear Strength	49 lbf (218 N) 45 lbf (200 N)	(ASTM D-752 (ASTM Type III D-4434 Spec. Requirement			
Seam Strength	Pass 75% of original ²	(ASTM D-751) (ASTM Type III D-4434 Spec. Requirement)			
	² Failure occurs through membrane rupture not seam	failure.			
Linear Dimensional Change	-0.14% 0.5%	(ASTM D-1204) (ASTM Type III D-4434 Spec. Requirement)			



020905012060203002



Solar Reflectance	EnergySmart Colors	Initial Solar Reflectance ¹		3-Year Solar Reflectance ¹	
	EnergySmart White ²	0.84		0.76	
	EnergySmart Tan ²	0.73		0.65	
	EnergySmart Reflective Gray ²	0.73		0.66	
	¹ Solar Reflectance testing accord ² Meets LEED, Green Globes, and		eria for Low and	Steep Slope applications.	
Solar Reflectance Index	EnergySmart Colors	Initial Solar Reflectance I	ndex¹	3-Year Solar Reflectance Index ¹	
	EnergySmart White ²	105		93	
	EnergySmart Tan ²	89		78	
	EnergySmart Reflective Gray ²	90		80	
	¹ Solar Reflectance Index calculated according to ASTM E1980. ² Meets LEED, Green Globes, and California's Title 24 criteria for Low and Steep Slope applications.				
Thermal Emittance	EnergySmart Colors	Initial Therma Emittance ¹	al	3-Year Thermal Emittance ¹	
	EnergySmart White ²	0.86		0.85	
	EnergySmart Tan ²	0.85		0.86	
	EnergySmart Reflective Gray ²	0.89		0.88	
	¹ Thermal Emittance testing according to ASTM C1371, Slide Method. ² Meets LEED, Green Globes, and California's Title 24 criteria for Low and Steep Slope applications.				
Low Temperature Bend	Pass Pass -40°F (-40°C)	(ASTM D-2136) (ASTM Type III D-4434 Spec. Requirement)			
Weight Change after Immersion in Water	1.8% ± 3.0%		(ASTM Type I	(ASTM D-5 II D-4434 Spec. Requireme	
UV Exposure	10,000 hours 5,000 hours		(ASTM Type I	(ASTM G-1 II D-4434 Spec. Requireme	
	Cracking (7x magnification)	None			
	Crazing (7x magnification)	None			
Retention of Properties after Heat Ageing	Tensile Strength, % of of Elongation, % of original Tensile Strength, % of o	al: Pass	(ASTM Type I	(ASTM D-7. (ASTM D-7. II D-4434 Spec. Requireme	

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

AVAILABILITY/WARRANTY

AVAILABILITY

Elongation, % of original: 90

From Sika Corporation – Roofing Authorized Applicators for use within Sarnafil or Sikaplan systems.

Product Data Sheet

Sarnafil® S 327-80 EnergySmart September 2023, Version 08.01 020905012060203002



WARRANTY

Upon successful completion of the installed roof by the Sika Authorized Applicator in compliance with Sika requirements, Sika Corporation will provide a warranty to the Building Owner via the Sika Authorized Applicator.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

APPLICATION

Sarnafil S 327 is rolled out after proper preparation of the approved substrate and fastened to the roof deck with appropriate mechanically attached system with Sarnafasteners in accordance with Sika's technical requirements. Sarnafil S 327 seams are heat-welded together by trained operators using hot-air welding equipment. Different mechanically attached systems require different application methods. Please consult Sika's Specifications or Applicator Handbook for detailed installation procedures.

MAINTENANCE

Standard maintenance of Sarnafil and Sikaplan systems should include regular inspections of flashings, drains, and termination sealants at least twice a year and after each storm.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at https://usa.sika.com/en/group/SikaCorp/termsandconditions.html or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue Lyndhurst, NJ 07071 Phone: +1-800-933-7452 Fax: +1-201-933-6225 usa.sika.com



Product Data Sheet Sarnafil® S 327-80 EnergySmart September 2023, Version 08.01 020905012060203002



