

# LITHOCHROME®

## Antiquing Release Pro

LITHOCHROME® Antiquing Release Pro is an odorless, high performance, colored, powder stamp tool release.



A SIKA BRAND

### ■ 1. Product Description:

LITHOCHROME™ Antiquing Release Pro is a color powdered bond breaker used with stamping mats, texturing skins and texture rollers. It also provides accent colors that compliment or contrast with the underlying concrete surface. Additionally, it enhances the transfer of the detailed pattern and texture, and prolongs the surface life of the stamping mat or texturing tool. It is compatible with integrally colored concrete, color hardened concrete and stampable cementitious overlays.

LITHOCHROME® Antiquing Release Pro is a finely ground, streak free powder that is a blend of UV-resistant pigments and water repelling additives. It is broadcast over the concrete surface prior to placing the stamping or texturing tools. As the imprinting tool is pressed into the plastic concrete surface, a portion of the LITHOCHROME® Antiquing Release Pro is embedded into the textured surface of the concrete. As the tool is removed, it breaks cleanly, without marring the colored concrete surface. Upon washing and sealing, the difference in color between the base concrete and the release creates a visually attractive, antiqued look to the concrete. The added color visually enhances the depth of the texture. The amount of release agent retained on the concrete will vary. LITHOCHROME® Antiquing Release Pro can be used in matching or contrasting colors to create a variety of effects. A combination of colors can add interesting shading and highlights to the finished concrete surface. LITHOCHROME® Antiquing Release Pro is available in 14 standard colors.

### ■ 2. Limitations:

LITHOCHROME® Antiquing Release Pro should not be used as the primary coloring agent. It should not be troweled into concrete. Do not use as a curing compound. LITHOCHROME® Antiquing Release Pro will produce variegated colors and is a function of concrete mix design, timing, method of application and removal, method of imprinting, and weather.

Avoid over application, which may minimize the depth of texture. Cover and protect adjacent surfaces from contamination during application and residue removal. Consider using SCOFIELD® Liquid Release BG if contamination is a concern, particularly on interior applications or when imprinting cementitious overlays.

LITHOCHROME® Antiquing Release Pro is retained on the surface by a mechanical bond. It will require an application of a sealer to enhance the longevity of the antiqued coloration.

### ■ 3. Packaging:

LITHOCHROME® Antiquing Release Pro is packaged in 30 lb. (13.6 kg) plastic pails.

#### ■ 3.1. Shelf Life:

Indefinite, when stored in original, unopened containers, in dry storage.

### ■ 4. Coverage:

Coverage varies depending on timing, application technique, method of finishing, surface texture prior to imprinting, coloration

effect desired, and other conditions. For most applications, the coverage rate is approximately 3-4 lb./100 sq. ft. (1.4-1.8 kg/9.3 m<sup>2</sup>) which equates to 750-1,000 sq. ft. (70-93 m<sup>2</sup>) per 30 lb. (13.6 kg) pail. Experienced release applicators can achieve coverage up to 1,200 sq. ft. (111 m<sup>2</sup>) per 30 lb. (13.6 kg) pail. Note: Creating the antiqued color effects requires skill and practice. Prior to the installation of any job site concrete, make and approve a representative sample for each color effect desired to determine the timing, application rate, finishing, removal, and sealing techniques.

### ■ 5. Application:

Cover and protect adjacent surfaces near the work area prior to applying LITHOCHROME® Antiquing Release Pro. This is especially critical on windy days. The concrete surface should be lightly troweled before the application. Rougher finishes may require more material to achieve the proper coverage and may retain an excessive amount of release powder after the removal process, thereby affecting the color of the surface.

Immediately prior to the placement of stamping mats, texturing skins or texture rollers, broadcast LITHOCHROME® Antiquing Release Pro uniformly over the surface with a soft bristled, 6 inch mason's brush. Apply enough release so that the moist sheen on the concrete surface is covered. Do not apply over standing bleed water. LITHOCHROME® Antiquing Release Pro should not be broadcast for more than a few feet or from above the knee to minimize drifting outside of the work area. Multiple colors of LITHOCHROME® Antiquing Release Pro may be used for more unique colorations. Once applied, do not work the surface with a float or a trowel. The surface of the imprinting tools should also be lightly brushed with the release powder.

Timing is critical; applied too early, the antiquing release may be difficult to remove; applied too late, and most of the antiquing release will be removed during the removal and cleaning process.

An antiquing method may also be applied to concrete surfaces and cementitious overlays after the imprinting process has been completed. This method is useful when more accent color is desired on a new installation or as a means of rejuvenating an older, unsealed weathered surface. Detailed information about this process can be found in the LITHOTIQUE™ Antiquing Agent Technical Data Sheet. All information is available for download online at [www.scofield.com](http://www.scofield.com) and at point of purchase.

### ■ 6. Removal:

After imprinting has been completed, the residual LITHOCHROME® Antiquing Release Pro must be removed to prevent tracking and loss of adhesion when a sealer is applied. Do not clean the surface until the concrete has cured for 24-48 hours. Cold temperatures may delay the cleaning process, since the concrete will require a longer cure time. Cleaning too soon may cause complete loss of the antiqued color, as well as damage to the colored concrete substrate. A small area should be test cleaned to evaluate the cleaning process and the resultant colorations.

Sweep or vacuum excess release, and follow by scrubbing with a



soft bristled brush and water. Water can be applied with a garden hose or a high pressure wash. With either method, take care not to damage the surface of the curing concrete or remove too much antiqued colorations. Protect adjacent surfaces from runoff. Dispose of all residual materials in accordance with local, state, and federal regulations. The antiquing release is mechanically bonded to the concrete, so the surface must be sealed and maintained to preserve its antiqued appearance over time.

#### ■ 7. Sealing:

After LITHOCHROME® Antiquing Release Pro has been removed from the surface, SCOFIELD® Cureseal™ 700 should be applied after the concrete has thoroughly dried for a minimum of 72 hours at 70°F (21°C). Approve final color before the sealer is applied. Sealed surfaces may become slippery when wet. Sealed surfaces will require maintenance. Read the SCOFIELD® Cureseal™ 700 Technical Data Sheet before installing product. All information is available for download online at [www.scofield.com](http://www.scofield.com) and at point of purchase.

#### ■ 8. Quality Control:

Cast a job site sample at least 21 days prior to the installation for approval of color and finish. Utilize all materials, tools, and techniques from the actual job in the mock-up. Consistent batching, pouring, finishing, curing, sealing, and preparation techniques, will ensure the uniformity of architectural concrete. Verify adequate wet and dry slip resistance. Discuss maintenance requirements. Site visits by Scofield personnel are for making technical recommendations only and not for supervising or providing quality control. Maintenance requirements should also be discussed.

#### ■ WARNING

Use with adequate ventilation. Applicators and all other on-site personnel must wear an OSHA-NIOSH approved dust respirator while applying or working around this product. Avoid contact with skin and eyes. Wear rubber gloves to protect skin and safety eye goggles. Close containers after each use. Use good hygiene when handling this product. Wash and bathe after each use. Keep out of reach of children and animals. Do not take internally. Dispose of all residual material in accordance with local, state, and federal regulations. Read the Safety Data Sheet (SDS) before handling and using product. All information is available for download online at [www.scofield.com](http://www.scofield.com) and at point of purchase.

#### ■ WARRANTY

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at <http://usa.sika.com/> or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. **Nothing contained in any**

**Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.**

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor.

**NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS**



**Suggested Short Form Specification for Scofield CHROMIX® Admixtures for Color-Conditioned® Concrete:**

Add Scofield CHROMIX® Admixtures for Color-Conditioned® Concrete to concrete in proportion required to obtain [ ] color and mix according to manufacturer's instructions. Maintain mix characteristics for all concrete having matching finish. Concrete shall contain a minimum of five sacks of cement per cubic yard and have a maximum slump of 4 inches. Do not use calcium chloride. Place and finish concrete according to industry standards. [Optional: Apply Scofield LITHOCHROME® Antiquing Release Pro according to manufacturer's instructions using [ ] color and imprint using Scofield LITHOTEX® Pavecrafters® using [ ] pattern according to manufacturer's instructions.] Cure and seal concrete with 2 coats SCOFIELD® Cureseal™ 700 with slip-resistive additive according to manufacturer's instructions.

**Suggested Short Form Specification for Scofield LITHOCHROME® Color Hardener:**

Apply Scofield LITHOCHROME® Color Hardener to fresh concrete according to manufacturer's instructions using [ ] color and a minimum of [ ] pounds per 100 square feet. Apply Scofield LITHOCHROME® Antiquing Release Pro according to manufacturer's instructions using [ ] color and imprint using Scofield LITHOTEX® Pavecrafters® using [ ] pattern. Seal concrete with 2 coats Scofield SCOFIELD® Cureseal™ 700 with slip-resistive additive according to manufacturer's instructions.



A SIKA BRAND

■ Scofield customer service: 1 800 800 9900  
4155 Scofield Road, Douglasville, GA 30134 voice: 770 920 6000 fax: 770 920 6060

[www.scofield.com](http://www.scofield.com)