

# ZONO-PATCH®

## Commercial Product Data Sheet



Zono-Patch is a unique mixture of cementitious binders, low density fine aggregates and proprietary additives specifically designed for repair of lightweight insulating concrete roof deck surfaces of all types. It is fast setting, provides resistance to moisture, and provides the ability to feather-edge thin coat applications.

Contact Siplast for information on approved product uses.

### USES: SLIC PATCHING COMPOUND

Wet Density	Min. 65 pcf (1041 kg/m <sup>3</sup> )
Dry Density	Min. 35 pcf (560.6 kg/m <sup>3</sup> )
Compressive Strength	Min: 300 psi (21.1 kg/m <sup>2</sup> ) at 3 days
Thickness	≤ 2 in
Base Ply Fastener Withdrawal Resistance	Min. 40 lb (18.1 kg)
Temperature Limitations	Do not install below 32°F during 24 hours following application of product.
Container Yield	Pails: 7.0 BF (16.4 L) Bag: 13.0 BF (30.6 L)

### PRODUCT INFORMATION

#### Application

Refer to the applicable Siplast Technical Guide for detailed application information.



#### Storage and Handling

Zono-Patch contains cementitious binders, which must be kept dry and away from moisture at all times. Failure to protect stored product from moisture will cause the binders to set in the container, rendering the product unusable. Therefore, store the product in a dry location until ready for jobsite delivery and use. On the jobsite, the product must be protected from moisture until it is mixed with water. When stored in a dry location, the product has a maximum shelf life of 12 months.

See product packaging and the Safety Data Sheet for specific information on the safe handling of this product.

#### Packaging

Pallet: 42 in x 48 in (107 cm x 122 cm) wooden pallet

Weight Per Container: 22 lb (10.0 kg)  
Pails Per Pallet: 42

Weight Per Bag: 40 lb (18.14 kg)  
Bags Per Pallet: 50

Pallets Per Truckload: 20