

SODABOND DRYWALL

Revision: 07/26/21

Page 1 of 2

Technical Data:

Base	Single component polyurethane
Consistency	Semi-collapsible foam adhesive
Curing system	Moisture cure at room temperature
Curing time (*)	About 1 hour
Skin formation (*)	About 8 minutes
Full strength (*)	About 24 hours
Post expansion	Minimal
Shear strength after 14 days (ASTM D6464)	67 psi
Shear strength after 14 days (after cyclic exposure) (ASTM D6464)	53 psi
Tensile strength after 14 days (ASTM D6464)	32 psi
Temperature resistance	-40°F to +194°F +248°F (up to max. 1 hour)
Application temperature	+41°F to +95°F

(*) Measured at 68°F / 65% R.H. These values may vary depending on ambient factors such as temperature, humidity and type of substrate.

Product description

Soudabond Drywall is a ready-to-use, single component, high strength, fast curing polyurethane adhesive that is semi-collapsible after dispensing. It is used for clean, efficient and economical permanent drywall bonding in building and construction. Soudabond Drywall does not contain CFC's or HCFC's.

Product characteristics:

- One can of Soudabond Drywall replaces up to 10 quart cartridges of traditional adhesive.
- Saves application time (up to 25%) and money over the use of traditional adhesives.
- Excellent initial bond.
- Economical in use due to precise application.
- Can be applied at temperatures between +41°F and +95°F.
- Limited post expansion for fast and precise installation of drywall.
- Substantial space and weight savings compared to conventional PU adhesives, bonding mortars, etc.
- Fast curing.
- Solvent-free.

- Resistant to a variety of solvents, paints and chemicals.
- Does not age or rot, mold and mildew resistant, but not UV resistant.
- Water resistant (not watertight).
- Prevents screw pops.
- Tested according to ASTM D6464.

Application:

- Clean, efficient and economical permanent bonding of all common types of drywall panels.
- Other construction adhesive applications.

Form of delivery:

Color: Champagne

Packaging: 26 oz aerosol can (12 per box)

Shelf life:

24 months from date of production in unopened packaging with cool (41°F to 77°F) and dry storage. Cans must be stored upright to prevent blockage of spray valve. Once opened, keep container tightly closed and use within a short period.

Remark: This information and all further technical advice are based on SODAL present knowledge and experience. However, SODAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, SODAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SODAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SODAL reserves the right to make any changes according to technological progress or further developments.

Soudabond Drywall

Revision: 07/26/21

Page 2 of 2

Substrates:

All usual substrates such as drywall, lumber, plywood, OSB, particle board, concrete, metals, masonry, stone and plaster. Adhesive surfaces must be stable, clean, without bubbles and free of separating agents such as talcum, grease, oils, etc. Not suitable for use on substrates with a water film or standing water.

Any cement slurries and sinter layers on mineral substrates must be removed mechanically.

Does not adhere to PE, PP, PTFE and silicone.

All substrates should be tested for suitability with regard to adhesion and compatibility.

Instructions for use:

Prior to using the product, cover all adjacent areas for protection against soiling. In windy conditions, precautions must be taken to ensure that Soudabond Drywall cannot contaminate components, objects or persons in the vicinity. Good ventilation must be ensured for indoor use. The product is flammable during dispensing.

Wear protective goggles and gloves. Tightly screw the can to the thread in the gun and shake the gun about 30 seconds with the valve pointing downwards so that the contents are mixed well to ensure an optimum adhesive quality and high yield. After extended periods of non-use, the can must be shaken again to obtain the required adhesive quality! With the control knob on the gun, adjust the adhesive bead to the required diameter of about 1/2". (The emptier the can, the more the control knob needs to be opened). The can must be held vertical during application.

1. Apply the adhesive in uniform beads of 1/2" centrally onto the mounting studs. A distance of 0.4 to 0.8 inch must be maintained between the gun nozzle and substrate while spraying.
2. Place the drywall panel against the gel adhesive within the skin formation time of 8 minutes after dispensing. Do not remove and reapply panels as this will damage the adhesive structure and reduce the adhesive strength substantially. At high temperatures and low humidity in particular, curing can be accelerated by lightly spraying the adhesive bead with water.
3. Once the panels are set, and while keeping pressure, secure the boards additionally with mechanical fasteners.

Application temperature:

Surface: +41°F to +95°F

Can Temperature: +41°F to +77°F (optimal +59°F to +77°F)

If required, slowly bring the can to the optimal temperature by placing in cool or warm water.

Cleaning: With GUN & FOAM CLEANER or SWIPEX prior to curing, subsequently with PU REMOVER or remove mechanically.

Repair option: With Soudabond Drywall

Safety recommendations:

Observe the standard industrial hygiene procedures. Wear protective goggles and gloves. Remove cured adhesive mechanically, never remove with a flame.

For further information on product safety and handling, refer to the information on the container.

Standards and approvals:

- ASTM D6464