

## SoudaFoam Flex

Revision date: 11/12/2015

Page 1 of 3

### Technical data:

|   |  |
|---|--|
| Base  | Polyurethane   |
| Consistency   | Stable Foam, thixotropic                                 |
| Curing System   | Moisture Cure  |
| Skin Formation  | Ca. 6 minutes (20°C/65% R.H.)                            |
| Drying time   | Dustfree after 20-25 min. at 20°C                        |
| Curing Rate   | Ca 1 hour for a 1.2" bead                                |
| Foam Yield  | 24 oz yields 6.6 gallon of cured foam                    |
| Yield (ASTM C-1536) (for 24 oz)   | 4005 linear feet (1221m) @ ¼" (6.4 mm) dia. bead         |
| Shrink  | Very limited   |
| Postexpansion   | Very limited   |
| Cellular Structure  | Fine cellular structure                                  |
| Specific Gravity  | Ca. 25kg/m <sup>3</sup> (extruded, fully cured)          |
| Temperature Resistance  | -40°F to +194°F when cured                               |
| Colour  | Champagne  |
| Fire Class  | B2 (DIN4102 part2)                                       |
| Air penetration (DIN 18542)   | $a < 0.1 \text{ m}^3 / [\text{h.m.}(\text{daPa})^{2/3}]$ |
| Vapour permeability (DIN EN ISO 12572)  | Water diffusion resistance $\mu = 20$                    |
| Water Absorption  | 1% Vol.  |
| Acoustic Rating (EN ISO 717-1)  | $R_{ST,W} (C; C_{tr}) = 60\text{dB} (-1; -4)$            |
| Permanent deformation at pressure (ISO 1856) – 50% compression 22h 1 day recovery | Ca 6%  |
| Insulation Factor (DIN52612)  | 35mW/meter Kelvin  |
| Shear Strength (ASTM C-273)   | 3.6 psi  |
| Elastic Recovery (ISO 1856)   | Until 92% (75% compressed)                               |
| Compressive Strength (ASTM D-1621)  | 2.2 psi  |
| Change of Volume (DIN EN ISO 10563)   | <5%  |

( values may change slightly due temperature, humidity , surface and way of application )

### Product:

SoudaFoam Flex is a one-component, self-expanding, ready to use polyurethane foam. It is fitted with a plastic adaptor head for use with a foam applicator gun. It contains CFC-free propellants, which are completely harmless to the ozone layer.

The product has a minimal expansion after application (less than 50%) and is therefore very economical to use.

The foam is very elastic and has a very high Acoustic Rating and Thermal Insulation value.

This information and all further technical advice are based on SOUDAL present knowledge and experience. However, SOUDAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, SOUDAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SOUDAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SOUDAL reserves the right to make any changes according to technological progress or further developments.

---

## SoudaFoam Flex

---

Revision date: 11/12/2015

Page 2 of 3

### Characteristics:

- Very high elastic recovery
- Copes with extreme mechanical movement without cracking
- Excellent adhesion on most substrates (except Teflon, PE and PP)
- High thermal and acoustical insulation performance
- Very good filling capacities
- Excellent stability (no shrink or post expansion)
- Very precise application due to the foam applicator gun system
- Low expansion
- Good compressibility

### Application areas:

- Good applicability in expanding joints.
- Vibrating constructions
- Use as fixing foam while minimizing noise transmission
- Impact and shock damping
- Sealing of window- and doorframes
- Filling of cavities
- Sealing of all openings in roof constructions
- Creation of a soundproof screen
- Connecting of insulation materials and roof constructions
- Application of a soundproofing layer on motors
- Improving thermal isolation in cooling/heating systems

### Shelf life:

- 18 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°.
  - Always store can with the valve pointed upwards

### Packaging:

Aerosol can 24 oz with gun adaptor.

### Application:

*Shake the aerosol can for at least 20 seconds.* Fit the gun on the adaptor. **Moisten surfaces with a water sprayer prior to application to have the optimal performance to elasticity, noise reduction and cellular structure**. Fill joints and cavities for 65 %, as the foam will continue to expand slightly.

Repeat shaking regularly during application. If you have to work in layers repeat moistening after each layer. Fresh foam can be removed using Soudal Foamcleaner or acetone. Cured foam can only be removed mechanically. Working temperature 41°F to 95°F. (68°F-77°F recommended) Due to the flexibility of the product, it is recommended to use a sharp knife to cut the foam.

### Health and safety recommendation:

- Apply the usual industrial hygiene.
- Wear gloves and safety goggles.
- never burn away PU-foam
- Consult the label for more information.

### Remarks:

- Work in layers and repeat moistening after each layer
- cured PU foam must be protected from UV-radiation by painting or applying a top layer of sealant (silicone, MS Polymer, acrylic and PU-sealant)
- Respect the cleaning and storage instructions enclosed in the Foam Gun box.

### Norms and certificates:

- Fire rating B2 ( DIN 4102-1 ) Prüfzeugnis P-SAC 02/III-164 (MFPA)
- Heat transmission rating ( DIN 52612) PB 070598.1 Hu ( MPA Bau Hannover)
- Acoustic Insulation ( EN ISO 717-1) PB 16733428 (IFT Rosenheim)
- Vapour penetration ( DIN EN ISO 12572 ) PB 50933428 ( IFT)
- Air Penetration (DIN 18452) PB 10533428 (IFT Rosenheim)

---

This information and all further technical advice are based on SOUDAL present knowledge and experience. However, SOUDAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, SOUDAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SOUDAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SOUDAL reserves the right to make any changes according to technological progress or further developments.