

ProSTUD® 250PDS125-15G90

Product Description 2 1/2" PROSTUD®25 (15MIL)
G90
Coating G90

Physical Properties

Design Thickness (in) 0.0158
Minimum Thickness (in) 0.015
Web Width (in) 2.5
Flange Width (in) 1.25
Stiffening Lip (in) 0.25
Yield Strength (ksi) 50



Gross Section Properties

Cross Sectional Area (A)	0.085
Moment of Inertia (Ix)	0.088
Radius of Gyration (Rx)	1.02
Gross Moment of Inertia (Iy)	0.018
Gross Radium of Gyration (Ry)	0.459


Effective Section Properties

Effective Area (Ae)	0.033
Moment of Inertia for deflection (Ixe)	0.08
Section Modulus (Sxe)	0.044
Allowable Bending moment (Ma)	1318
Allowable shear force in web (U)(Vag)	147
Allowable shear force in web (P) (Vanet)	141

Torsional Properties

St. Venant torsion constant (J x 1000)	0.00704
Warping constant (Cw)	0.023
Distance from shear center to neutral axis (Xo)	-0.959
Radii of gyration (Ro)	1.473
Torsional flexural constant (Beta)	0.576
Unbraced Length (Lu)	24.5

Punch Out



Notes

1. Calculated properties are based on AISI S100-12, North American Specification for Design of Cold-Formed Steel Structural Members and AISI S220-15, North American Standard for Cold-Formed Steel Framing - NonStructural Members.
2. Effective Properties incorporate the strength increase from the cold work of forming as applicable per AISI A7.2.
3. Tabulated gross properties including torsional properties are based on full-unreduced cross section of the studs, away from punchouts.
4. For deflection calculations, use the effective moment of inertia.
5. Allowable moment includes cold-work of forming.
6. Allowable moment is taken as the lowest value based on load or distortional buckling. Distortional buckling strength is based on a k-phi = 0.

ASTM & Code Standards

• AISI S100-07 & S220-11 • Meets or exceeds ASTM C645 & C754 • ASTM E119, E72, & E90 • ATI CCRR-0207 • LA RR 26019

Mill Steel Framing LEED Green Credits

- MR Credit 2** • ConstructionWaste Management – Mill Steel Framing steel framing is 100% recyclable
- MR Credit 4** • Recycled Content – Mill Steel Framing products contain no less than 25.5% post-consumer and 6.8% pre-consumer recycled content
- MR Credit 5** • Regional Materials – Mill Steel Framing has manufacturing facilities in Indiana, Alabama & Texas
- V4 MR Credits** • Building Product Disclosure and Optimization EPD (1 point)
• Materials Ingredients (1 point) – Construction and Demolition Waste Management (1 point)

