

www.millsteelframing.com | 2905 Lucerne Dr. SE Grand Rapids, MI 49546 | (812) 670-4195

ProTRAK®

250PDT200-15

Product Description Coating	2 1/2" ProTrak®25 (15mil) 2" leg G40
Physical Properties Design Thickness (in) Minimum Thickness (in) Web Width (in) Flange Width (in) Yield Strength (ksi)	0.0158 0.015 2.5 2 50

Gross Section Properties	
Cross Sectional Area (A)	0.103
Moment of Inertia (lx)	0.124
Radius of Gyration (Rx)	1.098
Gross Moment of Inertia (ly)	0.045
Gross Radium of Gyration (Ry)	0.662

Effective Section Properties	
Effective Area (Ae)	0.021
Moment of Inertia for deflection (lxe)	0.064
Section Modulus (Sxe)	0.024
Allowable Bending moment (Ma)	720
Allowable shear force in web (U)(Vag)	143

Torsional Properties		
St. Venant torsion constant (J x 1000)	0.00854	
Warping constant (Cw)	0.052	
Distance from shear center to neutral axis (Xo)	-1.431	
Radii of gyration (Ro)	1.921	
Torsional flexural constant (Beta)	0.445	

ASTM & Code Standards

- AISI S100-07 & S220-11
- Meets or exceeds ASTM C645 & C754
- ASTM E119, E72, & E90
- ATI CCRR-0207
- LA RR 26019

Section Properties Table Notes

- Calculated properties are based on AISI S100-12, North American Specification for Design of Cold-Formed Steel Structural Members and AISI S220-15, North American Standard for Cold-Formed Steel Framing -NonStructural Members.
- 2. Effective Properties incorporate the strength increase from the cold work of forming as applicable per AISI A7.2.
- 3. Tabulated gross properties including torsional properties are based on fullunreduced cross section of the studs, away from punchouts.
- 4. For deflection calculations, use the effective moment of inertia.
- 5. Allowable moment includes cold-work of forming.
- Allowable moment is taken as the lowest value based on loacl or distortional buckling. Distortional buckling strength is based on a k-phi = 0.

Mill Steel Framing LEED Green Credits

MR Credit 2
MR Credit 4
ConstructionWaste Management – Mill Steel Framing steel framing is 100% recyclable
Recycled Content – Mill Steel Framing products contain no less than 25.5% post-consumer and 6.8% pre-consumer recycled content
Regional Materials – Mill Steel Framing has manufacturing facilities in Indiana, Alabama & Texas
Building Product Disclosure and Optimization EPD (1 point)
Materials Ingredients (1 point) – Construction and Demolition Waste Management (1 point)

