

www.millsteelframing.com │ 2905 Lucerne Dr. SE Grand Rapids, MI 49546 │ (812) 670-4195

ProTRAK® 400PDT200-15G90

4" ProTrak®25 (15mil) 2" leg **Product Description**

G90

G90 Coating

Physical Properties

Design Thickness (in) 0.0158 Minimum Thickness (in) 0.015 Web Width (in) 4 Flange Width (in) 2 50 Yield Strength (ksi)



Gross Section Properties	
Cross Sectional Area (A)	0.126
Moment of Inertia (lx)	0.344
Radius of Gyration (Rx)	1.65
Gross Moment of Inertia (ly)	0.052
Gross Radium of Gyration (Ry)	0.642

Effective Section Properties Effective Area (Ae) 0.021 Moment of Inertia for deflection (Ixe) 0.168 Section Modulus (Sxe) 0.039 Allowable Bending moment (Ma) 1178 Allowable shear force in web (U)(Vag) 89

Torsional Properties	
St. Venant torsion constant (J x 1000)	0.01052
Warping constant (Cw)	0.151
Distance from shear center to neutral axis (Xo)	-1.24
Radii of gyration (Ro)	2.162
Torsional flexural constant (Beta)	0.671

ASTM & Code Standards

- AISI S100-07 & S220-11
- Meets or exceeds ASTM C645 & C754
- ASTM E119, E72, & E90
- ATI CCRR-0207
- LA RR 26019

Section Properties Table Notes

- 1. Calculated properties are based on AISI S100-12, North American Specification for Design of Cold-Formed Steel Structural Members and AISI S220-15, North American Standard for Cold-Formed Steel Framing -NonStructural Members.
- 2. Effective Properties incorporate the strength increase from the cold work of forming as applicable per AISI A7.2.
- 3. Tabulated gross properties including torsional properties are based on fullunreduced cross section of the studs, away from punchouts.
- 4. For deflection calculations, use the effective moment of inertia.
- 5. Allowable moment includes cold-work of forming.
- 6. Allowable moment is taken as the lowest value based on load or distortional buckling. Distortional buckling strength is based on a k-phi = 0.

Mill Steel Framing LEED Green Credits

MR Credit 2 MR Credit 4

- ConstructionWaste Management Mill Steel Framing steel framing is 100% recyclable
- Recycled Content Mill Steel Framing products contain no less than 25.5% post-consumer and 6.8% pre-consumer recycled content

MR Credit 5 V4 MR Credits · Regional Materials - Mill Steel Framing has manufacturing facilities in Indiana, Alabama & Texas

• Building Product Disclosure and Optimization EPD (1 point)

Materials Ingredients (1 point) – Construction and Demolition Waste Management (1 point)

