

www.millsteelframing.com │ 2905 Lucerne Dr. SE Grand Rapids, MI 49546 │ (812) 670-4195

**ProTRAK®** 250PDT125-30G60

2 1/2" ProTrak®30MIL (30mil) **Product Description** 

1-1/4" leg G60

G60 Coating

**Physical Properties** 

Design Thickness (in) 0.0312 Minimum Thickness (in) 0.0296 Web Width (in) 2.5 Flange Width (in) 1.25 Yield Strength (ksi) 33



Gross Section Properties	
Cross Sectional Area (A)	0.156
Moment of Inertia (lx)	0.169
Radius of Gyration (Rx)	1.042
Gross Moment of Inertia (ly)	0.025
Gross Radium of Gyration (Ry)	0.397

## **Effective Section Properties** Effective Area (Ae) 0.084 Moment of Inertia for deflection (Ixe) 0.14 Section Modulus (Sxe) 0.087 Allowable Bending moment (Ma) 1713

Torsional Properties	
St. Venant torsion constant (J x 1000)	0.05054
Warping constant (Cw)	0.029
Distance from shear center to neutral axis (Xo)	-0.763
Radii of gyration (Ro)	1.351
Torsional flexural constant (Beta)	0.681

## **ASTM & Code Standards**

- AISI S100-07 & S220-11
- Meets or exceeds ASTM C645 & C754
- ASTM E119, E72, & E90
- ATI CCRR-0207
- LA RR 26019

## **Section Properties Table Notes**

- 1. Calculated properties are based on AISI S100-12, North American Specification for Design of Cold-Formed Steel Structural Members and AISI S220-15, North American Standard for Cold-Formed Steel Framing -NonStructural Members.
- 2. Effective Properties incorporate the strength increase from the cold work of forming as applicable per AISI A7.2.
- 3. Tabulated gross properties including torsional properties are based on fullunreduced cross section of the studs, away from punchouts.
- 4. For deflection calculations, use the effective moment of inertia.
- 5. Allowable moment includes cold-work of forming.
- 6. Allowable moment is taken as the lowest value based on load or distortional buckling. Distortional buckling strength is based on a k-phi = 0.

## Mill Steel Framing LEED Green Credits

MR Credit 2 MR Credit 4

ConstructionWaste Management – Mill Steel Framing steel framing is 100% recyclable

832

Allowable shear force in web (U)(Vag)

• Recycled Content - Mill Steel Framing products contain no less than 25.5% post-consumer and 6.8% pre-consumer recycled content

MR Credit 5 V4 MR Credits · Regional Materials - Mill Steel Framing has manufacturing facilities in Indiana, Alabama & Texas

• Building Product Disclosure and Optimization EPD (1 point)

· Materials Ingredients (1 point) - Construction and Demolition Waste Management (1 point)

