

ProTRAK®

362PDT200-30G60

Product Description


3 5/8" ProTrak®30MIL (30mil)
2" leg G60

Coating

G60

Physical Properties

Design Thickness (in)	0.0312
Minimum Thickness (in)	0.0296
Web Width (in)	3.625
Flange Width (in)	2
Yield Strength (ksi)	33



Gross Section Properties

Cross Sectional Area (A)	0.238
Moment of Inertia (Ix)	0.549
Radius of Gyration (Rx)	1.52
Gross Moment of Inertia (Iy)	0.099
Gross Radium of Gyration (Ry)	0.645

Effective Section Properties

Effective Area (Ae)	0.089
Moment of Inertia for deflection (Ixe)	0.397
Section Modulus (Sxe)	0.16
Allowable Bending moment (Ma)	3159
Allowable shear force in web (U)(Vag)	755

Torsional Properties

St. Venant torsion constant (J x 1000)	0.07712
Warping constant (Cw)	0.237
Distance from shear center to neutral axis (Xo)	-1.274
Radii of gyration (Ro)	2.086
Torsional flexural constant (Beta)	0.627

ASTM & Code Standards

- AISI S100-07 & S220-11
- Meets or exceeds ASTM C645 & C754
- ASTM E119, E72, & E90
- ATI CCRR-0207
- LA RR 26019

Section Properties Table Notes

1. Calculated properties are based on AISI S100-12, North American Specification for Design of Cold-Formed Steel Structural Members and AISI S220-15, North American Standard for Cold-Formed Steel Framing - NonStructural Members.
2. Effective Properties incorporate the strength increase from the cold work of forming as applicable per AISI A7.2.
3. Tabulated gross properties including torsional properties are based on full-unreduced cross section of the studs, away from punchouts.
4. For deflection calculations, use the effective moment of inertia.
5. Allowable moment includes cold-work of forming.
6. Allowable moment is taken as the lowest value based on local or distortional buckling. Distortional buckling strength is based on a $k\text{-}\phi = 0$.

Mill Steel Framing LEED Green Credits

- MR Credit 2** • ConstructionWaste Management – Mill Steel Framing steel framing is 100% recyclable
- MR Credit 4** • Recycled Content – Mill Steel Framing products contain no less than 25.5% post-consumer and 6.8% pre-consumer recycled content
- MR Credit 5** • Regional Materials – Mill Steel Framing has manufacturing facilities in Indiana, Alabama & Texas
- V4 MR Credits** • Building Product Disclosure and Optimization EPD (1 point)
• Materials Ingredients (1 point) – Construction and Demolition Waste Management (1 point)

