

www.millsteelframing.com | 2905 Lucerne Dr. SE Grand Rapids, MI 49546 | (812) 670-4195

**ProTRAK®** 400PDT200-30

Product Description 4" ProTrak®30MIL (30mil) 2"

leg

Coating G40

**Physical Properties** 

Design Thickness (in) 0.0312
Minimum Thickness (in) 0.0296
Web Width (in) 4
Flange Width (in) 2
Yield Strength (ksi) 33



Gross Section Properties	
Cross Sectional Area (A)	0.249
Moment of Inertia (lx)	0.682
Radius of Gyration (Rx)	1.654
Gross Moment of Inertia (ly)	0.102
Gross Radium of Gyration (Ry)	0.639

## Effective Section Properties Effective Area (Ae) Moment of Inertia for deflection (lxe) Section Modulus (Sxe) Allowable Bending moment (Ma) 0.639 0.089 0.089 0.502 3480

Torsional Properties	
St. Venant torsion constant (J x 1000)	0.08091
Warping constant (Cw)	0.297
Distance from shear center to neutral axis (Xo)	-1.232
Radii of gyration (Ro)	2.16
Torsional flexural constant (Beta)	0.674

## **ASTM & Code Standards**

- AISI S100-07 & S220-11
- Meets or exceeds ASTM C645 & C754
- ASTM E119, E72, & E90
- ATI CCRR-0207
- LA RR 26019

## **Section Properties Table Notes**

- Calculated properties are based on AISI S100-12, North American Specification for Design of Cold-Formed Steel Structural Members and AISI S220-15, North American Standard for Cold-Formed Steel Framing -NonStructural Members.
- 2. Effective Properties incorporate the strength increase from the cold work of forming as applicable per AISI A7.2.
- 3. Tabulated gross properties including torsional properties are based on full-unreduced cross section of the studs, away from punchouts.
- 4. For deflection calculations, use the effective moment of inertia.
- 5. Allowable moment includes cold-work of forming.
- 6. Allowable moment is taken as the lowest value based on loacl or distortional buckling. Distortional buckling strength is based on a k-phi = 0.

## Mill Steel Framing LEED Green Credits

Allowable shear force in web (U)(Vag)

MR Credit 2

• ConstructionWaste Management - Mill Steel Framing steel framing is 100% recyclable

683

 • Recycled Content – Mill Steel Framing products contain no less than 25.5% post-consumer and 6.8% pre-consumer recycled content

MR Credit 5

• Regional Materials - Mill Steel Framing has manufacturing facilities in Indiana, Alabama & Texas

**V4 MR Credits** • Building Product Disclosure and Optimization EPD (1 point)

· Materials Ingredients (1 point) - Construction and Demolition Waste Management (1 point)

