

www.millsteelframing.com │ 2905 Lucerne Dr. SE Grand Rapids, MI 49546 │ (812) 670-4195

**ProTRAK®** 362PDT125-33G90

3 5/8" ProTrak®33MIL (33mil) **Product Description** 

1-1/4" leg G90

G90 Coating

**Physical Properties** 

Design Thickness (in) 0.0346 Minimum Thickness (in) 0.0329 Web Width (in) 3.625 Flange Width (in) 1.25 Yield Strength (ksi) 33



Gross Section Properties	
Cross Sectional Area (A)	0.212
Moment of Inertia (lx)	0.432
Radius of Gyration (Rx)	1.429
Gross Moment of Inertia (ly)	0.03
Gross Radium of Gyration (Ry)	0.377

## **Effective Section Properties** Effective Area (Ae) 0.105 Moment of Inertia for deflection (Ixe) 0.375 Section Modulus (Sxe) 0.17 Allowable Bending moment (Ma) 3358 Allowable shear force in web (U)(Vag) 1024

Torsional Properties	
St. Venant torsion constant (J x 1000)	0.08444
Warping constant (Cw)	0.074
Distance from shear center to neutral axis (Xo)	-0.659
Radii of gyration (Ro)	1.618
Torsional flexural constant (Beta)	0.834

## **ASTM & Code Standards**

- AISI S100-07 & S220-11
- Meets or exceeds ASTM C645 & C754
- ASTM E119, E72, & E90
- ATI CCRR-0207
- LA RR 26019

## **Section Properties Table Notes**

- 1. Calculated properties are based on AISI S100-12, North American Specification for Design of Cold-Formed Steel Structural Members and AISI S220-15, North American Standard for Cold-Formed Steel Framing -NonStructural Members.
- 2. Effective Properties incorporate the strength increase from the cold work of forming as applicable per AISI A7.2.
- 3. Tabulated gross properties including torsional properties are based on fullunreduced cross section of the studs, away from punchouts.
- 4. For deflection calculations, use the effective moment of inertia.
- 5. Allowable moment includes cold-work of forming.
- 6. Allowable moment is taken as the lowest value based on load or distortional buckling. Distortional buckling strength is based on a k-phi = 0.

## Mill Steel Framing LEED Green Credits

MR Credit 2 MR Credit 4

- ConstructionWaste Management Mill Steel Framing steel framing is 100% recyclable
- Recycled Content Mill Steel Framing products contain no less than 25.5% post-consumer and 6.8% pre-consumer recycled content
  - · Regional Materials Mill Steel Framing has manufacturing facilities in Indiana, Alabama & Texas

MR Credit 5 V4 MR Credits

• Building Product Disclosure and Optimization EPD (1 point)

· Materials Ingredients (1 point) - Construction and Demolition Waste Management (1 point)

