

www.millsteelframing.com | 2905 Lucerne Dr. SE Grand Rapids, MI 49546 | (812) 670-4195

## Structural Stud 600S300-54

Product Description 16 GA GALV 6.00" WEB X 3.00"

FLANGE C-STUD .054 MIN

**GAUGE** 

Coating G60

**Physical Properties** 

 Design Thickness (in)
 0.0566

 Minimum Thickness (in)
 0.0538

 Web Width (in)
 6.0000

 Flange Width (in)
 3.0000

 Stiffening Lip (in)
 0.6250

 Yield Strength (ksi)
 50.0000




Gross Section Properties	
Cross Sectional Area (A)	0.726
Weight of Member (lb/ft)	2.47
Section Modulus (Sx)	1.440
Moment of Inertia (lx)	4.320
Radius of Gyration (Rx)	2.439
Gross Moment of Inertia (ly)	0.875
Gross Radium of Gyration (Ry)	1.098

Effective Section Properties	
Moment of Inertia for deflection (lxe)	4.015
Section Modulus (Sxe)	1.106
Allowable Bending moment (Ma)	33.13
Allowable shear force in web (U)(Vag)	2823
Allowable shear at punch (Vanet)	1947

Torsional Properties	
St. Venant torsion constant (J x 1000)	0.775
Warping constant (Cw)	6.452
Distance from shear center to neutral axis (Xo)	-2.299
Radii of gyration (Ro)	3.527
Torsional flexural constant (Beta)	0.575

### **Punch Out**



# ASTM & Code Standards

- AISI S100-12 & ICC ES ESR-4062
- Framing meets ASTM A1003, A653 & C955

#### **Notes**

- Calculated properties are based on AISI S100-16, North American Specification for Design of Cold-Formed Steel Structural Members.
- 2. The centerline bend radius is based on inside corner radii shown in thickness chart.
- 3. Effective properties incorporate the strength increase from the cold work of forming as applicable per AISI A3.3.2.
- 4. Tabulated gross properties are based on fullunreduced cross section of the studs, away from punch outs.
- 5. For deflection calculations, use the effective moment of inertia.
- 6. Allowable moment includes cold-work of forming.

### **Mill Steel Framing LEED Green Credits**

MR Credit 2
MR Credit 4

- ConstructionWaste Management Mill Steel Framing steel framing is 100% recyclable
- Recycled Content Mill Steel Framing products contain no less than 25.5% post-consumer and 6.8% pre-consumer recycled content

MR Credit 5

• Regional Materials - Mill Steel Framing has manufacturing facilities in Indiana, Alabama & Texas

**V4 MR Credits** • Building Product Disclosure and Optimization EPD (1 point)

· Materials Ingredients (1 point) - Construction and Demolition Waste Management (1 point)

