

## Structural Track 250T150-68G90

**Product Description** 14 GA GALV 2.50" WEB x 1.50"  
**FLANGE TRACK .068 MIN**  
**GAUGE G90**  
**Coating** G90

### Physical Properties

**Design Thickness (in)** 0.0713  
**Minimum Thickness (in)** 0.0677  
**Web Width (in)** 2.5  
**Flange Width (in)** 1.5  
**Yield Strength (ksi)** 50



### Gross Section Properties

Cross Sectional Area (A)	0.391
Weight of Member (lb/ft)	1.33
Section Modulus (Sx)	0.344
Moment of Inertia (Ix)	0.472
Radius of Gyration (Rx)	1.099
Gross Moment of Inertia (Iy)	0.089
Gross Radius of Gyration (Ry)	0.478

### Effective Section Properties

Moment of Inertia for deflection (Ixe)	0.445
Section Modulus (Sxe)	0.276
Allowable Bending moment (Ma)	8.27
Allowable shear force in web (U)(Vag)	3199

### Torsional Properties

St. Venant torsion constant (J x 1000)	0.6627
Warping constant (Cw)	0.114
Distance from shear center to neutral axis (Xo)	-0.953
Radii of gyration (Ro)	1.531
Torsional flexural constant (Beta)	0.613

### ASTM & Code Standards

- AISI S100-12 & ICC ES ESR-4062
- Framing meets ASTM A1003, A653 & C955

### Notes

1. Calculated properties are based on AISI S100-16, North American Specification for Design of Cold-Formed Steel Structural Members.
2. The centerline bend radius is based on inside corner radii shown in thickness chart.
3. Effective properties incorporate the strength increase from the cold work of forming as applicable per AISI A3.3.2.
4. Tabulated gross properties are based on full-unreduced cross section of the studs, away from punchouts.
5. For deflection calculations, use the effective moment of inertia.
6. Allowable moment includes cold-work of forming.
7. Web depth for track sections is equal to the nominal height plus 2 times the design thickness plus the bend radius. Hems on non-structural rack sections are ignored.

## Mill Steel Framing LEED Green Credits

- MR Credit 2** • ConstructionWaste Management – Mill Steel Framing steel framing is 100% recyclable
- MR Credit 4** • Recycled Content – Mill Steel Framing products contain no less than 25.5% post-consumer and 6.8% pre-consumer recycled content
- MR Credit 5** • Regional Materials – Mill Steel Framing has manufacturing facilities in Indiana, Alabama & Texas
- V4 MR Credits** • Building Product Disclosure and Optimization EPD (1 point)  
 • Materials Ingredients (1 point) – Construction and Demolition Waste Management (1 point)

