

www.millsteelframing.com | 2905 Lucerne Dr. SE Grand Rapids, MI 49546 | (812) 670-4195

Structural Track 362T150-54G90

Product Description	16 GA GALV 3.62" WEB x 1.50" FLANGE TRACK .054 MIN GAUGE G90
Coating	G90
Physical Properties	
Design Thickness (in)	0.0566
Minimum Thickness (in)	0.0538
Web Width (in)	3.625
Flange Width (in)	1.5
Yield Strength (ksi)	50

Gross Section Properties	
Cross Sectional Area (A)	0.374
Weight of Member (lb/ft)	1.27
Section Modulus (Sx)	0.431
Moment of Inertia (lx)	0.823
Radius of Gyration (Rx)	1.483
Gross Moment of Inertia (ly)	0.08
Gross Radium of Gyration (Ry)	0.462

Effective Section Properties	
Moment of Inertia for deflection (lxe)	0.735
Section Modulus (Sxe)	0.325
Allowable Bending moment (Ma)	9.74
Allowable shear force in web (U)(Vag)	3372

Torsional Properties	
St. Venant torsion constant (J x 1000)	0.3997
Warping constant (Cw)	0.202
Distance from shear center to neutral axis (Xo)	-0.844
Radii of gyration (Ro)	1.768
Torsional flexural constant (Beta)	0.772

ASTM & Code Standards

- AISI \$100-12 & ICC ES ESR-4062
- Framing meets ASTM A1003, A653 & C955

Notes

- 1. Calculated properties are based on AISI S100-16, North American Specification for Design of Cold-Formed Steel Structural Members.
- 2. The centerline bend radius is based on inside corner radii shown in thickness chart.
- 3. Effective properties incorporate the strength increase from the cold work of forming as applicable per AISI A3.3.2.
- 4. Tabulated gross properties are based on full-unreduced cross section of the studs, away from punchouts.
- 5. For deflection calculations, use the effective moment of inertia.
- 6. Allowable moment includes cold-work of forming.
- 7. Web depth for track sections is equal to the nominal height plus 2 times the design thickness plus the bend radius. Hems on non-structural rack sections are ignored.

Mill Steel Framing LEED Green Credits

MR Credit 2	 ConstructionWaste Management – Mill Steel Framing steel framing is 100% recyclable
MR Credit 4	 Recycled Content – Mill Steel Framing products contain no less than 25.5% post-consumer
	and 6.8% pre-consumer recycled content
MR Credit 5	• Regional Materials – Mill Steel Framing has manufacturing facilities in Indiana, Alabama & Texas
V4 MR Credits	Building Product Disclosure and Optimization EPD (1 point)
	• Materials Ingredients (1 point) – Construction and Demolition Waste Management (1 point)

