

www.millsteelframing.com | 2905 Lucerne Dr. SE Grand Rapids, MI 49546 | (812) 670-4195

# Structural Track 600T200-54

Product Description	16 GA GALV 6.00" WEB x 2.00" FLANGE TRACK .054 MIN GAUGE
Coating	G60
<b>Physical Properties</b> Design Thickness (in) Minimum Thickness (in) Web Width (in) Flange Width (in) Yield Strength (ksi)	0.0566 0.0428 6 2 50

Gross Section Properties	
Cross Sectional Area (A)	0.565
Weight of Member (lb/ft)	1.92
Section Modulus (Sx)	1.015
Moment of Inertia (lx)	3.146
Radius of Gyration (Rx)	2.359
Gross Moment of Inertia (ly)	0.203
Gross Radium of Gyration (Ry)	0.6

Effective Section Properties	
Moment of Inertia for deflection (lxe)	2.641
Section Modulus (Sxe)	0.717
Allowable Bending moment (Ma)	21.48
Allowable shear force in web (U)(Vag)	2728

Torsional Properties	
St. Venant torsion constant (J x 1000)	0.6037
Warping constant (Cw)	1.381
Distance from shear center to neutral axis (Xo)	-1.038
Radii of gyration (Ro)	2.646
Torsional flexural constant (Beta)	0.846

### **ASTM & Code Standards**

- AISI \$100-12 & ICC ES ESR-4062
- Framing meets ASTM A1003, A653 & C955

#### Notes

- Calculated properties are based on AISI S100-16, North American Specification for Design of Cold-Formed Steel Structural Members.
- 2. The centerline bend radius is based on inside corner radii shown in thickness chart.
- 3. Effective properties incorporate the strength increase from the cold work of forming as applicable per AISI A3.3.2.
- 4. Tabulated gross properties are based on full-unreduced cross section of the studs, away from punchouts.
- 5. For deflection calculations, use the effective moment of inertia.
- 6. Allowable moment includes cold-work of forming.
- 7. Web depth for track sections is equal to the nominal height plus 2 times the design thickness plus the bend radius. Hems on non-structural rack sections are ignored.

## Mill Steel Framing LEED Green Credits

MR Credit 2	<ul> <li>ConstructionWaste Management – Mill Steel Framing steel framing is 100% recyclable</li> </ul>
MR Credit 4	Recycled Content – Mill Steel Framing products contain no less than 25.5% post-consumer
	and 6.8% pre-consumer recycled content
MR Credit 5	• Regional Materials – Mill Steel Framing has manufacturing facilities in Indiana, Alabama & Texas
V4 MR Credits	Building Product Disclosure and Optimization EPD (1 point)
	• Materials Ingredients (1 point) – Construction and Demolition Waste Management (1 point)

