

www.millsteelframing.com │ 2905 Lucerne Dr. SE Grand Rapids, MI 49546 │ (812) 670-4195

Structural Track 250T125-33

Product Description 20 GA GALV 2.50" WEB x 1.25"


FLANGE TRACK .033 MIN

GAUGE

Coating G60

Physical Properties

Design Thickness (in)0.0346Minimum Thickness (in)0.0329Web Width (in)2.5Flange Width (in)1.25Yield Strength (ksi)33



Gross Section Properties	
Cross Sectional Area (A)	0.173
Weight of Member (lb/ft)	0.59
Section Modulus (Sx)	0.145
Moment of Inertia (lx)	0.192
Radius of Gyration (Rx)	1.054
Gross Moment of Inertia (ly)	0.027
Gross Radium of Gyration (Ry)	0.397

Effective Section Properties	
Moment of Inertia for deflection (Ixe)	0.166
Section Modulus (Sxe)	0.103
Allowable Bending moment (Ma)	2.03
Allowable shear force in web (U)(Vag)	1024

Torsional Properties	
St. Venant torsion constant (J x 1000)	0.069
Warping constant (Cw)	0.033
Distance from shear center to neutral axis (Xo)	-0.76
Radii of gyration (Ro)	1.358
Torsional flexural constant (Beta)	0.687

ASTM & Code Standards

- AISI S100-12 & ICC ES ESR-4062
- Framing meets ASTM A1003, A653 & C955

Notes

- Calculated properties are based on AISI S100-16, North American Specification for Design of Cold-Formed Steel Structural Members.
- 2. The centerline bend radius is based on inside corner radii shown in thickness chart.
- 3. Effective properties incorporate the strength increase from the cold work of forming as applicable per AISI A3.3.2.
- 4. Tabulated gross properties are based on full-unreduced cross section of the studs, away from punchouts.
- 5. For deflection calculations, use the effective moment of inertia.
- 6. Allowable moment includes cold-work of forming.
- 7. Web depth for track sections is equal to the nominal height plus 2 times the design thickness plus the bend radius. Hems on non-structural rack sections are ignored.

Mill Steel Framing LEED Green Credits

MR Credit 2 MR Credit 4

- ConstructionWaste Management Mill Steel Framing steel framing is 100% recyclable
- Recycled Content Mill Steel Framing products contain no less than 25.5% post-consumer and 6.8% pre-consumer recycled content

MR Credit 5

• Regional Materials - Mill Steel Framing has manufacturing facilities in Indiana, Alabama & Texas

V4 MR Credits • Building Product Disclosure and Optimization EPD (1 point)

· Materials Ingredients (1 point) - Construction and Demolition Waste Management (1 point)

