

### STEGO™WRAP 10-MIL CLASS A VAPOUR RETARDER

A STEGO INDUSTRIES, LLC INNOVATION | VAPOUR RETARDERS 07 26 00, 03 30 00 | VERSION: 3 MAR 2022

### 1. PRODUCT NAME

#### STEGO WRAP 10-MIL CLASS A VAPOUR RETARDER

### 2. MANUFACTURER

Stego Industries, LLC 216 Avenida Fabricante, Suite 101 San Clemente, CA 92672 USA Sales, Technical Assistance +1 (877) 464-7834 international@stegoindustries.com stegoindustries.com



### 3. PRODUCT DESCRIPTION

USES: Stego Wrap Class A is used as an exceptional vapour retarder.

COMPOSITION: Stego Wrap Class A is a multi-layer plastic extrusion manufactured with only high grade prime, virgin, polyolefin resins.

ENVIRONMENTAL FACTORS: Stego Wrap Class A can be used in systems for the control of soil gases (radon, methane), soil poisons (oil by-products) and sulfates.

### 4. TECHNICAL DATA

#### TABLE 1: PHYSICAL PROPERTIES OF STEGO WRAP 10-MIL CLASS A VAPOUR RETARDER

PROPERTY	TEST	RESULTS	
Under Slab Vapour Retarders	ASTM E1745 Class A, B & C – Standard Specification for Water Vapour Retarders Used in Contact with Soil or Granular Fill under Concrete Slabs	Exceeds Class A, B & C	
	Permeance Units (perms):	ng/(m <sup>2</sup> *s*Pa)	gr/(ft <sup>2</sup> *hr*in-Hg)
Water Vapour Permeance	ASTM F1249 – Test Method for Water Vapour Transmission Rate Through Plastic Film and Sheeting Using a Modulated Infrared Sensor	1.45	0.0254
Permeance After Conditioning	ASTM E154 Section 8, F1249 – Permeance after wetting, drying, and soaking	1.47	0.0258
(ASTM E1745 Sections 7.1.2 - 7.1.5)	ASTM E154 Section 11, F1249 – Permeance after heat conditioning  ASTM E154 Section 12, F1249 – Permeance after low temperature conditioning  ASTM E154 Section 13, F1249 – Permeance after soil organism exposure	1.48 1.38 1.40	0.0259 0.0241 0.0245
Puncture Resistance	ASTM D1709 – Test Method for Impact Resistance of Plastic Film by Free-Falling Dart Method	3,006 grams	
Tensile Strength	ASTM D882 – Test Method for Tensile Properties of Thin Plastic Sheeting	8.9 kN/m (50.6 lbf/in)	
Thickness		0.25 mm (10 mil)	
Roll Dimensions	width x length: area:	4.3 m x 64 m (14' x 210') 273 m <sup>2</sup> (2,940 ft <sup>2</sup> )	
Roll Weight		63 kg (140 lb)	

#### STEGO™ WRAP 10-MIL CLASS A VAPOUR RETARDER

A STEGO INDUSTRIES, LLC INNOVATION | VAPOUR RETARDERS 07 26 00, 03 30 00 | VERSION: 3 MAR 2022

### 5. INSTALLATION

UNDER SLAB: Unroll Stego Wrap Class A over an aggregate, sand or tamped earth base. Overlap all seams a minimum of 150 mm (6") and tape using Stego™ Tape or Stego™ Crete Claw™ Tape. All penetrations must be sealed using a combination of Stego Wrap Class A and Stego accessories.

For additional information, please refer to Stego's complete installation instructions.

## 6. AVAILABILITY & COST

Stego Wrap Class A is available through our network of building supply distributors. For current cost information, contact your local Stego Wrap distributor or Stego Industries' Sales Representative.

# 7. WARRANTY

Stego Industries, LLC believes to the best of its knowledge, that specifications and recommendations herein are accurate and reliable. However, since site conditions are not within its control, Stego Industries does not guarantee results from the use of the information provided herein. Stego Industries, LLC does offer a limited warranty on Stego Wrap. Please see **stegoindustries.com/legal** 

### 8. MAINTENANCE

None required.

## 9. TECHNICAL SERVICES

Technical advice, custom CAD drawings, and additional information can be obtained by contacting Stego Industries or by visiting the website.

**Email:** international@stegoindustries.com

Contact Number: +1 (877) 464-7834
Website: stegoindustries.com

FILING SYSTEMS: stegoindustries.com

