

Sto RFP

80225 Sto RFP



Technical Data

REPORT	TEST METHOD	TEST CRITERIA	TEST RESULTS
Adhesion (psi) [kPa]	ASTM C-297	28 days	> 13 EPS board* [90] > 30 Dens-Glass® Gold** [207]* > 25 Gypsum sheathing* [172] > 95 Concrete block [655] > 50 Concrete [345]
Water Absorption (oz/ft ² /hr) [kg/m ² /hr]	Lab Method	28 days	0.331 [0.099]
Flexural Strength (psi) [kPa]	ASTM C-203	28 days	65 [448]
Impact Strength	EIMA 101.86	Standard impact classification	Pass
Accelerated Weathering	ASTM G-23	2000 hours	Pass
Freeze/Thaw Resistance	EIMA 101.01	No deterioration at 60 cycles	Pass @ 90 cycles
Surface Burning	ASTM E-84	< 25 Flame Spread < 450 Smoke Developed	0 20
VOC (g/L)	This product complies with US EPA (40 CFR 59) and South Coast AQMD (Rule 1113) VOC emission standards for architectural coatings. VOC less than 50 g/L.		

A ready-mixed, acrylic based plaster material used as a base coat in StoTherm® ci System.

Coverage
85-100 ft² (7.9-9.3 m²) at the recommended dry thickness of 1/16" (1.6 mm) over properly rasped Sto Insulation Board.

Coverages may vary depending on application technique and surface conditions.

Packaging
5 gal. pail (19 L).

Shelf Life
12 months, if properly stored and sealed.

Storage
Protect from extreme heat [90°F (32°C)], freezing, and direct sunlight.

* Substrate failure

** Dens-Glass® Gold is a registered trademark of the G-P Gypsum Corp.

Features	Benefits
1 Ready-mixed	Ready to use; no cement added at job site
2 Polymer-based	Eliminates efflorescence risk; increases finish coverage
3 100% Acrylic polymers	Superior flexural strength; resists cracking
4 Vapor permeable	Allows substrate to breathe naturally; resist blisters caused by trapped vapor
5 Water-based	Safe, non-toxic; cleans up with water
6 Low VOC	Meets South Coast Air Quality Management District Requirements

Sto RFP

Surface Preparation

Concrete and masonry surfaces: Surfaces must be clean, dry, and free of frost, damage, and all bond-inhibiting materials, including dirt, efflorescence, form oil and other foreign matter. Loose or damaged material must be removed by water blasting, sandblasting or mechanical wire brushing and repaired. Avoid application over irregular surfaces. Refer to ASTM D-4258 and ASTM D-4261 for complete details on methods of

preparing cementitious substrates for coatings. **StoTherm® ci Systems:** Insulation board must be rasped and free of all bond-inhibiting materials.

StoQuik® Silver System: Sheathing surface must be free of all bond-inhibiting materials, damage or deterioration.

Health And Safety

Health Precautions

Product is water-based. As with any chemical construction product, exercise care when handling.

WARNING!

Causes eye and skin irritation.

Precautionary Statement

Wash hands thoroughly after handling. Wear protective gloves/protective clothing/eye protection/face protection.

FIRST AID MEASURES

Eye Contact: Immediately flush eyes with plenty of water for at least 15 to 20 minutes. Ensure adequate flushing of the eyes by separating the eyelids with fingers. Get immediate medical attention.

Skin Contact: Immediately wash skin with plenty of soap and water for 15 to 20 minutes, while removing contaminated clothing and shoes. Get medical attention if irritation develops or persists.

Inhalation: If inhaled, remove to fresh air. If not breathing, give artificial respiration or give oxygen by trained personnel. Seek immediate medical attention.

Ingestion: If swallowed, do NOT induce vomiting. Call a physician or poison control center immediately. Never give anything by mouth to an unconscious person.

Spills

Collect with suitable absorbent material such as cotton rags.

Disposal

Dispose of in accordance with local, state or federal regulations.

Warning

KEEP CONTAINER CLOSED WHEN NOT IN USE. KEEP OUT OF THE REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. Consult the Safety Data Sheet (SDS) at www.stocorp.com for further health and safety information.

LIMITED WARRANTY

This product is subject to a written limited warranty which can be obtained free of charge from Sto Corp.

Refer to Sto Specifications for more complete information on proper use and handling of this product.

Mixing

Mix with a clean, rust-free electric drill and paddle. A small amount of clean, potable water may be added to aid workability.

Application

Apply only to sound and clean, dry, properly prepared, frost-free surfaces.

StoTherm® ci Systems/StoQuik® Silver System:

Apply Sto RFP with spray equipment such as the StoSilo System or Sto's M-8 Spray Pump, or apply manually with a stainless steel trowel, to an approximate thickness of 1/8" (3 mm). Work horizontally or vertically in strips of 40" (1 m), and immediately embed Sto Mesh into the wet Sto RFP by troweling from the center to the edges of the mesh. Avoid wrinkles in the mesh and smooth the base coat to eliminate trowel marks. Sto RFP must completely hide the reinforcing mesh when dry. Reapply additional base coat, if necessary, to hide the reinforcing mesh as soon as first application is dry. Once applied, the working time is up to 25 minutes depending upon material, ambient temperatures and surface conditions.

Crack Repair: Embed 6" (152 mm) wide Sto Mesh centered over the crack in Sto RFP and feather along edges.

Curing/Drying

Sto RFP dries within 24 hours under normal conditions [70°F (21°C), 50% RH]. Full drying varies depending on temperature/humidity and surface conditions.

Cool damp conditions retard drying and may require extended periods of protection from rain and freezing.

Protect from rain, freezing and continuous high humidity until completely dry.

Clean Up

Clean tools and equipment with water immediately after use. Dried material can only be removed mechanically.

Limitations

- Use RFP only when surface and ambient temperatures are above 40°F (4°C) and below 100°F (38°C) during application and drying period.
- Sloped surfaces: refer to Sto details..
- Sto RFP should not be used as a finish coat.
- Sto RFP should not be used on weather-exposed horizontal or below grade surfaces or where immersion in water may occur

Sto Corp.
3800 Camp Creek Parkway
Building 1400, Suite 120
Atlanta, GA 30331

Tel: 404-346-3666
Toll Free: 1-800-221-2397
Fax: 404 346-3119

www.stocorp.com

S155-80225
Revision Number: A3.0
Date: 06/2016

Attention

This product is intended for use by qualified professional contractors, not consumers, as a component of a larger construction assembly as specified by a qualified design professional, general contractor or builder. It should be installed in accordance with those specifications and Sto's instructions. Sto Corp. disclaims all, and assumes no, liability for on-site inspections, for its products applied improperly, or by unqualified persons or entities, or as part of an improperly designed or constructed building, for the nonperformance of adjacent building components or assemblies, or for other construction activities beyond Sto's control. Improper use of this product or use as part of an improperly designed or constructed larger assembly or building may result in serious damage to this product, and to the structure of the building or its components. **STO CORP. DISCLAIMS ALL WARRANTIES EXPRESSED OR IMPLIED EXCEPT FOR EXPLICIT LIMITED WRITTEN WARRANTIES ISSUED TO AND ACCEPTED BY BUILDING OWNERS IN ACCORDANCE WITH STO'S WARRANTY PROGRAMS WHICH ARE SUBJECT TO CHANGE FROM TIME TO TIME.** For the fullest, most current information on proper application, clean-up, mixing and other specifications and warranties, cautions and disclaimers, please refer to the Sto Corp. website, www.stocorp.com.