


StoGuard[®] RapidSeal[™] CMU Crack Repair

Detail No.: 20.01R

Date: January 2010



Notes:

1) Prepare substrate by:

- striking mortar joints flush
- removing mortar droppings or other debris from surface
- cleaning any dirt, efflorescence or other bond-inhibiting materials
- repairing any cracks or damage to the wall surface.

2) Repair minor up to 1/8-inch (3mm) nonstructural cracks with StoGuard RapidSeal. Apply a bead of StoGuard Rapid Seal to the crack, then smooth with application tool. Allow StoGuard RapidSeal to dry before applying coatings. StoGuard RapidSeal may feel slightly tacky, but if it does not transfer with finger pressure coating may begin.

3) Apply StoGuard coating as soon as StoGuard RapidSeal is dry-to-touch and within 48 hours. Final surface shall be free of voids and pinholes that are continuous to the substrate.

4) StoGuard RapidSeal can be coated with:
 • Sto Gold Coat[®]
 • Sto EmeraldCoat[®]
 • StoGuard[®] VaporSeal[™]
 Refer to appropriate Product Bulletin.

Attention

Sto products are intended for use by qualified professional contractors, not consumers, as a component of a larger construction assembly as specified by a qualified design professional, general contractor or builder. They should be installed in accordance with those specifications and Sto's instructions. Sto Corp. disclaims all, and assumes no, liability for on-site inspections, for its products applied improperly, or by unqualified persons or entities, or as part of an improperly designed or constructed building, for the nonperformance of adjacent building components or assemblies, or for other construction activities beyond Sto's control. Improper use of Sto products or use as part of an improperly designed or constructed larger assembly or building may result in serious damage to Sto products, and to the structure of the building or its components. **STO CORP. DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED EXCEPT FOR EXPLICIT LIMITED WRITTEN WARRANTIES ISSUED TO AND ACCEPTED BY BUILDING OWNERS IN ACCORDANCE WITH STO'S WARRANTY PROGRAMS WHICH ARE SUBJECT TO CHANGE FROM TIME TO TIME.** For the fullest, most current information on proper application, clean-up, mixing and other specifications and warranties, cautions and disclaimers, please refer to the Sto Corp. website, www.stocorp.com.

www.stocorp.com