

AWAPLAN™

APPLICATION INSTRUCTIONS

STORAGE

All roofing materials must be properly stored in a dry location prior to application. Store materials on platforms off the ground or roof deck and covered with opaque waterproof tarps that have been properly tied down. During cold or damp environmental conditions, place the rolls in a heated area. Wet or damp roofing materials must never be used in the construction of a TAMKO roof assembly. To prevent the rolls from becoming deformed, unroll the rolls on the roof and allow the sun to relax them. Any areas where accidental damage occurs to the roll must be cut out before the material is installed. All marked factory splices must be cut out and covered with like material.

ROOF DRAINAGE

Proper and adequate drainage of roof surfaces is critical, and a minimum slope of ¼ in. per ft. is recommended. Positive drainage is required and is the responsibility of those involved in the design and construction of the roof deck and supporting structure.

COLD WEATHER APPLICATION

Roof application below 40°F can result in problems. Special measures must be taken to insure proper performance of the roofing system. Store materials in a protected environment and limit the amount of time that they are exposed to cold conditions on the roof.

Since moppings of asphalt tend to chill quickly on a cold deck or insulation, components of the roofing system must be installed rapidly, close to the mop, well embedded, and completely broomed. Asphalt must not be overheated to compensate for rapid cooling. AWAPLAN should not be applied with asphalt that is below 400°F at the point of application. Do not mop more than 4 ft. in front of the roll. Immediately press the roll into the hot asphalt by applying pressure to the factory core in the roll.

The AWAPLAN may need to be unrolled and allowed to relax to flatten and warm up prior to application. If this is necessary, unroll the AWAPLAN and expose the back side of the sheet to the sun. The sun will warm and relax the sheet, then the AWAPLAN can be rerolled and installed. You may choose to cut the AWAPLAN into lengths of 12 to 18 ft. before you reroll them. Storage in a heated area immediately prior to application is recommended. Remember the “mop and flop” method of installation is not acceptable with AWAPLAN.

LAYING THE ROOF MEMBRANE

The roof deck must be smooth, dirt free, and moisture free. All exposed (open) edges must have wood nailers. In the case of steel or masonry roof decks, wood nailers shall be provided around the perimeter of the roof and around all openings so flashings may be securely fastened. All masonry and metal surfaces that are to receive a mopping of asphalt must first be primed with TAMKO's Asphalt Primer. Begin all plies of roofing membrane at the low points. Application will not be acceptable if at any point the flow of water is against the laps.



AWAPLAN™

APPLICATION INSTRUCTIONS

BASE PLY

Install one or more base plies prior to the application of AWAPLAN. TAMKO Glass-Base®, Type 43 Organic Base Sheet, Tam-Ply IV®, and Versa-Base® are the recommended base ply materials. Alternatively, base sheets that meet the requirements of ASTM D4601, Type II; ASTM D2178, Type IV or Type VI; ASTM D2626; ASTM D6163, ASTM D6164 or ASTM D4897, Type II are acceptable. The base sheet shall have minimum side laps of 2 in. and end laps of 4 in. Not all application methods apply to all base sheets. Certain base plies are limited in the manner in which they may be applied. Consult the base ply manufacturer's application instructions for the base ply used and the current National Roofing Contractor Association (NRCA) Manual - Membrane Roof Systems for installation instructions. See the chart below for information regarding acceptable application methods of TAMKO base sheets.

Product Name	Application Method		
	Hot Asphalt	Mechanically Fastened	Cold Process Adhesive
TAMKO Glass-Base®	Yes	Yes	No
Tam-Ply IV®	Yes	No	No
Type 43 Coated Organic Base	Yes	Yes	No
Versa-Base®	Yes	Yes	Yes

HOT ASPHALT APPLICATION

Interply moppings of asphalt shall consist of approximately 23 lbs. (±15%) per 100 sq. ft. of roof area. For any surfaces including insulating materials which absorb asphalt, it may be necessary to apply the asphalt in greater quantities to assure adequate adhesion. Avoid excessive interply moppings as slippage may result. The asphalt must meet ASTM D312, Type III for slopes up to ¼ in. and Type IV for slopes up to 3 in. The asphalt must be a minimum of 400°F at the point of application. MOP NO FURTHER THAN 4 FT. IN FRONT OF THE ROLL. Immediately press the roll into the hot asphalt by applying pressure to the factory core in the roll. The AWAPLAN membrane shall have side laps of 4 in. and end laps of 6 in. The entire sheet, including the side and end laps, must be totally adhered in asphalt with no void areas. A small amount of asphalt protruding from the side and end laps is acceptable. However, care should be taken to avoid excessive amounts of asphalt at the lap. All exposed asphalt in excess of ¼ in. width should be covered with granules.

COLD ADHESIVE APPLICATION

TAM-PRO® M3 Adhesive or TAM-PRO 856 Premium SBS Adhesive may be applied using a 3/16" V notched squeegee or TAM-PRO M3 Adhesive may be applied using spray equipment designed for this purpose. The rate of application is approximately 1-1/2 gallons per square for squeegee application and 1-1/2 to 2-1/2 gallons per square for spray application. CAUTION: Using excessive amounts of cold adhesive may cause blistering or damage to the finished AWAPLAN membrane.

For TAM-PRO 856 Premium SBS Adhesive, the side and end laps must be set in adhesive or heat welded.
For TAM-PRO M3 Adhesive, it is recommended that the side and end laps be heat welded.

Use same technique as outlined in HOT ASPHALT APPLICATION for side and end laps. Use adhesive only in well-ventilated areas.

Alternatively, a cold process adhesive that meets the requirements of ASTM D3019, Type III may be used. Follow the manufacturer's application requirements.



AWAPLAN™

APPLICATION INSTRUCTIONS

FASTENING

For inclines of $\frac{3}{4}$ in. per ft. or greater, the AWAPLAN membrane shall be applied parallel (i.e. strap) to the slope of the roof and fastened in all end laps. Fasten the membrane at intervals of 6 in. across the top of the sheet. All fastening shall be done through flat metal caps or with nails with attached caps of a minimum 1 in. in diameter.

For fire resistance and wind uplift resistance rating information contact the Technical Services Department at 1-800-641-4691.

IMPORTANT

CAUTION: TAMKO MODIFIED ASPHALT PRODUCTS MUST NOT BE ALLOWED TO COME INTO CONTACT WITH COAL TAR PITCH OR TARRED FELT AT ANY POINT.

These are TAMKO's application instructions for this product for the roofing conditions described herein. Additional information concerning the proper installation of modified bitumen roofing systems is available in the current NRCA Roofing Manual – Membrane Roof Systems. If any variances are found, the TAMKO application instructions prevail. Specific information concerning this product may be obtained from TAMKO upon request. Questions concerning the use of this product which are not covered by these instructions or on the TAMKO web site should be addressed to TAMKO's Technical Services Department in Joplin, MO, 1-800-641-4691. These application instructions were current at the time of printing. To obtain a copy of the most current version of the application instructions, visit us online at tamko.com or call us at 1-800-641-4691.

TAMKO Building Products, Inc. is not liable or responsible for leaks or other matters which result in any way from failure to follow these manufacturer's instructions. AWAPLAN carries a 15-year product Limited Warranty. The Limited Warranty printed on this wrapper was current at the time of printing. To obtain a copy of the most current version of the Limited Warranty, visit us online at tamko.com or call us at 800-641-4691. The applicable Limited Warranty for this Product is the Limited Warranty that was current at the time of purchase. Failure to follow TAMKO's application instructions terminates all obligations of TAMKO under the Limited Warranty and all applicable implied warranties.

TAMKO application recommendations represent our best judgment based on experience to date but are subject to change and improvement as continued research and experience dictate. TAMKO reserves the right to alter, change or review the application instructions to meet specific job or climatic conditions, or both. However, TAMKO shall have no liability with respect to any supplemental advice or for variation from the recommended methods of application unless expressly set forth in writing and signed by the Corporate Director of Technical Systems.

Information included in this product data sheet was current at time of printing. To obtain a copy of the most current version of this product data sheet, visit us online at tamko.com or call us at 800-641-4691.

This product is covered by a 15-year Limited Warranty. For information regarding or a copy of TAMKO's Limited Warranty, contact your local TAMKO representative, visit us online at tamko.com, or call us at 800-641-4691.

tamko.com

Corporate	220 West 4th Street, Joplin, Missouri 64801	800-641-4691
Central District	220 West 4th Street, Joplin, Missouri 64801	800-641-4691
Northeast District	4500 Tamko Drive, Frederick, Maryland 21701	800-368-2055
Southeast District	2300 35th Street, Tuscaloosa, Alabama 35401	800-228-2656
Southwest District	7910 South Central Expressway, Dallas, Texas 75216	800-443-1834
Western District	5300 East 43rd Avenue, Denver, Colorado 80216	800-530-8868



©2015 TAMKO Building Products, Inc.

TAMKO®, TAMKO Glass-Base®, Tam-Ply IV® and Versa-Base® are registered trademarks and AWAPLAN is a trademark of TAMKO Building Products, Inc.