



# MIRAGRID 10XT

MIRAGRID® 10XT uniaxial geogrid is composed of high molecular weight, high tenacity polyester multifilament yarns woven in tension and finished with a PVC coating. MIRAGRID 10XT geogrid is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

MIRAGRID 10XT geogrid is used as soil reinforcement in MSE structures such as segmental retaining walls, precast modular block walls, wire faced walls, geosynthetic wrapped faced walls and steepened slopes. MIRAGRID 10XT is also used in MSE stabilized platforms for voids bridging, embankments on soft soils, landfill veneer stability, reducing differential settlement and for foundation seismic stability.

TenCate Geosynthetics Americas (A Solmax Company) is accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)).

MIRAFI 10XT meets Build America, Buy America Act, Pub. L. No. 117-58, div. G §§ 70901-52.

MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM AVERAGE ROLL VALUE MD
Tensile Strength @ Ultimate	ASTM D6637(Method B)	lbs/ft (kN/m)	10200 (148.8)
Tensile Strength @ 5% strain	ASTM D6637(Method B)	lbs/ft (kN/m)	3150 (46.0)
			MINIMUM ROLL VALUE
Creep Rupture Strength <sup>1</sup>	ASTM D5262/D6992	lbs/ft (kN/m)	7083 (103.3)
Long Term Design Strength <sup>2</sup>		lbs/ft (kN/m)	6133 (89.5)
PHYSICAL PROPERTIES		UNIT	ROLL SIZE
Roll Dimensions <sup>3</sup> (width x length)		ft (m)	12 x 200 (3.6 x 61) 12 x 1000 (3.6 x 305)
Roll Area		yd <sup>2</sup> (m <sup>2</sup> )	267 (220) 1333 (1114)
Estimated Roll Weight		lbs (kg)	223 (102) 1075 (490)

<sup>1</sup> 75-year design life based on NTPEP Report [REGEO-2016-01-067](#).

<sup>2</sup> Value based on Long Term Design Strength for sand, silt, clay.  $RF_{CR} = 1.44$ ;  $RF_{ID} = 1.05$ ;  $RF_D = 1.1$   
(Installation damage reduction factor for other soils available upon request)

<sup>3</sup> Special order roll lengths are available upon request.

365 South Holland Drive Pendergrass, GA 30567

Tel +1 706 693 2226 [www.solmax.com](http://www.solmax.com)



Solmax is not a design or engineering professional and has not performed any such design services to determine if Solmax's goods comply with any project plans or specifications, or with the application or use of Solmax's goods to any particular system, project, purpose, installation, or specification.  
FGS000026 ETQR33

