



# MIRAFI G200NC

MIRAFI® G200NC Drainage Composite is produced from a perforated, high compressive strength polymer core with an AASHTO M288 Class 2 nonwoven with elongation  $\geq 50\%$  filter geotextile bonded to both sides.

TenCate Geosynthetics Americas (A Solmax Company) is accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)).

MIRAFI G200NC meets Build America, Buy America Act, Pub. L. No. 117-58, div. G §§ 70901-52.

CORE MECHANICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL ROLL VALUE	
Thickness	ASTM D1777	in (mm)	0.4 (10.2)	
Compressive Strength	ASTM D1621	psf (kPa)	18,000 (862)	
Maximum Flow rate <sup>1</sup>	ASTM D4716	gal/min/ft (l/min/m)	21 (260)	

  

GEOTEXTILE MECHANICAL PROPERTIES AASHTO M288 CLASS 2 NONWOVEN	TEST METHOD	UNIT	MINIMUM AVERAGE ROLL VALUE	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs (N)	160 (712)	160 (712)
CBR Puncture Strength	ASTM D6241	lbs (N)	410 (1825)	
Trapezoid Tensile Strength	ASTM D4533	lbs (N)	70 (0.212)	

  

			MINIMUM ROLL VALUE	
Permittivity	D4491	sec <sup>-1</sup>	1.5	
Flow Rate	D4491	gal/min/ft <sup>2</sup> (l/min/m <sup>2</sup> )	110 (4481)	

  

PHYSICAL PROPERTIES	UNIT	TYPICAL ROLL VALUE
Roll Dimensions (width x length)	ft (m)	4 x 50 (1.2 x 15.2)
Roll Area	ft <sup>2</sup> (m <sup>2</sup> )	200 (18.6)
Estimated Roll Weight	lb (kg)	50 (22)

<sup>1</sup> In- plane flow rate measured at 172 kPa (3600 psf) compressive load and a gradient of 1.0

365 South Holland Drive Pendergrass, GA 30567

Tel +1 706 693 2226 [www.tencategeo.us](http://www.tencategeo.us)



Solmax is not a design or engineering professional and has not performed any such design services to determine if Solmax's goods comply with any project plans or specifications, or with the application or use of Solmax's goods to any particular system, project, purpose, installation, or specification.  
FGS000852 ETQR02

