



Mirafi® MTK

Mirafi® MTK is a self-adhering waterproofing membrane designed especially for pavement reflective crack control and as a moisture barrier to prevent water permeation or penetration through pavement surfaces and the subsequent damage that moisture causes in the roadway sub-base.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](https://www.gai-lap.com)).

MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM AVERAGE ROLL VALUE
Thickness	ASTM D1777 ²	mils (mm)	65 (1.7)
Grab Tensile Strength	ASTM D4632	lbs (N)	160 (712)
Grab Tensile Elongation	ASTM D4632	%	60
Puncture Strength	ASTM E154	lbs (N)	200 (890)
Permeance	ASTM E96, Method B	perms	0.05 (max)
Strip Tensile	ASTM D882	lbs/in (kN/m)	50 (8.8)
Strip Elongation	ASTM D882	%	50
Melting Point	STM D276	F° (C°)	325 (163)
Pliability	ASTM D146 ¼" Mandrel 180° @ -25° F	No cracks in fabric or rubberized asphalt	

PHYSICAL PROPERTIES	UNIT	TYPICAL ROLL VALUE				
Roll Dimensions (width)	in (m)	12(0.3)	18(0.5)	24(0.6)	36(0.9)	
Roll Dimensions (length)	ft (m)	200(61)	200(61)	100(30)	50(15.2)	
Roll Area	yd ² (m ²)	23(19)	17(14)	23(19)	17(14)	
Estimated Roll Weight	lbs (kg)	55	40	60	40	
Label Roll Color		WHITE				

¹ Testing performed on composite

² ½" Presser Foot

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Mirafi® is a registered trademark of Nicolon Corporation. Copyright © 2021 Nicolon Corporation. All Rights Reserved

FGS00009

ETQR18