





PETROTAC 4591

PETROTAC® 4591 is a self adhesive paving strip membrane geotextile, and will meet the following typical roll values when tested in accordance with the methos listed below PETROTAC 4591 is used as a strip membrane to treat local pavement distress and joints and cracks (effected over moderate cracks/joints¹. It is also used a s a bridge deck moisture barrier.

PETROTAC 4591 conforms to the property values listed below and meets the requirements of ASTM D-6153 for type III Bridge Deck Waterproofing Membrane Systems².

TenCate Geosynthetics Americas (A Solmax Company) is accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

PETROTAC 4591 meets Build America, Buy America Act, Pub. L. No. 117-58, div. G §§ 70901-52.

MECHANICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL ³
Strip Tensile	ASTM D-882	lbs/in (N/m)	75 (13,135)
Puncture Resistance	ASTM E-154	lbs (N)	200 (890)
Permeance – Perms	ASTM E-96 Method B		0.05 (max)
Pliability	ASTM D146 ¼" Mandrel 180° @ -25° F	No cracks in fabric or rubberized asphalt	
MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM ROLL VALUE
Asphalt Retention	ASTM D6140	gal/yd² (l/m²)	≥ 0.20 (0.91)
Melting Point	ASTM D276	F° (C°)	325 (163)
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	70
PHYSICAL PROPERTIES		UNIT	TYPICAL ROLL VALUE
Roll Dimensions (width x length)			12in x 108ft (.31 x 32.9)
			18in x 108ft (.46 x 32.9)
		in x ft (m)	24in x 108ft (.61 x 32.9)
			36in x 45ft (.91 x 13.7)
			48in x 50ft (1.22 x 15.2)
Roll Area			12 (10)
			18 (18)
		yd² (m²)	24 (20)
			15 (13)
			22 (19)
Estimated Roll Weight			44 (20)
			67 (30)
		lbs (kg)	89 (40)
			56 (25)
			82 (37)

¹Minimum temperature of 280° F of asphalt overlay suggested during installation.









²Property values listed above are effective 01/19/2021 and are subject to change without notice. values represent testing at time of manufacture.

³Values shown are in weaker principal direction.