

## Mirafi<sup>®</sup> TM14S

Mirafi® TM14S is a 3-dimensional, lofty synthetic, erosion control mat, which provides bare soil retention, vegetation nurturing and turf reinforcement. Mirafi® TM14S is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

PERFROMANCE PROPERTIES	TEST METHOD	UNIT	VALUE	
Overtopping Discharge (Q) <sup>1</sup>	Large Scale	CFS/ft² (Is/m²)	4.0 (1219)	
Manning's Coefficient <sup>2</sup>	Calculated	"n"	0.033	
MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM AVERAGE ROLL VALUE	
			MD	CD
Tensile Strength @ Ultimate	ASTM D6818	lbs/ft (kN/m)	3000 (43.8)	2400 (35.0)
			MINIMUM TEST VALUE	
UV Resistance (at 3000 hours)	ASTM D4355	% strength retained	95	
UV Resistance (at 6000 hours)	ASTM D4355	% strength retained	90	
UV Resistance (at 10000 hours)	ASTM D4355	% strength retained	80	
			TYPICAL ROLL VALUE	
Resiliency <sup>3</sup>	ASTM D6524	mils (mm)	330 (8.4)	
Thickness	ASTM D6525	mils (mm)	475 (1.21)	
			MAXIMUM ROLL VALUE	
			MD	CD
Tensile Elongation	ASTM D6818	%	50	50
Light Penetration	ASTM D6567	%	40	
PHYSICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL ROLL SIZE	
Mass Per Unit Area	ASTM D6566	oz/yd² (g/m²)	8.5 (288)	
Roll Dimensions (width x length)			12' x 75' (3.66m x 22.9m)	
Estimated Roll Weight			60 lbs (27 kg)	
Label Roll Color			White	

<sup>&</sup>lt;sup>1</sup> Based on 3:1 Bed Slope

PATENT # 8,252,705

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Mirafi\* is a registered trademark of Nicolon Corporation. Copyright © 2021 Nicolon Corporation. All Rights Reserved FGS000795
ETQR5







<sup>&</sup>lt;sup>2</sup> Higher Manning's Coefficient will result in reduced flow velocity.

 $<sup>^{3}</sup>$  Typical Resiliency Thickness reported in mils,  $\emph{Tf}$  per Section 9.5, ASTM D6524.