

# Thermafiber® FRF 114 & FRF 514



Milled mineral wool fibers are commonly used in brake pads and other friction components for cost-effective reinforcement strength and friction properties.



FRF fibers are used in the manufacturing of gaskets, paints, caulks, mastics and adhesives.



High-Performance Milled Fibers are easily poured and blended into batching systems.

## High-Performance Milled Fiber

- + Economical high-performance fiber and filler
- + Excellent reinforcement strength
- + Superior fire and heat resistance
- + Abrasion and friction properties
- + Increases viscosity of liquid and semi-liquid products
- + Available with water-absorbent and repellent surface treatments

Minimum  
**70%**  
Recycled  
Content



**Thermafiber**®



Made in the USA

# Thermafiber® FRF 114 & FRF 514

## Description:

THERMAFIBER High-Performance Milled Products provide a top quality mineral wool fiber with properties that enhance the performance of a host of products. These economical filler/reinforcement fibers retain their integrity at high temperatures and provide excellent wear resistance. FRF 514 is a standard milled product, while the new FRF 114 is further refined to provide a non-fibrous content of less than 5%.

## Typical End Uses:

Brake Shoes/Clutches	Wear resistance/abrasion
Cement Coatings	Reinforcement/filler
Plastics	Shape retention
Auto Gaskets	Heat resistance
Roofing Asphalt	Wear resistance/resilience
Paint	Viscosity modification

## Product Options:

Product	Finish	Treatment*	Bag Weight
FRF 114	Milled	S, A	50 lbs (22.7 kg)
FRF 514	Milled	S, A	50 lbs (22.7 kg)

\*Treatments can be added upon request. S = Silicone, A = Surfactant

## Technical Data:

Product	Non-Fibrous Content per ASTM C 1335 (% of weight)	Poured Density (pcf)	Tested to ASTM E 84	
			Flame Spread	Smoke Developed
FRF 114	< 5%	7.5 - 9.5	0	5
FRF 514	< 20%	8.2 - 10.5	0	5

Performance Characteristics	
Color	White to Gray
Density (Specific Gravity)	2.8-3.0 g/cc
Hardness	6.0 Mohs
Fiber Diameter	5 Microns, average
Fiber Diameter Range	1.73 -8.65 microns
Fiber Length	0.1-4.0 mm, average
Fiber Tensile Strength	80,000 psi
Fiber Tensile Modulus	1,500-5,000 kpsi
Refractive Index	1.62-1.64
Devitrification Temperature	1,550° F (843° C)
Melting Point <sup>1</sup>	Approximately 2,200° F (1,204° C)

<sup>1</sup>For continuous temperatures above 1,200° F, consult with your Thermafiber sales representative.

Chemical Composition	
Oxide	Percent by Weight
SiO <sub>2</sub>	38-46
Al <sub>2</sub> O <sub>3</sub>	9-12
CaO	31-40
MgO	8-15
Fe <sub>2</sub> O <sub>3</sub>	0-2

## Standards Compliance:

**ASTM E 136** Rated Non-combustible per NFPA Standard 220

## For Further Information:

For additional information about these or other Thermafiber products contact us at 1-888-834-2371 or visit our website [www.thermafiber.com](http://www.thermafiber.com).

## Notice:

THERMAFIBER, Inc. shall not be liable for incidental and consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instructions or for other than the intended use. THERMAFIBER liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing within thirty (30) days from date it was or reasonably should have been discovered.

## Submittal Approvals:

Project	
Approval	Date

