

# EXOAIR<sup>®</sup> AIR BARRIER MEMBRANES

## Self-Adhered Air & Vapor Membrane Comparison

Membrane	ExoAir 110	ExoAir 110AT
Adhesive	SBS Rubberized Asphalt	Butyl
Facer Composition	HDPE (High Density Polyethylene)	HDPP (High Density Polypropylene)
Facer Color	White with large green logo	White with small green logo & website
Mil Thickness	40 mils	22 mils
Puncture Resistance	49 lbf	52 lbf
Installation Temperature	40°F (4°C) and rising	20°F (-7°C) and rising
In-Service Temperature	Up to 158°F (70°C)	Up to 240°F (116°C)
Weight	68 lbs	39 lbs
Primer Required	Yes, ExoAir Primer	No
UV Exposure	30 days	12 months
NFPA 285 Tested Assembly	No, options with stone wool, please contact Technical Service	Yes, FWFO.EWS0010 & FWFO.EWS0019
Sealants adhere to facer	Dymonic 100 & Spectrem 1	Dymonic 100 & Spectrem 1
Stain of adjacent sealant	Yes, possible staining of sealant	No

