

We certify that ExoAir 110 as manufactured by Tremco Incorporated, Cleveland, Ohio has been tested against the following ASTM Standards and does conform to the specification requirements.

TYPICAL PHYSICAL PROPERTIES

| | |
|--|-----------------------|
| Air Leakage of Air Barrier Assemblies ASTM E2357 | 0.004cfm/sf |
| Air Permeance ASTM E2178-01 (NML) | No Measurable Leakage |
| Permeance ASTM E96B | 0.05 perms |
| Elongation (Membrane) ASTM D412 Die C | 250% |
| Tensile Strength ASTM D412 Die C (Membrane) | 500 psi |
| Tensile Strength (Film) ASTM D412 Die C | 5,000 psi |
| Puncture Resistance - Membrane ASTM E154 | 55 lbs |
| Pliability, 180° - 1" mandrel ASTM D1970 @ -25°F, -32°C | Pass |
| Moisture Absorption ASTM D570 | 0.1% |