



Tremco Commercial Sealants & Waterproofing
3735 Green Road
Beachwood, OH 44122
US: 800.852.9068
Canada: 800.363.3213
www.tremcosealants.com

We certify that ExoAir 120 as manufactured by Tremco Incorporated, Cleveland, Ohio has been tested against the following ASTM Standards and does conform to the specification requirements.

TYPICAL PHYSICAL PROPERTIES

Property Description

| | |
|-------------|--|
| Type | Polymer-modified emulsion |
| Color | Black |
| Solids | 62% |
| Density | 8.1 lbs/gal |
| Application | Airless spray/Roller |
| Cure Time | 16-24 hours (at 75°F (23°C) at 50% RH) |
| Thickness | Minimum 60 mils (wet) Minimum 40 mils (dry) |

Property Test Method Typical Values

| | | |
|---------------------------------------|------------------------------------|--------------------|
| Air Leakage of Air Barrier Assemblies | ASTM E2357 | Passed |
| Air Permeance | ASTM E2178-01 .00120 CCMC 07273 | L/s/m ² |
| Elongation | ASTM D412 Die C | 1500% |
| Nail Sealability | ASTM D1970 | Passed |
| Water Vapor Permeance | ASTM E96 | 0.08 |
| Maximum V.O.C. | | 65 grams/liter |