



Tremco Commercial Sealants & Waterproofing
 3735 Green Road
 Beachwood, OH 44122
 US: 800.852.9068
 Canada: 800.363.3213
 www.tremcosealants.com

We certify that ExoAir 130 has been tested against the following test methods/standards.

TYPICAL PHYSICAL PROPERTIES

Property	Test Method	Typical Values
Adhesion	ASTM C794	Concrete >16 lbf Aluminum >10 lbf Sheathing >8 lbf
Crack Bridging	ASTM C1305	Pass
Elongation	ASTM D412 Die C	346 %
Tensile Strength	ASTM D412 Die C	170 PSI
Water Immersion	ASTM D870	11.60%
Pliability, 180°, 1" (25mm) @ -29°F(-34°C) Low Temperature Flex	ASTM D1970 Section 7.6	Pass
Nail Sealability	ASTM D1970 Section 7.9	Pass
Water Vapor Permeance	ASTM E96 (Dry Cup)	<0.1 US Perm Applications*
28 Day Shore A Hardness	ASTM C661	30
Flame Spread	ASTM E84	15
Smoke Spread	ASTM E84	25
Cone Calorimeter	ASTM E1354	Data for EJ Analysis
Air Leakage – Material	ASTM E2178	<0.0005 L/sm ² <0.0001 cfm/ft ²
Air Leakage – Assembly	ASTM E2357	Pass
Fire Test of Assembly	NFPA 285	Pass

Property	Description
Type	UV Resistance Synthetic
Color	White
Solids	55%
Storage	Keep from freezing
Application Temperature	40° (4° C) and rising
Thickness	Minimum 70 mils (wet), 40 mils (dry)
Service Temperature	Intermittent exposure up to 240° F (116° C)

*Evaluated in a variety of conditions for specific assemblies. Please contact Tremco Sales or Technical Service for more information.