



Tremco Commercial Sealants & Waterproofing  
 3735 Green Road  
 Beachwood, OH 44122  
 US: 800.852.9068  
 Canada: 800.363.3213  
 www.tremcosealants.com

We certify that ExoAir 220 has been tested against the following test methods/standards.

### TYPICAL PHYSICAL PROPERTIES

Property	Test Method	Typical Values
Water Resistance	AATCC 127-2008	55 cm for 5 hours
Crack Bridging	ASTM C1305	Pass
Elongation	ASTM D412 Die C	900%
Tensile Strength	ASTM D412 Die C	325 psi
Nail Sealability	ASTM D1970, Section 7.9	Pass
Adhesion	ASTM D4541	Concrete 28 psi Sheathing 19 psi
Water Penetration Testing	ASTM E331	600 Pa (12.5 psf)
Air Permeance	ASTM E2178	0.0006 cfm/ft <sup>2</sup> (0.012 L/sm <sup>2</sup> ) 75 Pa (1.57 psf)
Air Leakage of Assembly	ASTM E2357	0.002 cfm/ft <sup>2</sup> (0.012 L/sm <sup>2</sup> ) 75 Pa (1.57 psf)
Assembly Evaluation of Fire Propagation Characteristics	NFPA 285	Successfully tested as par of a UL listed assembly
Property	Description	
Type	Polymer-modified emulsion	
Color	Black	
Solids	60%	
VOC	2 g/L	
Thickness	70 wet mils; 40 dry mils	
Storage	Keep from freezing	
Application Temperature	40° F (4° C) and rising	