

### Product Description

A spun-bonded polyester fabric consisting of a nonwoven fabric of continuous filament polyester fibers that are randomly arranged. These fibers are highly dispersed and thermally bonded at the filament junctions.

### Basic Uses

Tremco® Reinforcing Fabric is used to reinforce fluid-applied membranes in multi-lift applications.

### Availability

Immediately available from your local Tremco Sales Representative or Tremco Distributor. For Distributor locations visit [www.tremcosealants.com](http://www.tremcosealants.com).

### Packaging

84" x 675' (2.13 M x 206 M) roll

36" x 600' (0.91 m x 183 M) roll

12" x 600' (30 cm x 183 M) roll

6" x 600' (15 cm x 183 M) roll

### Warranty

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Product proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

## TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUES
Color		White
Weight		1.0 oz/y <sup>2</sup>
Thickness (Mil)		9 mil
Sheet Grab Tensile (lb - MD x XD)	ASTM D2523	21 lb x 17 lb
Trapezoid Tear (lb - MD x XD)	ASTM D2263	6 lb x 11 lb
Mullen Burst (psi)	ASTM D2523	22 psi

### 0816/REEMAYDS-BG

#### Tremco Commercial Sealants & Waterproofing

3735 Green Rd  
Beachwood OH 44122  
216.292.5000 / 800.321.7906

1451 Jacobson Ave  
Ashland OH 44805  
419.289.2050 / 800.321.6357

220 Wicksteed Ave  
Toronto ON M4H1G7  
416.421.3300 / 800.363.3213

1445 Rue de Coulomb  
Boucherville QC J4B 7L8  
514.521.9555

