



TECHNICAL DATA SHEET

TREMProof™ 560A

Self-adhesive waterproofing membrane.

PRODUCT DESCRIPTION

TREMproof 560A Waterproofing Membrane is a self-adhesive waterproofing membrane specifically designed for below-grade waterproofing. The membrane is composed of SBS modified bitumen with a cross-laminated, non-perforated polyethylene facer.

BASIC USES

Specifically designed for below-grade waterproofing, TREMproof 560A is ideal for:

- Poured concrete and CMU backfilled walls.
- Approved for use of Nudura® Insulated Concrete Forms.

FEATURES & BENEFITS

- Manufactured to a preset, uniform thickness that provides consistent and uniform coverage.
- Highly flexible material easily forms around corners and contours.

AVAILABILITY

Available immediately from your local Tremco Sales Representative or Distributor. For Distributor locations, visit <https://www.tremcosealants.com/>.

PACKAGING

Each roll of TREMproof 560A is securely held together with a self-adhesive band.

Roll Dimensions: 67 ft x 39 in (20.4 m x 1 m)

LIMITATIONS

- Ensure the surface is smooth, clean, dry, free from dirt and any other impurities.
- Membrane must be stored upright (standing vertically) in a cool, dry location (not in direct contact with the ground).
- Protect with a tarp to prevent exposure to direct sunlight until the membrane is ready to be used.
- Primer is required for application to poured concrete and CMU walls.
- Applied product should not be left uncovered to UV exposure longer than 30 days or covered with a protection course longer than 30 days.
- Not intended for use on continuous horizontal flat or sloped deck applications.
- A concrete curing time of 14 days at a temperature 60°F (16°C) or above is recommended prior to installation of the membrane.

WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit <https://www.tremcosealants.com/warranties/> for details.

TYPICAL PHYSICAL PROPERTIES		
PROPERTY	TEST METHOD	TYPICAL RESULTS
Thickness		60 mil (1.5 mm)
Dimensions		39" x 61' (1 x 18.6 m)
Surface		Cross laminated polyethylene
Service Temperature		-4°F to 167°F (-20°C to 75°C)
Application Temperature		41°F to 113°F (5°C to 45°C)
Tensile Strength, MD/CD	ASTM D882	45/48 N/mm ²
Elongation (Film), (MD/CD)	ASTM D882	230%/200%
Low Temperature Flexibility	ICC AC 48	Pass
Lap Adhesion	ASTM D1876	9 lbf/in (1576 N/m)
Water Absorption	ASTM D570	<0.1
Water Vapor Permeance	ASTM E96	Procedure B <0.01 perm
Crack bridging ability, 100 cycles, @ -26 °F (-32°C)	ASTM C1305	Pass
Resistance to hydrostatic head	ASTM D5385	Pass
Adhesion to Primed Concrete	ASTM D1000	7lbs/inch

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TP560A-DS/1124

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



tremcosealants.com | 800.321.7906



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122
800.321.7906 | tremcocpg.com