

Vulkem® 360NF - Sloping/Patching

Waterproofing Membrane

Product Description

Vulkem 360NF is a low odor, V.O.C. compliant, water-cured, rapid setting polyurethane product that possesses tenacious adhesion to clean and dry concrete, wood and metal.

Basic Uses

When mixed with aggregate, Vulkem 360NF can be used to slope decks and to fill in low and spalled concrete. Vulkem 360NF is compatible for use with Tremco topcoats as a pedestrian or traffic waterproof deck coating system. (See Tremco published application instructions for deck coatings.)

Availability

Immediately available from your local Tremco Sales Representative.

Sloping and Patching Application

Thoroughly mix Vulkem 360NF in original pail prior to adding water. Thoroughly mix 5 parts of Vulkem 360NF base with 1 part of water (by volume).

In a rotating-bucket mixer, begin adding sand to the mixed Vulkem 360NF until desired consistency is reached. Use 40-50 mesh silica sand or aluminum oxide for optimum workability. Trowel the mixture in the area to be filled or sloped. The following table provides a general guideline for use in high traffic areas.

SAND: 360NF MIX	@ 1/8" DEPTH	@ 1/4" DEPTH	@ 1/2" DEPTH
1:1	19 ft²/gal		
2:1		13 ft²/gal	6 ft²/gal
	Sloping	Sloping	
3:1 (<5% slope)	578 in³/gal	1/3 ft³/gal	
4:1 (<5% slope)	693 in ³ /gal	1/2 ft³/gal	

Packaging

Vulkem 360NF: 6-gal pails

Detailing and Coating

Treat all vertical to horizontal junctures with a one-inch cant bead of Dymonic 100 per Tremco coating application instructions. This includes areas that will be sloped with the Sand/Vulkem 360NF mixture. All Vulkem 360NF detail coats, patching and sloping areas may be recoated immediately with neat Vulkem 360NF base coat that has been mixed with water. See Tremco coating application instructions for installation of the complete coating system. The sloping/patching coat should be placed into a neat coat of Vulkem 360NF.

Limitations

- Do not apply to damp or contaminated surfaces.
- Use with adequate ventilation.
- Not recommended for high traffic or vehicular drive lanes, ticket spitters and turning radii.


Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES			
PROPERTY	TEST METHOD	VULKEM 360NF	
Flash Point	Set-A-Flash	185°F (85°C)	
% Solids (by Weight)	ASTM D1353	91%	
Drying Time @ 75°F, 50% RH	ASTM D1640	40 mil film, 6 to 12 hr	
Viscosity	Brookfield C&P	8000 to 10000 cps	
Elongation	ASTM D638	500%	
Tensile Strength	ASTM D638 @ 75°F	275 psi	
Hardness (Shore A)	ASTM D2240	40 to 50	
Adhesion (Peel Strength)	ASTM D903	Unprimed concrete, 45 pli, 100% cohesive failure	
Adhesion (Pull-Off)	ASTM D4541	350 psi	
Accelerated Aging	ASTM D573	No loss of elongation or tensile strength	



0417/V360NFSPDS-DC

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.



3735 Green Rd Beachwood OH 44122 216.292.5000 / 800.321.7906 1451 Jacobson Ave Ashland OH 44805 419.289.2050 / 800.321.6357

Tremco Commercial Sealants & Waterproofing 220 Wicksteed Ave Toronto ON M4H1G7 416.421.3300 / 800.363.3213

1445 Rue de Coulomb Boucherville QC J4B 7L8 514.521.9555