

POWERply® Endure® 320 Smooth

*Smooth Surfaced, High Tensile Bilaminate Reinforced
SBS Modified Bitumen Membrane*

FEATURES

SBS elastomer enhanced with Reactive Enhanced Terpolymer (RET) and Thermoplastic Polyurethane (TPU)

Antiwicking reinforcement

Roof ID™ chip embedded into each roll

UL Classified

BENEFITS

Improves durability of the modified bitumen blend

Blister resistance

Capability to identify the membrane and its QC data over the life of the roof system

Fire Protection



DESCRIPTION

POWERply Endure 320 Smooth is an asbestos free, smooth surfaced, modified bitumen membrane with fire resistant characteristics. It consists of specially selected bitumens, modified with SBS rubber along with RET and urethane high performance elastomers and reinforced with a high strength antiwicking polyester and fiberglass fabric. POWERply Endure 320 Smooth exceeds the requirements of ASTM D 6162, Type III, Grade S and CSA A123.23. POWERply Endure 320 Smooth roof systems are fire rated by Underwriters Laboratories for an exterior fire hazard. Refer to UL Roofing Materials and Systems Directory for applicable system configurations.

BASIC USES

POWERply Endure 320 Smooth is designed for roof membrane and flashing applications in cold process adhesives in multi-ply systems where a high strength, bilaminate reinforced, smooth surfaced membrane is desired.

PACKAGING

POWERply Endure 320 Smooth is a 2.2mm (87 mil) thick membrane. A roll covers 150 sq. ft. (13.9 m²) when applied, with roll dimensions of 39-3/8" x 51'6" (1m x 15.7m), and weighs approximately 97 lbs (44 kg).

POWERply Endure 320 Smooth is available in pallets only, with 20 rolls per pallet.

APPLICATION

According to job specifications, prepare the surface to be covered:

Replace areas of wet insulation, deteriorated deck and wood components.

Install roof insulation or nailed base sheet and multi-ply base ply system.

Plan the placement of POWERply Endure 320 Smooth to ensure that water flows over or along, but not against, the exposed edges. Starting at the low point of the roof, apply adhesive uniformly and continuously according to specifications. Embed the ply sheet(s) as specified. Avoid walking on plies during the placement.

For cold process applications, cut the POWERply Endure 320 Smooth in 16' to 18' (4.9 to 5.5 m) lengths, maximum. Allow lengths to relax for the following time length prior to installation:

Above 55° F (13° C): 30 minutes

Below 55° F (13° C): 60 minutes

Place the POWERply Endure 320 Smooth in a uniform and continuous application of adhesive. For cold process applications, press the membrane into the adhesive using a weighted roller 35-75 lbs. (16-34 kg.) to assure full contact of the back of the membrane into the adhesive..

Side laps 4" (102 mm) minimum; end laps 6" (152 mm) minimum. Hot air welding of laps is acceptable. Offset membrane laps from the base of the membrane laps. Stagger end laps at least 36" (914 mm). Install flashing as specified.

POWERply® Endure® 320 Smooth

LIMITATIONS

Special application procedures are required for application of POWERply Endure 320 Smooth in hot applied bitumen. Contact Tremco Roofing Product Group for additional information.

- Not intended to perform under ponding conditions. Positive drainage required.
- Not to be exposed to solvents, oils, or other contaminants harmful to asphaltic materials
- Backnail on roofs with slopes 2:12 (2" per foot) (16.6%) or greater
- Not intended for phased construction

PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUE	TEST METHOD
Thickness	2.2 mm (87 mils.)	ASTM D 5147
Tensile Strength @ 0°F (-18°C)	650 lbf/in MD (113 kN/M) 600 lbf/in XMD (105 kN/M)	ASTM D 5147
Elongation @ 0°F (-18°C)	6% MD 6%XMD	ASTM D 5147
Tensile Strength @ 77°F (25°C)	550 lbf/in MD (96 kN/M) 500 lbf/in XMD (87.5 kN/M)	ASTM D 5147
Elongation @ 77°F (25°C)	10% MD 10% XMD	ASTM D 5147
Tear Strength @ 77°F (25°C)	850 lbf MD (3779 N) 800 lbf XMD (3556 N)	ASTM D 5147
Low Temp Flex	-40° F (-40° C)	ASTM D 5147
Dimensional Stability	pass	ASTM D 5147
Compound Stability @ 215°F (102°C)	pass at 311° F (155° C)	ASTM D 5147

PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

TECHNICAL SUPPORT

Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



www.tremcoroofing.com
3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

220 Wicksteed Avenue
Toronto, Ontario, M4H 1G7
1.800.668.9879

Tremco Roofing and Building
Maintenance is part of Tremco
Construction Products Group.

Tremco is a US Registered trademark of Tremco CPG Inc.

The information provided on this data page supersedes all previous data concerning this product and its application. The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.