

Solargard® Fluoro-Prime

Acrylic metal primer

FEATURES

Provides maximum bond

VOC compliant

BENEFITS

- Prepares fluoropolymer/PVDF/Kynar coated metal substrates to receive SOLARGARD 6083
- Environmentally safe

DESCRIPTION

Solargard Fluoro-Prime is a water-based, acrylic metal primer formulated to provide adhesion of Solargard 6083 to fluoropolymer/PVDF/Kynar coated metal substrates.

BASIC USES

Solargard Fluoro-Prime is the recommended primer for use on fluoropolymer/PVDF/Kynar coated metal substrates prior to the application of Solargard 6083.

PACKAGING

4 gals (15.1 L) *Packaged in a 5 gallon pail
1 gal (3.7 L)

STORAGE LIFE

6 months in unopened container.

APPLICATION

Preparation: All surfaces are to be free of dirt, grease, oil, chalk, loose paint, rust, mortar, and other foreign matter which could prevent proper adhesion. This is best accomplished using a high pressure power wash of at least 2,000 psi. A surface cleaner shall be used to remove all grease or oily deposits.

Application: Solargard Fluoro-Prime can be applied by brush, roller or spray application. Mix thoroughly with a standard drill mixer for 5-10 minutes. A slight foam appearance is typical and will not affect application.

Solargard Fluoro-Prime can be applied using a low pressure hand compression sprayer (Hudson Type). Allow Solargard Fluoro-Prime to dry completely (minimum of one hour, depending on weather conditions).

When Solargard Fluoro-Prime has been applied longer than 72 hours prior to application of Solargard 6083, Solargard Fluoro-Prime is to be reapplied. All surfaces, which have been primed, must be clean and free of dirt, grease, oil and other foreign matter, which could prevent proper adhesion.

Refer to appropriate application specification for further information.

COVERAGE

Applied as a single coat; will cover approximately 200-250 sq. ft./gal. (6-8 wet mils). The age and composition of the surface to be coated may cause coverage to vary.

CLEAN UP

Soap & water. Promptly clean tools and equipment with soap and water. Cured primer can be cleaned with mineral spirits.

LIMITATIONS

- For industrial use only.
- Application temperature shall be above 50°F.
- Protect from freezing.
- Not intended for use in ponded areas.
- SOLARGARD FLUORO-PRIME must be top-coated with SOLARGARD 6083 within 72 hours.

LIMITATIONS (CONTINUED)

PHYSICAL PROPERTIES

MAINTENANCE

PRECAUTIONS

TECHNICAL SUPPORT

Solargard® FLUORO-PRIME

- Not intended to be used as a final surface coating.
- Do not apply when rain is imminent.

PROPERTY	TYPICAL VALUE	TEST METHOD
Density per Gallon	8.36 ± 0.2 lbs.	
Solids by Volume	5.50% ± 1%	
Solids by Weight	8.19% ± 1%	
Specific Gravity	1.002 ± 0.02	
VOC	< 50 g/L	

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



www.tremcoroofing.com
3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

50 Beth Nealson Drive
Toronto, Ontario M4H 1M6
1.800.668.9879

Tremco Roofing & Building
Maintenance is a part of the Tremco
Construction Products Group

Tremco is a US Registered trademark of Tremco Incorporated.

The information provided on this data page supersedes all previous data concerning this product and its application. The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.