

Solargard® 6083 Base Coat

Premium acrylic elastomeric roof coating

FEATURES

Excellent Weathering Performance

Highly Reflective (White)

Low Odor

Versatile

Color Availability

BENEFITS

- Solargard 6083 System with finish coat delivers excellent weathering and dirt pick-up resistance.

- Lowers rooftop temperatures, resulting in less stress and potential energy savings

- Perfect for odor-sensitive accounts

- Can be applied to many roofing substrates

- Wide range of standard colors, as well as, custom tint capabilities for finish coat

DESCRIPTION

Solargard 6083 is an acrylic elastomeric roof coating formulated to meet and/or exceed the standards as established in ASTM 6083 - Standard Specification for Liquid Applied Coating Used in Roofing.

BASIC USES

Solargard 6083 Base Coat is the first coat installed in a Solargard 6083 system, which is a system that waterproofs and weatherproofs a variety of roofing substrates including asphalt-based smooth BUR, metal, modified bitumen, and weathered single ply membranes.

PACKAGING

5 gal (18.9 L) pail, 53 gal (200.6 L) lined drums

COLOR

Off White

GRADE

Brush, Roller, Spray

STORAGE

12 months shelf life in unopened containers when properly stored.

DO NOT FREEZE

Recommended storage is indoors in a ventilated, dry area removed from heat, open flame, ignition sources and direct sunlight. Storage temperatures should range from 60-70°F (15-21°C) and must not drop below 32°F (0°C) or exceed 110°F (43°C).

On the job site, materials should remain on the pallet until use and be stored in a shaded, ventilated area. Materials should be covered with a light-colored, reflective tarp for protection against the elements. Allow for adequate air flow inside the pallets.

Shelf life could be affected if the product is not stored properly.

APPLICATION

Surface Preparation: Surface must be clean, dry, in sound condition, and free of dirt, debris, and contaminants. Rust must be abraded until it no longer exhibits flaking or chalking.

Existing wet roofing components must be identified and replaced. Deficient areas of existing system must be repaired. All repairs should be made with like materials matching the existing components and allowed to properly cure prior to application of liquid-applied products.

Allow new concrete to cure for a minimum of 28 days and until moisture, RH, and compressive strength values reach an appropriate level. Concrete surfaces must be shot-blasted to a an ICRI 3-6 surface profile.

Metal surfaces and coated metal including fluoropolymer/PVDF coatings such as Kynar® (Registered trademark of Arkema Inc.) and Hylar® (Registered trademark of Solvay Solexis Inc.) must be ground to clean bright metal free of rust and primed prior to application.

Solargard® 6083 Base Coat

APPLICATION CONTINUED

ROOF SUBSTRATES/ SURFACES APPLICATION CHART

COVERAGE RATES

Product Type	Product Name	BUR - Smooth	BUR - Gravel	Concrete	MB - Smooth	MB - Granule	Metal	Metal - Fluoropolymer	Single Ply	SPUF	Walls
Primer	See Chart	SP Primer 1/3 gal / SQ (5 wet mils)	N/A	N/A	SP Primer 1/3 gal / SQ (5 wet mils)	SP Primer 1/3 gal / SQ (5 wet mils)	Solargard Rust Primer WB ½ gal / SQ (8 wet mils)	Solargard Fluoro-Prime ½ gal / SQ (8 wet mils)	SP Primer ¼ gal / SQ (4 wet mils)	N/A	N/A
Detailing Product	Solargard 6083 Base Coat Solargard 6083 Finish Coat Solargard Acrylic Sealer Solargard Seam Sealer TremLasticS	3-Course: 30-65 In ft / gal	N/A	N/A	3-Course: 30-65 In ft / gal	3-Course: 30-65 In ft / gal	Solargard Seam Sealer Solargard Acrylic Sealer Back-Brush: 60-100 In ft / gal Fasteners: 200-250 / gal	Solargard Seam Sealer Solargard Acrylic Sealer Back-Brush: 60-100 In ft / gal Fasteners: 200-250 / gal	3-Course: 30-65 In ft / gal	N/A	N/A
Reinforcement	Permafab Rapid-Set Reinforcing Fabric (for use with TremLasticS)	Approx. 300 In ft / roll	N/A	N/A	Approx. 300 In ft / roll	Approx. 300 In ft / roll	Approx. 300 In ft / roll	Approx. 300 In ft / roll	Approx. 300 In ft / roll	N/A	N/A
Base Coat	Solargard 6083 Base Coat Solargard 6083 Finish Coat	1½ gals / SQ (24 wet mils)	N/A	N/A	1½ gals / SQ (24 wet mils)	1½ gals / SQ (24 wet mils)	1 gals / SQ (16 wet mils)	1 gals / SQ (16 wet mils)	1 gals / SQ (16 wet mils)	N/A	N/A
Top Coat	Solargard 6083 Finish Coat	1½ gals / SQ (24 wet mils)	N/A	N/A	1½ gals / SQ (24 wet mils)	1½ gals / SQ (24 wet mils)	1 gals / SQ (16 wet mils)	1 gals / SQ (16 wet mils)	1 gals / SQ (16 wet mils)	N/A	N/A

If the surface has a pre-existing coating, paint, or sealant, please contact Tremco for adhesion/compatibility testing and surface preparation recommendations.

Mixing:

Pails: Use a heavy duty corded power drill with Jiffy Mixer mixing blade. Mix until product is consistent in appearance and viscosity. Do not thin.

Drums: Use industrial drum mixing equipment to mechanically mix each container. Mix until product is consistent in appearance and viscosity. Do not thin.

Priming: Primers may be needed on specific substrates/surfaces prior to application. See the Roof Substrates/Surfaces Application Chart for recommended primers. Review the recommended primer product data sheet for specific product and application information.

Installation: Install product using one of the approved application methods evenly at the recommended coverage rate. Use wet mil gauges to monitor coverage rates throughout application.

Note: Coverage rates are listed at minimum recommended rates. The application surface can affect the necessary coverage rate. Additional surface area must be accounted for on applications over corrugated or standing seam metal substrates. Coverage may require an additional 15-25% depending on profile.

TEMPERATURE/WEATHER RECOMMENDATIONS

Min Ambient: 50°F (10°C)
Max Ambient: 110°F (43.3°C)
Min Surface: 50°F (10°C)
Max Surface: 130°F (54.4°C)

- Minimum temperatures must be rising following application
- Do not apply when dew point is within 5°F (2.7°C) of ambient temperatures
- Do not apply when precipitation, fog or dew is imminent prior to cure of the product
- Do not apply when temperatures could fall below 32°F (0°C) within 24 hours of application.

Skin Time: 70°F (21.1°C) / 50% RH - 6 hours
Recoat Time: Minimum 24 hours

General Guidelines

Component	Pressure	Tip Size	Flow Rate	Filters	Hose Type	WHIP	Product Temp
One-Component	1,500 psi	.035 - .045	1.6 - 2.6 gpm	Remove	High Pressure	¼" High Pressure	Ambient

- Must use heavy duty or industrial grade spray tips
- Properly clean and maintain spray equipment before, during and after use
- Equipment should be properly grounded during use

Soap & Water

CURE TIMES

SPRAY EQUIPMENT RECOMMENDATIONS

CLEAN UP

Solargard® 6083 Base Coat

LIMITATIONS

Not recommended for use over the following:

Roof Decks: Cementitious wood fiber, metal, poured-in-place gypsum, structural lightweight or lightweight insulating concrete, and wood decks (includes plywood, tongue and groove, etc.).

Products/Systems: Asphalt-based or coal tar gravel surfaced BUR systems, clay tile, expanded or extruded polystyrene insulation, shingles, silicone-based products, and tar-based products.

- Not for use under continuous immersion.

MAINTENANCE

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

TECHNICAL SUPPORT

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



Roofing & Building Maintenance

3735 Green Road
Beachwood, Ohio 44122

220 Wicksteed Avenue
Toronto, Ontario, M4H 1G7

www.tremcoroofing.com

1.800.852.6013

Tremco Roofing and Building
Maintenance is part of Tremco
Construction Products Group.

Tremco is a US Registered trademark of Tremco CPG Inc.

The information provided on this data page supersedes all previous data concerning this product and its application.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.